TITLE:

High-spin polycationic states of an alternate meta-para-linked oligoarylamine incorporating two macrocycles.

AUTHOR(S):

Sakamaki, Daisuke; Ito, Akihiro; Furukawa, Ko;
Kato, Tatsuhisa; Tanaka, Kazuyoshi

CITATION:

Sakamaki, Daisuke ...[et al]. High-spin polycationic states of an alternate meta-para-linked oligoarylamine incorporating two macrocycles.. Chemical communications (Cambridge, England) 2009, 2009(30): 4524-4526

ISSUE DATE:

2009-08-14

URL:

<http://hdl.handle.net/2433/123381>

RIGHT:

Chem. Commun., 2009, pp.4524-4526 - Reproduced by permission of The Royal Society of Chemistry (RSC); 許諾条件により本文は2010-09-01に公開; This is not the published version. Please cite only the published version.; この論文は出版社版ではありません。引用の際には出版社版をご確認ご利用ください。

High-spin polycationic states of an alternate *meta-para*-linked oligoarylamine incorporating two macrocycles†

Daisuke Sakamaki,^a Akihiro Ito,^{*a} Ko Furukawa,^b Tatsuhisa Kato,^c and Kazuyoshi Tanaka^a

Received (in XXX, XXX) 1st January 2009, Accepted 1st January 2009

First published on the web 1st January 2009

DOI: 10.1039/b000000x

5 **High-spin alignment for dicationic, tricationic, tetracationic, and hexacationic species of a *meta-para*-linked oligoarylamine was accomplished by incorporating cyclophane skeletons into the oligomer backbone.**

Poly(radical cation) form of poly(*m*-aniline) (Fig. 1(a)), the
10 position isomer of polyaniline as the well-known conductive
polymer, is anticipated to be a candidate of the ferromagnetic
polymers from the viewpoint of superdegeneracy among the
half-filled bands,¹ and has been investigated so far through the
15 direct polymerization study^{2–4} and the oligomer model
study.^{5–7} Afterwards, it has been widely accepted that the
semi-quinone radical cation of *para*-phenylenediamine (PD)
moiety is far more stable than the aminium radical cation as the
20 spin-containing unit in poly(*m*-aniline), and therefore, the
main focus has been shifted to the alternating *meta-para*-
isomers of polyaniline and/or oligoaniline.^{8–10} Recently,
Kulszewicz-Bajer and co-workers have conducted elaborate
work on the oxidized form of poly(*m-p*-aniline) (Fig. 1(b)),
and as a consequence, the generated spins in the polymer were
25 shown to be mainly uncoupled ($S = 1/2$) except for the
existence of minor triplet ($S = 1$) spin clusters.¹⁰ Furthermore,
their unfortunate results are also supported from our oligomer
model study.¹¹

Fig. 1 Poly(radical cation)s of (a) poly(*m*-aniline), (b) poly(*m-p*-aniline), and (c) cyclophane-containing poly(*m-p*-aniline).

On the other hand, we have demonstrated that the high-spin
alignment has been fulfilled for the macrocyclic oligomers of
poly(*m*-aniline) and/or poly(*m-p*-aniline), and hence, the
35 macrocyclic oligoanilines can be effectively utilized as the
promising high-spin building blocks to construct the two- and
three-dimensional multi-spin system.¹² In particular,
tetraaza[14]*m,p,m,p*-cyclophane has a definite molecular
structure, and moreover, can be feasibly derived to pure spin
40 triplet species by two-electron-oxidation.^{12a,13} In this context,
the introduction of the cyclophane moieties into the polymer
backbone may bring in good results to obviate the uncoupled

spin difficulty in the one-dimensional poly(*m-p*-aniline). As a
first step to verify the validity of the cyclophane-containing
poly(*m-p*-aniline) (Fig. 1(c)), we prepared a *meta-para*-linked
oligoarylamine **1** incorporating two cyclophane moieties,
which is comprised of a central linearly-linked moiety and
two peripheral cyclophane moieties.

As shown in Fig. 2, the frontier molecular orbitals (MO) are
50 predicted to be virtually six-fold quasi-degenerate non-
disjoint π -MOs,¹⁴ judging from the simple Hückel MO
calculation of a model compound.

Fig. 2 Schematic drawing of the frontier MOs for a model compound of **1**.

The target molecule **1** has been prepared from *N,N',N''*-
55 tris(4-anisyl)-1,3,5-benzenetriamine (**3**)¹⁵ and *N,N'*-di(4-
bromophenyl)-*N,N'*-di(4-anisyl)-1,3-benzenediamine (**4**)^{13b}
using a 2:3 ratio of substrates by performing the palladium-
catalyzed aryl amination reaction (Buchwald-Hartwig
reaction)¹⁶ in a one-pot manner (Scheme 1, ESI†).

Scheme 1 Synthesis of *meta-para*-linked oligoarylamine incorporating two tetraazacyclophane **1**.

As shown in Fig. S1(ESI†), the cyclic voltammogram of **1**
in CH_2Cl_2 showed six redox couples at -0.04 , $+0.08$, $+0.16$,
 $+0.26$, $+0.59$, and $+0.68$ V (vs. Fc/Fc^+), which tentatively

correspond to oxidation processes, 1^0 to 1^{2+} , 1^{2+} to 1^{3+} , 1^{3+} to 1^{4+} , 1^{4+} to 1^{6+} , 1^{6+} to 1^{10+} , and 1^{10+} to 1^{12+} , respectively, judging from the differential pulse voltammogram (Fig. S2, ESI†). This indicates that **1** is oxidizable up to dodecacation: as compared to the first and second oxidation potentials (−0.01 and +0.02 V) and the third and fourth oxidation potentials (+0.54 and 0.67 V) of tetraazacyclophane **2**,^{12c} the first 4 redox couples correspond to the generation of 6 semi-quinoidal PD radical cations, while the remaining 2 redox couples to the generation of 6 quinoidal PD dication to produce diamagnetic (*i.e.* spinless) species; in the first oxidation process, two electrons are removed simultaneously from the two peripheral tetraazacyclophane moieties, so as to reduce the electrostatic repulsions between the charged semi-quinoidal PD units; the subsequent two one-electron-oxidation processes take place from the central two PD units; finally, two electrons are removed furthermore simultaneously from the two peripheral tetraazacyclophane moieties to generate the hexa(radical cation) of **1**. This conjecture is in good accordance with the Hückel MO pictures having the six-fold quasi-degenerate frontier MOs including the doubly degenerate HOMOs (Fig. 2).

The UV-Vis-NIR spectral change during the course of the electrochemical oxidation of **1** was monitored by using an optically-transparent thin-layer electrochemical cell (Fig. 3). As the oxidation proceeds, three new bands appeared at 426, 605, and ~1100 nm. The broad band (~1100 nm) in the NIR region is considered to be the intervalence band between the aminium radical cation center and the neutral amine center, and is composed of two bands at ~1000 and ~1200 nm. On going from 1^{2+} to 1^{6+} , it was found that the intensity of the higher energy band (~1000 nm) was gradually strengthened as compared to that of the lower energy band (~1200 nm), suggesting the charge-localization in the higher oxidation states of **1**. When 1^{6+} is further oxidized, a new intense band at 810 nm grew with an isosbestic point at 892 nm, corresponding to the conversion of the semi-quinoidal PD radical cation moieties to the diamagnetic quinoidal PD dication ones.

Fig. 3 UV-Vis-NIR spectra of the stepwise electrochemical oxidation of **1** to dication 1^{10+} in $\text{CH}_2\text{Cl}_2/0.1 \text{ M } n\text{-Bu}_4\text{NBF}_4$ at 298 K.

Encouraged by the observed electrochemical multi-stage oxidation processes, we have measured the continuous wave

ESR (cw-ESR) spectra of 1^+ , 1^{2+} , 1^{3+} , 1^{4+} , and 1^{6+} in a rigid-glass of CH_2Cl_2 at 123 K.¹⁷ Each oxidized species were generated by adding 1 to 6 molar equivalents of tris(4-bromophenyl)aminium hexachloroantimonate¹⁸ at 195 K. As is often the case with the high-spin molecules possessing delocalized spin centers, however, neither the definitive fine-structure in the allowed resonance ($\Delta M_S = \pm 1$) nor the forbidden resonance ($\Delta M_S = \pm 2$) were detected (Fig. S3, ESI†).¹⁹ These results prompted us to measure the electron spin transient nutation (ESTN) measurements based on the pulsed ESR method (ESI†).²⁰

As shown in Fig. 4, the observed 2-dimensional ESTN (2D-ESTN) spectra clearly displayed the change of spin-multiplicity corresponding to the stepwise-oxidized species of **1**. The nutation frequency components observed at 5 K for each oxidation state of **1** are summarized in Table 1. Besides the unknown doublet impurity, the triplet and quartet signals were seen in 1^{2+} and 1^{3+} , strongly indicating the high-spin alignment among the semi-quinoidal PD radical cations generated from the peripheral cyclophane moieties and the central linearly-linked moiety. In the higher oxidation states, 1^{4+} and 1^{6+} , the competing intermediate spin states (*i.e.* triplet and/or quintet states) were also detected in addition to the predicted quintet and septet states, suggesting that the high-spin state is nearly degenerate with thermally accessible intermediate spin states. As a consequence of introduction of macrocycles, the hope of the high-spin organic polymers can be pinned on the *meta-para*-linked polyarylamines.

The present work was supported by Grant-in-Aids for Scientific Research (B) (20350065) from Japan Society for the Promotion of Science (JSPS). Thanks are due to the Research Center for Molecular-Scale Nanoscience, the Institute for Molecular Science for use of the pulsed ESR spectrometer.

Table 1 Spectral data of the 2D-ESTN spectroscopy for poly(radical cation)s of **1**

Species	Obsd. nutation frequency (in MHz)	Transition assignment
1^{2+}	24.8 ($\equiv \sqrt{2} \omega_{\text{doublet}}$)	$ 1, \pm 1\rangle \leftrightarrow 1, 0\rangle$
(doublet impurity)	18.0 ($= \omega_{\text{doublet}}$)	$ 1/2, +1/2\rangle \leftrightarrow 3/2, -1/2\rangle$
1^{3+}	34.3 ($\equiv \sqrt{3} \omega_{\text{doublet}}$)	$ 3/2, \pm 3/2\rangle \leftrightarrow 3/2, \pm 1/2\rangle$
	39.0 ($\equiv 2 \omega_{\text{doublet}}$)	$ 3/2, +1/2\rangle \leftrightarrow 3/2, -1/2\rangle$
(doublet impurity)	20.0 ($= \omega_{\text{doublet}}$)	$ 1/2, +1/2\rangle \leftrightarrow 3/2, -1/2\rangle$
1^{4+}	36.4 ($\equiv \sqrt{2} \omega_{\text{triplet}}$)	$ 2, \pm 2\rangle \leftrightarrow 2, \pm 1\rangle$
	44.5 ($\equiv \sqrt{3} \omega_{\text{triplet}}$)	$ 2, \pm 1\rangle \leftrightarrow 2, 0\rangle$
(competing triplet)	26.0 ($= \omega_{\text{triplet}}$)	$ 1, \pm 1\rangle \leftrightarrow 1, 0\rangle$
1^{6+}	44.4 ($\equiv \sqrt{3} \omega_{\text{triplet}}$)	$ 2, \pm 2\rangle \leftrightarrow 2, \pm 1\rangle$
	56.8 ($\equiv \sqrt{5} \omega_{\text{triplet}}$)	$ 2, \pm 1\rangle \leftrightarrow 2, 0\rangle$
	62.9 ($\equiv \sqrt{6} \omega_{\text{triplet}}$)	$ 2, \pm 1\rangle \leftrightarrow 2, 0\rangle$
(competing quintet)	34.0 ($= \sqrt{2} \omega_{\text{triplet}}$)	$ 2, \pm 2\rangle \leftrightarrow 2, \pm 1\rangle$
	44.0 ($= \sqrt{3} \omega_{\text{triplet}}$)	$ 2, \pm 1\rangle \leftrightarrow 2, 0\rangle$
(competing triplet)	25.0 ($= \omega_{\text{triplet}}$)	$ 1, \pm 1\rangle \leftrightarrow 1, 0\rangle$

Fig. 4 2D-ESTN spectra of **1** in CH_2Cl_2 at 5K after the addition of (a) 2 equiv., (b) 3 equiv., (c) 4 equiv., and (d) 6 equiv. of oxidant.

Notes and references

^a Department of Molecular Engineering, Graduate School of Engineering,
5 Kyoto University, Nishikyo-ku, Kyoto 615-8510, Japan. E-mail: aito@scl.
kyoto-u.ac.jp

^b Institute for Molecular Science, Myodaiji, Okazaki 444-8585, Japan

^c Department of Chemistry, Josai University, 1-1 Keyakidai, Sakado,
Saitama 350-0295, Japan

[†] Electronic Supplementary Information (ESI) available: Experimental
10 section and the electrochemical and ESR spectroscopic data. See
DOI: 10.1039/b000000x/

- 1 (a) N. Mataga, *Theor. Chim. Acta*, 1968, **10**, 372; (b) T. Hughbanks
and M. Kertesz, *Mol. Cryst. Liq. Cryst.*, 1989, **176**, 115; K.
15 Yoshizawa and R. Hoffmann, *Chem. Eur. J.*, 1995, **1**, 403.
- 2 (a) K. Yoshizawa, K. Tanaka and T. Yamabe, *Chem. Lett.* 1990,
1331; (b) T. Ishida and H. Iwamura, *Chem. Lett.*, 1991, 317; (c) K.
Yoshizawa, K. Tanaka, T. Yamabe and J. Yamauchi, *J. Chem. Phys.*,
1992, **96**, 5516; (d) K. Yoshizawa, A. Takata, K. Tanaka and T.
20 Yamabe, *Polym. J.*, 1992, **24**, 857; (e) K. Yoshizawa, A. Ito, K.
Tanaka and T. Yamabe, *Solid State Commun.*, 1993, **87**, 935; (f) A.
Ito, K. Ota, K. Tanaka, T. Yamabe and K. Yoshizawa,
Macromolecules, 1995, **28**, 5618.
- 3 (a) M. Baumgarten, K. Müllen, N. Tyutyulkov and G. Madjarova,
Chem. Phys., 1993, **169**, 81; (b) G. Madjarova, M. Baumgarten, K.
25 Müllen and N. Tyutyulkov, *Macromol. Theory Simul.*, 1994, **3**, 803.
- 4 (a) J. Louie and J. F. Hartwig, *Macromolecules*, 1998, **31**, 6737; (b) F.
E. Goodson, S. I. Hauck and J. F. Hartwig, *J. Am. Chem. Soc.*, 1999,
121, 7527.
- 5 (a) A. Ito, T. Saito, K. Tanaka and T. Yamabe, *Tetrahedron Lett.*,
1995, **36**, 8809; (b) A. Ito, T. Saito, K. Ota, T. Miura, Y. Misaki, K.
Tanaka and T. Yamabe, *J. Mater. Chem.*, 1998, **8**, 1799; (c) A. Ito, H.
Ino, K. Tanaka, K. Kanemoto and T. Kato, *J. Org. Chem.*, 2002, **67**,
491.
- 6 (a) K. Sato, M. Yano, M. Furuichi, D. Shiomi, T. Takui, K. Abe, K.
Itoh, A. Higuchi, K. Katsuma, Y. Shirota, *J. Am. Chem. Soc.*, 1997,
119, 6607; (b) M. Yano, A. Fujiwara, M. Tatsumi, M. Oyama, K.
Sato and T. Takui, *Polyhedron*, 2007, **26**, 2008.
- 7 R. J. Bushby, C. A. Kilner, N. Taylor and M. E. Vale, *Tetrahedron*,
40 2007, **63**, 11458.
- 8 (a) M. M. Wienk and R. A. J. Janssen, *J. Am. Chem. Soc.*, 1996,
118, 10626; (b) M. M. Wienk and R. A. J. Janssen, *J. Am. Chem. Soc.*,
1997, **119**, 4492; (c) M. P. Struijk and R. A. J. Janssen, *Synth. Met.*,
1999, **103**, 2287.
- 9 A. Ito, A. Taniguchi, T. Yamabe and K. Tanaka, *Org. Lett.*, 1999, **1**,
741.
- 10 (a) I. Kulszewicz-Bajer, M. Zagórska, I. Wielgus, M. Pawłowski, J.
Gosk and A. Twardowski, *J. Phys. Chem. B*, 2007, **111**, 34; (b) I.
Kulszewicz-Bajer, J. Gosk, M. Pawłowski, S. Gambarelli, D.
50 Djurado and A. Twardowski, *J. Phys. Chem. B*, 2007, **111**, 9421; (c)
M. Gałęcka, I. Wielgus, M. Zagórska, M. Pawłowski and I.
Kulszewicz-Bajer, *Macromolecules*, 2007, **40**, 4924.
- 11 A. Ito, H. Ino, Y. Hirao, A. Taniguchi, K. Kanemoto, T. Kato and K.
Tanaka, *Eur. J. Org. Chem.*, 2009, to be appeared.
- 12 (a) A. Ito, Y. Ono and K. Tanaka, *Angew. Chem. Int. Ed.*, 2000, **39**,
1072; (b) A. Ito, S. Inoue, Y. Hirao, K. Furukawa, T. Kato and K.
Tanaka, *Chem. Commun.*, 2008, 3242; (c) A. Ito, Y. Yamagishi, K.
Fukui, S. Inoue, Y. Hirao, K. Furukawa, T. Kato and K. Tanaka,
Chem. Commun., 2008, 6573.
- 13 (a) T. D. Selby and S. C. Blackstock, *Org. Lett.*, 1999, **1**, 2053; (b) S.
I. Hauck, K. V. Lakshmi and J. F. Hartwig, *Org. Lett.*, 1999, **1**, 2057;
60 (c) I. Kulszewicz-Bajer, V. Maurel, S. Gambarelli, I. Wielgus and D.
Djurado, *Phys. Chem. Chem. Phys.*, 2009, **11**, 1362.
- 14 W. T. Borden and E. R. Davidson, *J. Am. Chem. Soc.*, 1977, **99**, 4587.
- 15 Ng. Ph. Buu-Hoi, *J. Chem. Soc.*, 1952, 4346.
- 16 (a) J. P. Wolfe, S. Wagaw, J. F. Marcoux and S. L. Buchwald, *Acc.*
Chem. Res., 1998, **31**, 805; (b) J. F. Hartwig, *Acc. Chem. Res.*, 1998,
31, 852; (c) J. F. Hartwig, *Angew. Chem. Int. Ed.*, 1998, **37**, 2046; (d)
A. R. Muci and S. L. Buchwald, *Top. Curr. Chem.*, 2002, **219**, 133.
- 17 The present poly(radical cation)s were found to be far more stable
70 than the oxidized oligo(*m*-aniline)s, which immediately decompose at
room temperature or lower temperatures. For instance, about 80 % of
the hexacation of **1** survive in solution after 1 hr at room temperature,
judging from the ESR intensity.
- 18 F. A. Bell, A. Ledwith and D. C. Sherrington, *J. Chem. Soc.*, 1969,
2719.
- 19 W. Weltner, Jr., *Magnetic Atoms and Molecules*, Dover, New York,
1989.
- 20 (a) J. Isoya, H. Kanda, J. R. Norris, J. Tang and M. K. Brown, *Phys.*
80 *Rev. B*, 1990, **41**, 3905; (b) A. V. Astashkin and A. Schweiger, *Chem.*
Phys. Lett., 1990, **174**, 595.