TITLE:

Photocatalytic reduction of CO₂ using H₂ as reductant over ATaO₃ photocatalysts (A=Li, Na, K)

AUTHOR(S):

Teramura, Kentaro; Okuoka, Shin-ichi; Tsuneoka, Hideo; Shishido, Tetsuya; Tanaka, Tsunehiro

---

CITATION:

Teramura, Kentaro ...[et al]. Photocatalytic reduction of CO₂ using H₂ as reductant over ATaO₃ photocatalysts (A=Li, Na, K). Applied Catalysis B: Environmental 2010, 96(3-4): 565-568

ISSUE DATE:

2010-06-07

URL:

<http://hdl.handle.net/2433/128766>

RIGHT:

© 2010 Elsevier B.V.; This is not the published version. Please cite only the published version.; この論文は出版社版ではありません。引用の際には出版社版をご確認ご利用ください。

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
1 / 21

Photocatalytic Reduction of CO₂ using H₂ as Reductant over ATaO₃ photocatalysts (A = Li, Na, K)

Correspondence authors

Dr. Kentaro Teramura

Kyoto University Pioneering Research Unit for Next Generation, Kyoto University,
Kyoto 615-8510, Japan

Tel: +81-75-585-6095 Fax: +81-75-585-6096

E-mail address: kentaro.teramura@kupru.iae.kyoto-u.ac.jp

and

Professor Tsunehiro Tanaka

Department of Molecular Engineering, Graduate School of Engineering, Kyoto
University, Kyoto 615-8510, Japan

Tel: +81-75-383-2558 Fax: +81-75-383-2561

E-mail address: tanakat@moleng.kyoto-u.ac.jp

List of the authors

Kentaro Teramura^{a,*}, Shin-ichi Okuoka^b, Hideo Tsuneoka^b, Tetsuya Shishido^b,
Tsunehiro Tanaka^{b,*}

Affiliation and full postal address

a. Kyoto University Pioneering Research Unit for Next Generation, Kyoto University,

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
2 / 21

Kyoto 615-8510, Japan

- b. Department of Molecular Engineering, Graduate School of Engineering, Kyoto
University, Kyoto 615-8510, Japan

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
3 / 21**Abstract**

ATaO₃ (A = Li, Na, K) compound oxides exhibit photocatalytic activity for the reduction of CO₂ in the presence of H₂. Only CO gas was generated over all samples under photoirradiation. The photocatalytic activity was higher in the order corresponding to KTaO₃, NaTaO₃ and LiTaO₃ (LiTaO₃ > NaTaO₃ > KTaO₃). The order of the photocatalytic activities was consistent with that of the E_g (optical gap) values. After 24 h of photoirradiation, the amount of evolved CO reached 0.42 μmol·g⁻¹ over LiTaO₃. TPD experiments indicated that the broad peak which is assigned to chemisorbed CO₂ gas was observed at 573 K in the case of LiTaO₃. On the contrary, there was no peak in the spectra of NaTaO₃ and KTaO₃. The amount of evolved CO gas almost strongly depends on amount of chemisorbed CO₂ in the case of ATaO₃ (A = Li, Na, K). In addition, the photocatalytic activity increased with increasing the calcination temperature of LiTaO₃. This means that a smooth charge separation in a LiTaO₃ photocatalyst and chemisorption of CO₂ on the surface contribute to effective reduction of CO₂ in the presence of H₂.

Introduction

Recently, many countries that have approved the ratification of the Kyoto Protocol are enforcing strict regulations on carbon dioxide (CO₂) emission to meet international environmental standards. These countries are reducing CO₂ emission in many different ways, for example, by storage in the ground and sea, absorption into various functionalized materials, and large-scale forestation. However, it is important to develop the technique to chemically convert CO₂ into harmless compounds or other chemical products in the future. Chemical fixation of CO₂ in the presence of a heterogeneous photocatalyst is a promising method for converting it into other carbon sources such as carbon monoxide (CO), formaldehyde (HCHO), formic acid (HCOOH), methanol (CH₃OH), and methane (CH₄)[1]. In the 1980s, the effect of H₂O as a reductant on heterogeneous photocatalysts used for the photocatalytic reduction of CO₂ attracted considerable interest[2, 3].

We have found that CO is generated as a result of the photocatalytic reduction of CO₂ in the presence of H₂ or CH₄ as a reductant over ZrO₂[4-9], Rh/TiO₂[10, 11], MgO[12, 13], and Ga₂O₃[14]. With the exception of Rh/TiO₂, these solid materials exhibit the properties of solid base catalysts; therefore, CO₂ can be adsorbed on the surface of these materials. We have insisted on the importance of CO₂ adsorption on the surface because this makes CO₂, which is a stable and linear molecular, into an active species which provides abundant reactivity for the photocatalytic reduction of CO₂. As mentioned above, it was reported that the photocatalytic reduction CO₂ in the presence of H₂ proceeds over many simple oxides such as ZrO₂, MgO, and Ga₂O₃. However, there is no report that a compound oxide exhibits photocatalytic activity for the

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
5 / 21

reduction of CO₂. In the field of water splitting, many compound oxides are known to function as an effective photocatalyst. Among them, Kudo et al.[15, 16] reported that La doped NaTaO₃ shows incredible photocatalytic activity for overall water splitting. In this study, we first found that ATaO₃ (A = Li, Na, K) as a compound oxide is a candidate of photocatalyst for the reduction of CO₂.

Experimental section

ATaO₃ (A = Li, Na, K) samples used in this study were synthesized by a conventional solid state reaction (SSR) method. A stoichiometric mixture of Ta₂O₅ and A₂CO₃ (A = Li, Na, K) was calcinated at 1373 K for 20 h in the atmosphere in a programmable box furnace. A 5mol% excess of A₂CO₃ (A = Li, Na, K) was used to counteract loss of alkali as an oxide vapor during the heating circle. X-ray diffraction pattern (XRD) of an ATaO₃ (A = Li, Na, K) photocatalyst was measured by a Rigaku Multi Flex powder X-ray diffractometer. Kr adsorption isotherm was obtained using a BELSORP 28SA-SP system supplied by the BEL Japan Inc. The specific surface area was calculated from Kr adsorption isotherm of ATaO₃ (A = Li, Na, K) using the Brunauer-Emment-Teller (BET) method because the specific surface area is too small to be estimated by N₂ adsorption isotherm. Scanning electron microscope (SEM) images were obtained on a Hitachi S-4700 scanning electron microscope. UV-Vis diffuse reflectance (UV-Vis. DR) spectra were obtained using a JASCO Corporation V-670 diffused reflectance spectrometer with an integrating sphere at room temperature. BaSO₄ was used as a standard reflection sample. Temperature programmed desorption (TPD) profile was recorded by a TPD-1-AT instrument supplied by the BEL Japan Inc.

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
6 / 21

The photocatalytic reduction was carried out in a closed circulating system connected to a vacuum line. 2.0 g of ATaO₃ (A = Li, Na, K) was spread on the flat bottom (50 φ) of a quartz reactor (dead space: 150 mL). The catalyst sample was heated and evacuated at 673 K and then treated with O₂ (80 kPa) for 60 min, followed by evacuation for 2 h at the same temperature. The purified CO₂ (150 μmol) as a substrate and H₂ (50 μmol) as a reductant were admitted to the reactor after the pretreatment. The ATaO₃ (A = Li, Na, K) sample was illuminated throughout a range of wavelength from the bottom of the reactor with a 200 W Hg-Xe lamp (SAN-EI ELECTRIC CO., LTD, UVF-204S Type C). The reaction temperature increased to 303 K after photoirradiation because of heat of the light source. The analysis of products was performed with TCD gas chromatograph (Shimadzu GC-8A) equipped with a column packed with active carbon and with helium (He) as a carrier gas.

Results and Discussion

The prepared ATaO₃ (A = Li, Na, K) powders were qualitatively analyzed by some conventional method of analysis for a photocatalyst (XRD, SEM, and UV-Vis. spectroscopy). Figure 1 shows the XRD patterns of ATaO₃ (A = Li, Na, K). The peak assigned to impurities did not appear in all XRD patterns. All of ATaO₃ consist of corner-sharing TaO₆ octahedra with ilmenite (LiTaO₃) and perovskite (NaTaO₃ and KTaO₃) like structures. The morphology of synthesized ATaO₃ (A = Li, Na, K) was observed by SEM as shown in Figure 2. All prepared samples had fine primary particles with an average diameter of 1-3 μm. The BET specific surface area of ATaO₃ (A = Li, Na, K) estimated by the Kr adsorption isotherm are 0.28, 0.10, and 0.10 m²·g⁻¹,

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
7 / 21

respectively. The UV-Vis. DR spectra of ATaO₃ (A = Li, Na, K) were obtained after converting reflection coefficient, R to $F(R_\infty)$ by Kubelka-Munk function, $F(R_\infty) = (1-R^2)/2R$ as shown in Figure 3. Generally, E_g (optical gap) values are derived from optical absorption spectra and diffuse reflectance spectra. In the case of Davis-Mott's method, the E_g values are derived from the equation following $[F(R_\infty) \cdot h\nu] \propto (h\nu - E_g)^n$, where $n = 2, 3, 1/2$ and $3/2$ for indirect allowed, indirect forbidden, direct allowed, and direct forbidden transitions, respectively. The E_g values of ATaO₃ (A = Li, Na, K) are estimated to 4.9, 4.1 and 3.7 eV by Davis-Mott's method with $n = 1/2$ (direct allowed)[17, 18].

Figure 4 shows the amount of evolved CO gas for the photocatalytic reduction of CO₂ in the presence of H₂ as a reductant over ATaO₃ (A = Li, Na, K) after 24 h of photoirradiation. We obviously confirmed that the reaction does not proceed in the absence of ATaO₃ or in the dark. The photocatalytic reduction of CO₂ proceeded over all ATaO₃ (A = Li, Na, K) samples. CO gas was evolved over all ATaO₃ (A = Li, Na, K) samples under photoirradiation and the other compounds (for example, HCOOH, HCHO, CH₃OH, and CH₄) were not produced in the gas phase. LiTaO₃ exhibits the highest activity in the ATaO₃ (A = Li, Na, K) samples. The photocatalytic activity was higher in the order corresponding to KTaO₃, NaTaO₃ and LiTaO₃ (LiTaO₃ > NaTaO₃ > KTaO₃). Amount of evolved CO gas over LiTaO₃ was eight times higher than that over KTaO₃. No product was observed over LiTaO₃ under photoirradiation $\lambda > 310$ nm using a UV-29 cut-off filter. Therefore, the electron transition between band gap energy is concerned in the photocatalytic reduction of CO₂ over LiTaO₃. The order of the photocatalytic activities was consistent with that of the E_g (optical gap) values as

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
8 / 21

described above. Kato and Kudo[15] concluded that the conduction band levels and the transferring excited energy contribute to photocatalytic activities of naked alkali tantalate photocatalysts and a surface area is not an important factor for overall water splitting because a LiTaO₃ photocatalyst showed the highest activity for overall water splitting among the naked alkali tantalate photocatalysts prepared in the presence of excess alkali and the order of the activities was LiTaO₃ > NaTaO₃ > KTaO₃. In our case, it is expected that the conduction band levels and the transferring excited energy influence the photocatalytic activity for the photocatalytic reduction of CO₂.

It was reported that solid base materials such as ZrO₂, MgO, CaO, Al₂O₃ and Ga₂O₃ which possess base sites on the surface exhibit photocatalytic activity for the photocatalytic reduction of CO₂ in the presence of H₂. CO₂ is able to be adsorbed on the base site easily, and then the conformation of a linear CO₂ molecule undergoes a great change. The adsorption of CO₂ contributes to the photocatalytic reduction of CO₂. Figure 5 shows the CO₂-TPD spectra ($m/z = 44$) of ATaO₃ (A = Li, Na, K) after pretreatment at 673 K and CO₂ adsorption at room temperature. A broad peak was observed at 573 K in the case of LiTaO₃, although there was no peak in the spectra of NaTaO₃ and KTaO₃. It is known that Li₂CO₃ is decomposed at 900 K (heat decomposition). In fact, we obtained the same result as the reference. Accordingly, the peak at 573 K is assigned to not decomposition of Li₂CO₃ but desorption of a CO₂ molecule adsorbed on LiTaO₃. The adsorption isotherm of CO₂ was observed after pretreatment at 673 K as shown in Figure 6a. After that, CO₂ was adsorbed on LiTaO₃ after evacuation at room temperature again as shown in Figure 6b. These adsorption isotherms are expressed as a function of the Langmuir adsorption isotherm. Amount of

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
9 / 21

adsorbed CO₂ was saturated when equilibrium pressure is more than 0.96 kPa. The subtraction between panels a and b was 0.75 $\mu\text{mol}\cdot\text{g}^{-1}$. The equilibrium pressure was about 2.7 kPa when 150 μmol of CO₂ was admitted to the reactor with 2.0 g of LiTaO₃ after the pretreatment. Thus, the amount of CO₂ physisorbed and chemisorbed on LiTaO₃ corresponds to 2.76 and 1.50 μmol under the reaction condition, respectively. Figure 7 demonstrates the amount of chemisorbed CO₂ on ATaO₃ (A = Li, Na, K). Amount of evolved CO gas almost depends on amount of chemisorbed CO₂ in the case of ATaO₃ (A = Li, Na, K) as well as the other reported materials such as ZrO₂, MgO, and Ga₂O₃.

We have reported that MgO exhibits the best photocatalytic activity for the reduction of CO₂ in the presence of H₂ as a reductant under UV light irradiation. It is clarified that the photoactive site of MgO is compatible with the CO₂ adsorption site. The amount of evolved CO gas over MgO (12.9 $\mu\text{mol}\cdot\text{g}^{-1}$) is thirty-first higher than that over LiTaO₃ (0.42 $\mu\text{mol}\cdot\text{g}^{-1}$) under 24 h of photoirradiation using the same light source. On the other hand, amount of chemisorbed CO₂ gas over MgO (130 $\mu\text{mol}\cdot\text{g}^{-1}$) is enormous as compared to that on LiTaO₃ (0.75 $\mu\text{mol}\cdot\text{g}^{-1}$)[12, 13]. Accordingly, the photoactive site of LiTaO₃ would be able to reduce adsorbed CO₂ to CO under photoirradiation effectively. We speculate that a smooth charge separation in LiTaO₃ contributes to the effective photocatalytic reduction of CO₂ in the presence of H₂. Generally, the high crystallinity of photocatalyst is known to provide the smooth charge separation. In our case, the photocatalytic activity increased with increasing the calcination temperature of LiTaO₃ despite decreasing the specific surface area as shown in Figure 8. The BET specific surface area of LiTaO₃ calcined at 973, 1173, and 1373 K

are 1.1, 0.77, and 0.28 m²·g⁻¹, respectively. On the other hand, all peaks in the XRD pattern of LiTaO₃ became sharper and higher with increasing the calcination temperature. In this study, we found that some compound oxides such as ATaO₃ (A = Li, Na, K) exhibit the photocatalytic activity for the photocatalytic reduction of CO₂ in the presence of H₂ and expanded the capability of the effective CO₂ photocatalytic reduction system using high crystallinity of LiTaO₃; however the observed activity is very low. High specific surface area of LiTaO₃ is now under investigation and preparation.

Conclusion

It is found that photocatalytic reduction of CO₂ using H₂ as a reductant proceeds over ATaO₃ (A = Li, Na, K). CO gas was evolved over all ATaO₃ (A = Li, Na, K) samples under photoirradiation and the other compounds were not produced in the gas phase. LiTaO₃ exhibits the highest activity in the ATaO₃ (A = Li, Na, K) samples. The photocatalytic activity was higher in the order corresponding to KTaO₃, NaTaO₃ and LiTaO₃ (LiTaO₃ > NaTaO₃ > KTaO₃). The order of the photocatalytic activities was consistent with that of the E_g (optical gap) values. Amount of evolved CO gas almost depends on amount of chemisorbed CO₂ in the case of ATaO₃. The photoactive site of LiTaO₃ would be able to capture CO₂ in the gas phase and reduce the adsorbed CO₂ to CO under photoirradiation effectively as compared to that of NaTaO₃ and KTaO₃.

Acknowledgement

This study was partially supported by the Program for Improvement of Research

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
11 / 21

Environment for Young Researchers from Special Coordination Funds for Promoting Science and Technology (SCF), commissioned by the Ministry of Education, Culture, Sports, Science and Technology (MEXT) of Japan, and a Grant-in-Aid for Young Scientists (B), 19760542, 2007, from the Japan Society for the Promotion of Science (JSPS).

References and Notes

- [1] M.M. Halmann, Chemical Fixation of Carbon Dioxide, CRC Press, Inc., United States of America, 1993.
- [2] M. Halmann, Nature (London, United Kingdom) 275 (1978) 115-116.
- [3] T. Inoue, A. Fujishima, S. Konishi, K. Honda, Nature (London, United Kingdom) 277 (1979) 637-638.
- [4] Y. Kohno, T. Tanaka, T. Funabiki, S. Yoshida, Chem. Commun. (1997) 841-842.
- [5] Y. Kohno, T. Tanaka, T. Funabiki, S. Yoshida, Chem. Lett. (1997) 993-994.
- [6] Y. Kohno, T. Tanaka, T. Funabiki, S. Yoshida, J. Chem. Soc. Faraday Trans. 94 (1998) 1875-1880.
- [7] Y. Kohno, T. Tanaka, T. Funabiki, S. Yoshida, Phys. Chem. Chem. Phys. 2 (2000) 2635-2639.
- [8] Y. Kohno, T. Tanaka, T. Funabiki, S. Yoshida, Phys. Chem. Chem. Phys. 2 (2000) 5302-5307.
- [9] S. Yoshida, Y. Kohno, Catal. Surv. Jpn. 4 (2000) 107-114.
- [10] Y. Kohno, H. Hayashi, S. Takenaka, T. Tanaka, T. Funabiki, S. Yoshida, J.

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
12 / 21

Photochem. Photobiol. A-Chem. 126 (1999) 117-123.

[11] Y. Kohno, T. Yamamoto, T. Tanaka, T. Funabiki, J. Mol. Catal., A: Chem. 175 (2001) 173-178.

[12] Y. Kohno, H. Ishikawa, T. Tanaka, T. Funabiki, S. Yoshida, Phys. Chem. Chem. Phys. 3 (2001) 1108-1113.

[13] K. Teramura, T. Tanaka, H. Ishikawa, Y. Kohno, T. Funabiki, J. Phys. Chem. B 108 (2004) 346-354.

[14] K. Teramura, H. Tsuneoka, T. Shishido, T. Tanaka, Chem. Phys. Lett. 467 (2008) 191-194.

[15] H. Kato, A. Kudo, J. Phys. Chem. B 105 (2001) 4285-4292.

[16] H. Kato, K. Asakura, A. Kudo, J. Am. Chem. Soc. 125 (2003) 3082-3089.

[17] E.A. Davis, N.F. Mott, Philo. Mag. 22 (1970) 903-922.

[18] X. Gao, I.E. Wachs, J. Phys. Chem. B 104 (2000) 1261-1268.

Figure captions

- Figure 1 XRD patterns of ATaO₃ (A = Li, Na, K): (a) LiTaO₃, (b) NaTaO₃ and (c) KTaO₃
- Figure 2 SEM images of ATaO₃ (A = Li, Na, K) : (a) LiTaO₃, (b) NaTaO₃ and (c) KTaO₃
- Figure 3 UV-Vis. DR spectra of ATaO₃ (A = Li, Na, K) : (a) LiTaO₃, (b) NaTaO₃ and (c) KTaO₃
- Figure 4 Amount of evolved CO gas for the photocatalytic reduction of CO₂ in the presence of H₂ as a reductant over ATaO₃ (A = Li, Na, K) after 24 h of photoirradiation
- Figure 5 CO₂-TPD spectra (m/z = 44) of ATaO₃ (A = Li, Na, K) after pretreatment at 673 K and CO₂ adsorption at room temperature
- Figure 6 The adsorption isotherms of CO₂ on LiTaO₃ (a) after pretreatment at 673 K, and then (b) after adsorption of CO₂ and evacuation at room temperature.
- Figure 7 Amount of chemisorbed CO₂ on ATaO₃ (A = Li, Na, K).
- Figure 8 Amount of evolved CO gas for the photocatalytic reduction of CO₂ in the presence of H₂ as a reductant over LiTaO₃ calcined at (a) 1373, (b) 973, and (c) 773 K after 24 h of photoirradiation.

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
14 / 21

Figure 1

Teramura et al.
Photocatalytic reduction of CO_2 over ATaO_3
15 / 21

Figure 2

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
16 / 21

Figure 3

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
17 / 21

Figure 4

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
18 / 21

Figure 5

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
19 / 21

Figure 6

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
20 / 21

Figure 7

Teramura et al.
Photocatalytic reduction of CO₂ over ATaO₃
21 / 21

Figure 8