TITLE:

Unconventional Superconductivity and Antiferromagnetic Quantum Critical Behavior in the Isovalent-Doped $\text{BaFe}_{\{2\}}(\text{As}_{\{1-x\}}\text{P}_{\{x\}})_{\{2\}}$

AUTHOR(S):

Nakai, Y.; Iye, T.; Kitagawa, S.; Ishida, K.; Ikeda, H.; Kasahara, S.; Shishido, H.; Shibauchi, T.; Matsuda, Y.; Terashima, T.

CITATION:

Nakai, Y. ...[et al]. Unconventional Superconductivity and Antiferromagnetic Quantum Critical Behavior in the Isovalent-Doped $\text{BaFe}_{\{2\}}(\text{As}_{\{1-x\}}\text{P}_{\{x\}})_{\{2\}}$. Physical Review Letters 2010, 105(10): 107003.

ISSUE DATE:

2010-09

URL:

<http://hdl.handle.net/2433/128772>

RIGHT:

© 2010 The American Physical Society

Unconventional Superconductivity and Antiferromagnetic Quantum Critical Behavior in the Isovalent-Doped $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$

Y. Nakai,^{1,2,*} T. Iye,^{1,2} S. Kitagawa,^{1,2} K. Ishida,^{1,2} H. Ikeda,^{1,2} S. Kasahara,³ H. Shishido,³
T. Shibauchi,¹ Y. Matsuda,¹ and T. Terashima³

¹Department of Physics, Graduate School of Science, Kyoto University, Kyoto 606-8502, Japan

²TRIP, JST, Sanban-cho Building, 5, Sanban-cho, Chiyoda, Tokyo 102-0075, Japan

³Research Center for Low Temperature and Materials Sciences, Kyoto University, Kyoto 606-8502, Japan

(Received 17 May 2010; published 2 September 2010)

Spin dynamics evolution of $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ was probed as a function of P concentration via ^{31}P NMR. Our NMR study reveals that two-dimensional antiferromagnetic (AF) fluctuations are notably enhanced with little change in static susceptibility on approaching the AF phase from the superconducting dome. Moreover, the magnetically ordered temperature θ deduced from the relaxation rate vanishes at optimal doping. These results provide clear-cut evidence for a quantum-critical point, suggesting that the AF fluctuations associated with the quantum-critical point play a central role in the high- T_c superconductivity.

DOI: 10.1103/PhysRevLett.105.107003

PACS numbers: 74.70.Xa, 74.25.nj, 74.40.Kb

Conventional phonon-mediated superconductivity occurs in a normal metal that is well accounted for by Landau's Fermi-liquid (FL) theory. However, the standard FL theory appears to break down above T_c in many "exotic" superconductors characterized by unconventional pairing rather than a conventional uniform-sign s -wave pairing function, such as in the heavy fermion materials and cuprates. The origin of the anomalous metallic properties, often referred to as "non-Fermi-liquid" (nFL) behavior, has triggered growing interest in quantum-critical points (QCPs) that provide a route towards nFL behavior [1]. The quantum-critical fluctuations induced by suppression of antiferromagnetic (AF) order [2] are suggested to mediate the Cooper pairing in exotic superconductors, in an analogous way to phonons in conventional superconductors [3].

Newly discovered iron-pnictide high- T_c superconductivity also appears where antiferromagnetism is suppressed via chemical substitution or pressure [4]. The existence of a QCP in iron pnictides has been suggested [5–9]. Spin-fluctuation-mediated superconductivity associated with the suppression of the antiferromagnetism is one likely scenario [10], but the identification of the mechanism is far from settled [11,12]. The difficulty in examining the superconducting (SC) mechanism could arise from complexity in the materials that can lead to ambiguous interpretations, e.g., nonuniversal SC gap functions and limited sample quality. It is thus essential to find a suitable model system to examine the mechanism of superconductivity.

The isovalent-doped $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ can be used as such a model system. It has the highest T_c (31 K) among iron-pnictide superconductors known to have line nodes in the SC gap [13–15]. Clarifying the mechanism that produces its high- T_c nodal gap is thus very important. Since isovalent P-doping is not expected to add carriers [16], $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ maintains the compensation condition; i.e., the volume of the hole Fermi surfaces (FSs) is equal to

that of the electron FSs. Very clean single crystals of $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ allow de Haas-van Alphen experiments that are the most precise technique to determine FSs, revealing the detailed electronic structure for comparison with band calculations [17,18]. The quasiparticle effective mass increases towards the maximum T_c , signaling the enhancement of electron-electron correlation. Such an increase in the quasiparticle mass as well as nFL behavior inferred from resistivity measurements [16,19] can be expected when the system is in proximity to a QCP. However, direct evidence for the existence of a QCP remains lacking in $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$.

Here, we report the normal-state spin dynamics in $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ for $0.2 \leq x \leq 0.64$ investigated by ^{31}P NMR measurements. NMR is highly sensitive to low-energy spin fluctuations and can give information of the dynamical magnetic susceptibility. Samples of a mosaic of single crystals were prepared as described elsewhere [16]. The de Haas-van Alphen experiments observed signals in single crystalline samples from the same batch as $x = 0.41, 0.56$, and 0.64 , indicating the excellent quality of our samples [17]. The high quality of our samples is also suggested by the sharp SC transitions [16]. ^{31}P -NMR spectra ($^{31}\gamma/2\pi = 17.237$ MHz/T) were obtained by sweeping frequency in a fixed magnetic field of 4.12 T. The Knight shift K was determined with respect to the reference material H_3PO_4 . The ^{31}P nuclear spin-lattice relaxation rate T_1^{-1} was determined by fitting the time dependence of spin-echo intensity after saturation of nuclear magnetization to a theoretical $I = 1/2$ curve with a single component of T_1 .

Figure 1(a) displays ^{31}P NMR spectra obtained from the $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ crystals. Each ^{31}P NMR spectrum consists of a single line, ruling out microscopic inhomogeneity caused by P substitution. K , which measures the effective field at the nucleus produced by electrons, is described as $K = K_{\text{spin}} + K_{\text{chem}}$; K_{spin} is the spin part of K and is related

FIG. 1 (color online). P substitution evolution of (a) ^{31}P NMR spectra and (b) ^{31}P Knight shift (3K) determined at the spectral peak, obtained in a mosaic of the single crystals at 4.12 T. (b) The arrows indicate the chemical shift K_{chem} (see text). The abrupt decrease in 3K at low temperatures is due to the onset of superconductivity. Inset: 3K vs $(T_1T)^{-1/2}$ at 270 K for different P concentrations x .

to the uniform spin susceptibility $\chi(\mathbf{q} = 0)$, which is proportional to the density of states at the Fermi energy $N(E_F)$. K_{chem} is the chemical shift, which is unrelated to $\chi(\mathbf{q} = 0)$, and is estimated to be $\sim 0.018\%$ as follows. Since no obvious AF fluctuations were detected by NMR at high temperatures as seen in Fig. 2, it would be a good approximation to assume that $(T_1T)^{-1/2}$ is proportional to $N(E_F)$ at high temperatures, i.e., to assume that the usual Korringa relation holds at 270 K. Based on the plot of $(T_1T)^{-1/2}$ against K at 270 K for different x shown in the inset of Fig. 1, we can estimate K_{chem} as the intercept. The obtained K_{chem} is $0.018 \pm 0.019\%$, indicating that K_{spin} accounts for 86% of the observed Knight shift for $x = 0.33$. Note that this K_{chem} would be a reasonable value, since the chemical shift for ^{31}P in many diamagnetic insulators is of the order of some hundreds of ppm, which is comparable to this K_{chem} [20]. By assuming $K_{\text{spin}} \propto \chi(\mathbf{q} = 0) = \mu_B^2 N(E_F)$, the P-substitution dependence of K_{spin} at 270 K suggests that the change in $N(E_F)$ would be at most 10% for $x \leq 0.64$, which is quantitatively consistent with the result of our band calculation discussed below.

FIG. 2 (color online). The ^{31}P nuclear spin-lattice relaxation rate divided by temperature $(T_1T)^{-1}$ for $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ at 4.12 T. Solid lines represent fits to $(T_1T)^{-1} = a + b(T + \theta)^{-1}$ (see text). As AF fluctuations are suppressed as inferred from the suppression of $(T_1T)^{-1}$, T_c (denoted by arrows) also decreases. Inset: Fitting parameters of $(T_1T)^{-1}$. The fitting parameters a and b are plotted against P concentration x . The a and b weakly depend on x , but θ shows a strong x dependence [see Fig. 3]. The small value of θ at $x = 0.33$ ($\theta \sim 0$) are insensitive to the fitting parameters of a and b .

Band-structure calculations by local-density-approximation were performed for nonspin-polarized BaFe_2As_2 and BaFe_2P_2 , using the WIEN2K package in the APW + local orbital basis [21]. In addition, to obtain systematic changes of the electronic band structure for $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$, we performed the local-density-approximation calculations for three virtual materials with linearly-interpolated $z = z_0(1 - x) + z_1x$: (i) BaFe_2As_2 with fixed $(a, c) = (a_0, c_0)$, (ii) BaFe_2As_2 with linearly interpolated $(a, c) = [a_0(1 - x) + a_1x, c_0(1 - x) + c_1x]$, and (iii) BaFe_2P_2 with fixed $(a, c) = (a_1, c_1)$, where $a_{0(1)}$, $c_{0(1)}$, and $z_{0(1)}$ are the experimental values for the crystallographic parameters of BaFe_2As_2 (BaFe_2P_2) [16,22]. $N(E_F)$ barely changes for $x < 0.5$, and then decreases for $x > 0.5$ (see supplementary information [23]). Such behavior is consistent with our Knight shift results.

As shown in Fig. 1(b), K is almost temperature independent for $x \leq 0.56$, and that the absolute value of K in the normal state decreases only slightly upon P substitution. These data indicate that P substitution does not produce significant changes in $\chi(\mathbf{q} = 0)$ and $N(E_F)$. This is in stark contrast to carrier-doped iron-pnictide superconductors; in electron-doped $\text{Ba}(\text{Fe}_{1-y}\text{Co}_y)_2\text{As}_2$, the Knight shift data indicate that $N(E_F)$ of non-SC $y = 0.26$ is approximately 50% that of $y = 0.08$ with the maximum T_c of 26 K [6]. Such drastic effects on $N(E_F)$ via electron-doping is expected from the characteristic band structure [24]; the calculated $N(E_F)$ rapidly changes near E_F with a negative gradient, resulting in a rapid decrease of $N(E_F)$ with

electron doping. Large changes in FSs via charge-carrier doping thus necessarily involve dramatic modification in the $N(E_F)$ and Fermi-surface nesting resulting in changes in spin fluctuations. In addition to possible changes in T_c due to the modification of spin excitation spectrum [6], drastic changes in $N(E_F)$ can also affect severely T_c [25], and the suggested giant magnetoelastic coupling may lead to further suppressions of T_c [26]. Therefore, the decrease in $N(E_F)$ as well as the suppression of spin fluctuations should be taken into account for the interpretation of possible changes in T_c for electron-doped $\text{Ba}(\text{Fe}_{1-y}\text{Co}_y)_2\text{As}_2$. In contrast, the nearly unperturbed K_{spin} by isovalent P doping demonstrates that $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ is an ideal model system to test the relevance of spin fluctuations to superconductivity.

Significant low-energy AF fluctuations are probed near the maximum T_c via T_1^{-1} . $(T_1T)^{-1}$ is described by the wave-vector average of the imaginary part of the dynamical susceptibility $\chi''(\mathbf{q}, \omega_0)$, i.e., $(T_1T)^{-1} \propto \sum_{\mathbf{q}} |A(\mathbf{q})|^2 \times \chi''(\mathbf{q}, \omega_0)/\omega_0$ where $A(\mathbf{q})$ represents the hyperfine coupling between ^{31}P nuclear spins and the surrounding electrons, and ω_0 is NMR frequency. The Korringa law $T_1TK^2 = \text{const}$ generally holds in a FL state, but is inapplicable to $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ near the AF phase since Curie-Weiss (CW) behavior is observed in $(T_1T)^{-1}$ [see Fig. 2]. For $x = 0.33$, $(T_1T)^{-1}$ increases significantly down to T_c whereas the Knight shift is constant. These $(T_1T)^{-1}$ and K data demonstrate convincingly that AF fluctuations with finite $\mathbf{q}$ continue to grow down to T_c at optimal doping [14].

The AF fluctuations in $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ are enhanced significantly as the P concentration is reduced towards the maximum T_c ($x \approx 0.33$), as evidenced by the rapid increase in $(T_1T)^{-1}$ from conventional FL behavior at $x = 0.64$ [where $(T_1T)^{-1}$ and K are almost constant]. The crossover from FL to CW behavior in $(T_1T)^{-1}$ correlates perfectly with the change in the resistivity results [16]; As the system evolves from a Fermi liquid ($x = 0.71$) towards the maximum T_c ($x = 0.33$) near the AF phase, the temperature dependence of the resistivity changes from T^2 to T linear, one hallmark of nFL behavior. The exponent of the temperature dependence of the resistivity is shown as a contour plot in Fig. 3(a). Specifically, the CW behavior of $(T_1T)^{-1}$ and the T -linear resistivity at $x = 0.33$ can be explained by the existence of two-dimensional (2D) AF spin fluctuations in the theory of nearly AF metals [27]. Indeed, the evolution of the AF spin excitations measured by $(T_1T)^{-1}$ upon P substitution can be fit consistently by the equation expected from the same theory [27], $(T_1T)^{-1} = a + b(T + \theta)^{-1}$ [see solid lines in Fig. 2]. Such 2D AF fluctuations were experimentally observed in the parent BaFe_2As_2 via neutron scattering experiments [28]. According to band calculations [13], substantial 2D AF fluctuations can be generated by the interband spin excitations between the multiple FSs predominantly derived from Fe d electrons.

FIG. 3 (color online). Temperature—P concentration phase diagram of $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$. T_c , T_s , and T_N denote the SC, orthorhombic-tetragonal, and AF transition temperatures, respectively. (a) Shades (colors) represent the exponent, $\alpha = d(\ln \Delta \rho_{ab})/d(\ln T)$, at zero magnetic field for the resistivity curves in Ref. [25], where $\Delta \rho_{ab} = \rho_{ab} - \rho_{ab}(T \rightarrow 0 \text{ K})$. (b) The triangles represent θ obtained by fitting $(T_1T)^{-1}$ data to the equation, $(T_1T)^{-1} = a + b(T + \theta)^{-1}$ (error bars are within the symbol size). T -linear resistivity, suggesting quantum-critical behavior, is observed in proximity to a magnetic instability signaled by $\theta \approx 0$ at $x = 0.33$. These quantum-critical fluctuations are found to correlate with the enhancement of the effective mass as denoted by the pentagons (taken from Ref. [17]).

Our central finding in $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ is that the 2D AF fluctuations of a quantum-critical nature have a clear correlation with the enhancement of quasiparticle effective mass and T_c as summarized in Fig. 3. We found that the Weiss temperature θ obtained from the fitting increases with P substitution and becomes almost zero near $x = 0.33$ where the maximum T_c is achieved. $\theta = 0 \text{ K}$ implies that the dynamical susceptibility probed by the $(T_1T)^{-1}$ measurement diverges at absolute zero, or that the magnetic correlation length continues to increase down to $T = 0 \text{ K}$. Our result thus strongly suggests the presence of an AF QCP near the maximum T_c in proximity to the AF phase boundary. As the P concentration is varied towards optimal doping ($x \sim 0.33$) from $x = 0.64$ where the FL state is observed, the magnetic fluctuations become dramatically enhanced as θ decreases. Importantly, the quasiparticle mass and T_c increase as θ approaches 0 K. This strongly suggests that the AF quantum-critical fluctuations lead to strong mass renormalization and unconventional supercon-

ductivity. Our systematic NMR measurements, which are compared with transport measurements, thus provide the first evidence that the quasiparticle mass enhancement is strongly coupled to the AF quantum-critical fluctuations in iron-pnictide superconductors as previously observed in heavy fermion systems [29]. Furthermore, since $N(E_F)$ generally correlates with T_c in conventional BCS superconductors, the enhancement of T_c with approaching the QCP from the overdoped side cannot be accounted for by a nearly unperturbed $N(E_F)$, demonstrating clearly that superconductivity in $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$ is tuned predominantly by the AF fluctuations. Therefore, we conclude that the 2D AF quantum-critical fluctuations are likely to play a central role in the occurrence of unconventional superconductivity in $\text{BaFe}_2(\text{As}_{1-x}\text{P}_x)_2$.

Previous NMR measurements also indicated that there is a strong connection between low-energy spin fluctuations and superconductivity in 122 [14], 111 [30], and 11 iron-based superconductors [31]. These suggest that the relevance of spin fluctuations to the high- T_c superconductivity is universal despite the nonuniversal gap structure. The strong connection would be naturally understood if one considers the superconductivity observed near magnetic phase and the well-nested hole and electron Fermi surfaces. By contrast, we reported that the connection is relatively weaker in $\text{LaFeAs}(\text{O}_{1-x}\text{F}_x)$ [32]. Such a weak link may originate from much lower T_c of 26 K in $\text{LaFeAs}(\text{O}_{1-x}\text{F}_x)$ than that of $R\text{FeAs}(\text{O}_{1-x}\text{F}_x)$ ($R = \text{Ce}, \text{Pr}, \text{Sm}, \text{etc.}$). However, it remains unresolved whether spin fluctuations are also important for high- T_c superconductivity in the 1111 system with T_c exceeding 50 K, since magnetic rare-earth atoms R hinder quasiparticle excitations responsible for superconductivity [33]. Therefore, examinations of the connection between magnetic fluctuations and superconductivity of high- T_c 1111 iron pnictides would be crucial for establishing general view of iron-pnictide superconductivity.

We thank K. Kitagawa, Y. Ihara, D.C. Peets, and Y. Maeno for experimental support and discussion. We also grateful to K. Kuroki, H. Kontani, Q. Si, and S. Fujimoto for theoretical discussions. This work was supported by Grants-in-Aid for Scientific Research on Innovative Areas “Heavy Electrons” (No. 20102006) from MEXT, for the GCOE Program “The Next Generation of Physics, Spun from Universality and Emergence” from MEXT, and for Scientific Research from JSPS.

*nakai@scphys.kyoto-u.ac.jp

- [1] H. v. Löhneysen *et al.*, *Rev. Mod. Phys.* **79**, 1015 (2007); G.R. Stewart, *Rev. Mod. Phys.* **73**, 797 (2001); P. Gegenwart, Q. Si, and F. Steglich, *Nature Phys.* **4**, 186 (2008); P. Coleman and A.J. Schofield, *Nature (London)* **433**, 226 (2005).
- [2] S. Sachdev, *Quantum Phase Transitions* (Cambridge University Press, Cambridge, England, 1999).
- [3] N.D. Mathur *et al.*, *Nature (London)* **394**, 39 (1998); P. Monthoux, D. Pines, and G.G. Lonzarich, *Nature (London)* **450**, 1177 (2007).
- [4] Y. Kamihara *et al.*, *J. Am. Chem. Soc.* **130**, 3296 (2008).
- [5] J.-H. Chu *et al.*, *Phys. Rev. B* **79**, 014506 (2009).
- [6] F.L. Ning *et al.*, *Phys. Rev. Lett.* **104**, 037001 (2010).
- [7] C. de la Cruz *et al.*, *Phys. Rev. Lett.* **104**, 017204 (2010).
- [8] J. Dai, Q. Si, J.-X. Zhu, and E. Abrahams, *Proc. Natl. Acad. Sci. U.S.A.* **106**, 4118 (2009).
- [9] S. Kawasaki *et al.*, *Supercond. Sci. Technol.* **23**, 054004 (2010).
- [10] I.I. Mazin, D.J. Singh, M.D. Johannes, and M.H. Du, *Phys. Rev. Lett.* **101**, 057003 (2008); K. Kuroki *et al.*, *Phys. Rev. Lett.* **101**, 087004 (2008); A.V. Chubukov, D.V. Efremov, and I. Eremin, *Phys. Rev. B* **78**, 134512 (2008); H. Ikeda, *J. Phys. Soc. Jpn.* **77**, 123707 (2008); S. Graser *et al.*, *New J. Phys.* **11**, 025016 (2009).
- [11] H. Kontani and S. Onari, *Phys. Rev. Lett.* **104**, 157001 (2010).
- [12] I. Mazin and J. Schmalian, *Physica C (Amsterdam)* **469**, 614 (2009).
- [13] K. Hashimoto *et al.*, *Phys. Rev. B* **81**, 220501 (2010).
- [14] Y. Nakai *et al.*, *Phys. Rev. B* **81**, 020503 (2010).
- [15] J.S. Kim *et al.*, *Phys. Rev. B* **81**, 214507 (2010).
- [16] S. Kasahara *et al.*, *Phys. Rev. B* **81**, 184519 (2010).
- [17] H. Shishido *et al.*, *Phys. Rev. Lett.* **104**, 057008 (2010).
- [18] J. Analytis, J.-H. Chu, R. McDonald, S.C. Riggs, and I. Fisher, *arXiv:1002.1304*.
- [19] S. Jiang *et al.*, *J. Phys. Condens. Matter* **21**, 382203 (2009).
- [20] G.C. Carter, L.H. Bennett, and D.J. Kahan, *Metallic Shifts in NMR (Progress in Materials Science)* (Pergamon Press, Oxford, 1977), Vol. 20.
- [21] P. Blaha, K. Schwarz, G.K.H. Madsen, D. Kvasnicka, and J. Luitz, *WIEN2K, An Augmented Plane Wave Plus Local Orbitals Program for Calculating Crystal Properties* edited by K. Schwarz (Techn. Universitat Wein, Austria, 2001).
- [22] M. Rotter *et al.*, *Phys. Rev. B* **78**, 020503(R) (2008).
- [23] See supplementary material at <http://link.aps.org/supplemental/10.1103/PhysRevLett.105.107003> for P doping dependence of $N(E_F)$.
- [24] D.J. Singh and M.-H. Du, *Phys. Rev. Lett.* **100**, 237003 (2008).
- [25] E.Z. Kuchinskii, I.A. Nekrasov, and M.V. Sadovskii, *arXiv:1004.0801*.
- [26] T. Yildirim, *Physica C (Amsterdam)* **469**, 425 (2009).
- [27] T. Moriya, Y. Takahashi, and K. Ueda, *J. Phys. Soc. Jpn.* **59**, 2905 (1990).
- [28] K. Matan *et al.*, *Phys. Rev. B* **79**, 054526 (2009).
- [29] H. Shishido *et al.*, *J. Phys. Soc. Jpn.* **74**, 1103 (2005).
- [30] L. Ma *et al.*, *arXiv:1005.1448*; P. Jeglic *et al.*, *Phys. Rev. B* **81**, 140511 (2010); Z. Li *et al.*, *J. Phys. Soc. Jpn.* **79**, 083702 (2010).
- [31] T. Imai *et al.*, *Phys. Rev. Lett.* **102**, 177005 (2009); S. Masaki *et al.*, *J. Phys. Soc. Jpn.* **78**, 063704 (2009); Y. Shimizu *et al.*, *J. Phys. Soc. Jpn.* **78**, 123709 (2009); C. Michioka *et al.*, *arXiv:0911.3729*.
- [32] Y. Nakai *et al.*, *J. Phys. Soc. Jpn.* **77**, 073701 (2008); Y. Nakai *et al.*, *New J. Phys.* **11**, 045004 (2009); S. Kitagawa *et al.*, *Phys. Rev. B* **81**, 212502 (2010).
- [33] H. Yamashita *et al.*, *Physica C (Amsterdam)* (in press).