TITLE:

Rheological properties of concentrated solutions of galactomannans in an ionic liquid

AUTHOR(S):

Horinaka, Jun-ichi; Yasuda, Ryosuke; Takigawa, Toshikazu

CITATION:

Horinaka, Jun-ichi ...[et al]. Rheological properties of concentrated solutions of galactomannans in an ionic liquid. Carbohydrate Polymers 2012, 89(4): 1018-1021

ISSUE DATE:

2012-08

URL:

<http://hdl.handle.net/2433/157343>

RIGHT:

© 2012 Elsevier Ltd.; This is not the published version. Please cite only the published version.; この論文は出版社版ではありません。引用の際には出版社版をご確認ご利用ください。

Rheological properties of concentrated solutions of galactomannans in an ionic liquid

Jun-ichi Horinaka*, Ryosuke Yasuda, and Toshikazu Takigawa

Department of Material Chemistry, Graduate School of Engineering, Kyoto University,

Nishikyo, Kyoto 615-8510, Japan

* Corresponding author.

E-mail: horinaka.junichi.5c@kyoto-u.ac.jp

Tel: +81-75-383-2455

Fax: +81-75-383-2458

Key Words: galactomannan; molecular weight between entanglements; guar gum; tara gum;
locust bean gum; ionic liquid

20 **Abstract**

21 The rheological behavior of galactomannans in concentrated solutions was examined by
22 using dynamic viscoelasticity measurements. Concentrated solutions of three galactomannans,
23 guar gum, tara gum, and locust bean gum were prepared with an ionic liquid
24 1-butyl-3-methylimidazolium chloride as the solvent. Each galactomannan solution showed
25 angular frequency dependence curves of the storage modulus and the loss modulus which were
26 characteristic of a solution of entangled polymer chains. The molecular weight between
27 entanglements (M_e) was obtained from the plateau modulus and the concentration dependence
28 of M_e showed M_e in the molten state ($M_{e,melt}$) to be 4.6×10^3 , 3.2×10^3 , and 2.7×10^3 for guar gum,
29 tara gum, and locust bean gum, respectively. It was found that the material constant $M_{e,melt}$
30 depends on the mannose/galactose ratio of the galactomannans. The number of monosaccharide
31 units between entanglements in the molten state for the galactomannans varied within the range
32 found for other polysaccharides such as cellulose and agarose in ionic liquids, suggesting that
33 all the galactomannans take a random-coil conformation in ionic liquid solutions.

34

35

1. Introduction

Galactomannans consist of a main chain of (1, 4)- β -D-mannose as units and a side group of (1, 6)- α -linked D-galactose. Among them guar gum (g-gum), tara gum (t-gum) and locust bean gum (lb-gum) are specifically well-known. They differ in the mannose/galactose (m/g) ratio: ~2 for g-gum, ~3 for t-gum, and ~4 for lb-gum (Sittikijyothin, Torres, & Goncalves, 2005; Wientjes, Duit, Jongschaap, & Mellema, 2000; Wu, Cui, Eskin, & Goff, 2009; Wu, Li, Cui, Eskin, & Goff, 2012). The three galactomannans have been widely used in the food industry as ingredients to enhance viscosities in processing (Cerqueira, Bourbon, Pinheiro, Martins, Souza, Teixeira, & Vicente, 2011), but the degree of enhancement depends on the species, or more precisely the m/g ratio. Similarly, how the m/g ratio is important to consider the viscoelastic properties of the solutions has been reported by many research groups (Sittikijyothin, Torres, & Goncalves, 2005; Wu, Cui, Eskin, & Goff, 2009; Wu, Li, Cui, Eskin, & Goff, 2012). The m/g ratio is really one of important factors determining the solution properties of the galactomannans, but the origin on the molecular basis is still controversial (Morris, Cutler, Ross-Murphy, & Rees, 1981; Richardson, & Ross-Murphy, 1987; Robinson, Ross-Murphy, & Morris, 1982; Wu, Cui, Eskin, & Goff, 2009). The galactose units are not randomly distributed along the main chain made of mannose for galactomannans, which generates a blockiness: galactose-poor blocks (g-poor blocks, i.e., mannose-rich blocks) and galactose-rich (g-rich) blocks on a chain. Of course, the

blockiness is not clear, but the mannose blocks easily form molecular association through hydrogen bonds, while such attractive interaction is small for the g-rich blocks (Sanderson, 1990; Urlacher, & Dalbe, 1994). This intermolecular association, enhanced with increasing the m/g ratio, may explain the difference in solution properties of the galactomannans.

The viscoelastic properties of the concentrated solutions of galactomannans are controlled firstly by the number density of entanglements on a polymer chain, as is the case of other homogeneous polymer liquids (Ferry, 1980; Doi, & Edwards, 1986), and the number density is a material constant reflecting the molecular parameters of the polymer chains such as the stiffness of the polymer chain. The molecular weight between entanglements (M_e) is often used to describe the spacing between entanglements and M_e in the molten state ($M_{e,melt}$) becomes a material constant. It is interesting to know if the chain stiffness and accordingly the spacing between entanglements change with the m/g ratio (McCleary, Amado, Waibel, & Neukom, 1981). However, we have no information of the values of $M_{e,melt}$ for the galactomannans at present. This is partly due to the difficulty in preparing concentrated solutions, solutions of overlapping polymers, of the galactomannans with conventional solvents. The aim of this study is to estimate $M_{e,melt}$ for the galactomannans. It should be noted that the rheological behavior reflecting $M_{e,melt}$ (or M_e) appears in much shorter time region than the intermolecular associations described above. Dynamic viscoelasticity is examined for concentrated solutions by

using an ionic liquid as a good solvent. Ionic liquids are known to dissolve several polysaccharides which are insoluble to conventional organic solvents. For each of galactomannans, M_e is determined as a function of the polymer concentration (c), and then $M_{e,melt}$ is estimated by extrapolation of the c -dependence curve of M_e .

2. Experimental

2.1. Materials

Galactomannan powders (g-gum, t-gum and lb-gum) were provided from MRC-Polysaccharide Co., Japan. All samples were used without further purification. A solvent 1-butyl-3-methylimidazolium chloride (BmimCl; Aldrich, USA) was used as received. According to the manufacturer's data sheet, the melting temperatures (T_m) of BmimCl was reported to be 70 °C. The galactomannan solutions in BmimCl were prepared as follows: The powders were added into liquid BmimCl in a dry glass vessel, and then the mixture was quickly stirred with a stainless steel spatula on a hot plate at about 80 °C. After that the glass vessel was sealed and was left on the hot plate for complete melting. For every galactomannan c ranged from 5.4×10^1 to $2.1 \times 10^2 \text{ kgm}^{-3}$ (ca. 5 to 20 wt %), and in the calculation of c , the density of BmimCl was assumed to be $1.08 \times 10^3 \text{ kgm}^{-3}$, as reported previously (Horinaka, Yasuda, Takigawa, 2011a; Horinaka, Yasuda, Takigawa, 2011b). The densities for the galactomannans

were commonly assumed to be 10^3 kgm^{-3} , since the values for the purely amorphous polymers are not available (Horinaka, Yasuda, Takigawa, 2011a). The viscoelasticity measurements were started just after finishing the sample preparation.

2.2. Measurements

The dynamic viscoelasticity measurements were carried out with an ARES rheometer (now TA Instruments, USA) under a nitrogen atmosphere with a cone-plate geometry. The diameter of the plates was 25 mm and the cone angle was 0.1 rad. The angular frequency (ω) dependence curves of the storage modulus (G') and the loss modulus (G'') were measured in the range of ω from 0.01 to 100 s^{-1} . The amplitude of the oscillatory strain (γ) was settled to be 0.1 so that the linear viscoelasticity was realized. The measurement temperature (T) ranged from 20 to 100°C . The viscoelasticity measurements were successfully taken even at 20°C , since the supercooled state of the BmimCl solutions was rather stable below T_m of 70°C . (Horinaka, Honda, Takigawa, 2009; Horinaka, Yasuda, Takigawa, 2011a)

3. Results and Discussion

Figure 1 (a) shows the master curves of G' and G'' at the reference temperature (T_r) of 80°C for the solutions of g-gum at $c =$ for 5.4×10^1 and $2.1 \times 10^2 \text{ kgm}^{-3}$. At both concentrations,

the ω dependence curves at different temperatures were well superimposed to give the master curves only by a horizontal shift (a_T : the shift factor). This means that the time (or, angular frequency)-temperature superposition principle holds for these systems. The frequency-dependence of loss tangent ($\tan\delta = G''/G'$) is also shown for the region in which the curves pass through a minimum. The zero-shear viscosity (η_0) of the solvent, BmimCl, at T_r of 80 °C was much smaller than that of the solutions examined here, and therefore the contribution of η_0 of the solvent to G'' was ignored. At low ωa_T the flow region can be seen clearly on the G' and G'' curves. In the middle ωa_T region in the figure the rubbery plateau exists on both G' curves. The rubbery plateau originates from the entanglement coupling between polymer chains, indicating the existence of entanglements between g-gum chains. The tilted plateau suggests that the molecular weight distribution of the g-gum is broad.

Figures 1 (b) and (c) show the master curves of G' and G'' for the solutions of t-gum and lb-gum, respectively. Similar viscoelastic behavior to the g-gum solutions is observed for these galactomannans.

Figure 2 shows $\log a_T$ ($T_r = 80$ °C) plotted against $1/T$ from 20 to 100 °C for the solutions of g-gum, t-gum and lb-gum. The shift factor a_T at a given T is almost the same regardless of c and all data points fall on a single line. These are common to the three figures ((a) to (c)). The above indicates that the T -dependence curve of a_T can be represented by an Arrhenius-type

equation and that even below the melting point of BmimCl, a_T has the same T dependence as above the melting point. Similar behavior has been observed for other polysaccharides in BmimCl (Horinaka, Yasuda, Takigawa, 2011a; Horinaka, Yasuda, Takigawa, 2012).

From the analogy with the rubber elasticity, M_e for a polymer at a concentration c can be calculated by

$$M_e = \frac{10^3 cRT}{G_N^0} \quad (1)$$

Here, G_N^0 is the plateau modulus in the rubbery region and R is the gas constant. (Ferry, 1980; Doi, & Edwards, 1986; Onogi, Masuda, & Kitagawa 1970) As stated previously, the actual G' curves in this study were tilted, so that we defined here G_N^0 as the G' value at ωa_T where the $\tan\delta$ versus ω curve stays at a minimum. This leads to the results that the 5.4×10^1 and 2.1×10^2 kgm^{-3} solutions of g-gum respectively have G_N^0 of 1.6×10^3 and 3.2×10^4 Pa (Figure 1(a)), finally giving M_e of 9.8×10^4 and 2.0×10^4 , respectively. The values of M_e for the solutions of other galactomannans were obtained in a similar way.

Figure 3 shows double-logarithmic plots of M_e against c for the three galactomannans. For each galactomannan, a straight line with a slope of -1 is drawn with the best fit method. This is based on the assumption that a relation for polymers $M_e \propto c^{-1}$ is also applied to the galactomannans (Doi, & Edwards, 1986; Masuda, Toda, Aoto, & Onogi, 1972; Nemoto, Ogawa, Odani, & Kurata, 1972). It is seen that data points for each galactomannan are fitted well by the

line of slope -1 , indicating that the c^{-1} dependence of M_e also holds well for the galactomannan solutions examined in this study. Comparing the values of M_e at a given c , we have the order g-gum > t-gum > lb-gum although the difference between t-gum and lb-gum is rather small. The quantity, $M_{e,melt}$ for the galactomannans can be determined as a value of the intercept on the right-hand ordinate in Figure 3 (or, more precisely, the value of M_e at $c = 10^3 \text{ kgm}^{-3}$), by assuming the density of all galactomannans to be $1.0 \times 10^3 \text{ kgm}^{-3}$. The obtained values of $M_{e,melt}$ are 4.6×10^3 , 3.2×10^3 , and 2.7×10^3 for g-gum, t-gum and lb-gum, respectively; namely, $M_{e,melt}$ becomes smaller with increasing the m/g ratio. Since $M_{e,melt}$ is a material constant, it is interesting to calculate the number of monosaccharide units between entanglements in the molten state (N_{unit}) from $M_{e,melt}$ and M_{unit} , with M_{unit} being the molecular weight of a repeating unit for the galactomannans. Here, M_{unit} was calculated based on the assumption that the m/g ratios are the typical values, i.e., 2 for g-gum, 3 for t-gum, and 4 for lb-gum, and that a galactose side group was included in a unit. We define N_{unit} as the number of mannose units along the main chain, not counting a galactose side group, i.e., $N_{unit} = (\text{the number of mannose units in a unit}) \times (M_{e,melt} / M_{unit})$. Table 1 lists N_{unit} for the galactomannans together with $M_{e,melt}$ and M_{unit} . The values of N_{unit} lie in almost the same range (13 to 19). If we see them more precisely, however, we may have a tendency that N_{unit} decreases with increasing the m/g ratio. The values for the galactomannans can also be compared with those for other polysaccharides estimated in

our previous studies. We have 19 for cellulose, 15 for agarose and 14 for gellan, which are almost the same and are typical for polysaccharides with the random-coil conformation in the ionic liquid (Horinaka, Yasuda, & Takigawa, 2011a). The values for the galactomannans are really close to those of the other polysaccharides with the random coil conformation, suggesting that the galactomannans in the ionic liquid here take the random coil conformation. This is, at least for g-gum, consistent with the previous prediction made from the intrinsic viscosity measurement that a g-gum molecule behaves as a random coil in water (Robinson, Ross-Murphy, & Morris, 1982).

4. Conclusions

Dynamic viscoelasticity of concentrated solutions of g-gum, t-gum, and lb-gum in BmimCl was examined to estimate $M_{e,melt}$ of the galactomannans. The values of $M_{e,melt}$ are 4.6×10^3 , 3.2×10^3 , and 2.7×10^3 for g-gum, t-gum, and lb-gum, respectively; namely, $M_{e,melt}$ for the galactomannans is dependent on the m/g ratio. As a whole, however, N_{unit} for the three galactomannans are rather close to each other being in the same range as for other polysaccharides such as cellulose and agarose. This suggests that the galactomannans take the random coil conformation in ionic liquid. It seems that a galactose side group causes no conformational changes of galactomannans, for example, to a helix.

180

181

182 **References**

- 183 Cerqueira, M. A., Bourbon, A. I., Pinheiro, A. C., Martins, J. T., Souza, B. W. S., Teixeira, J. A.,
184 & Vicente, A. A. (2011). Galactomannans use in the development of edible films/coatings
185 for food applications. *Trends in Food Science & Technology*. 22, 662-671.
- 186 Doi, M., & Edwards, S. F. (1986). *The theory of polymer dynamics*. Oxford: Clarendon.
- 187 Ferry, J. D. (1980). *Viscoelastic properties of polymers*. New York: John Wiley & Sons.
- 188 Horinaka, J., Yasuda, R., & Takigawa, T. (2009). Rheological Properties of Concentrated
189 Solutions of Gellan in an Ionic Liquid. *Carbohydr. Polym.*, 78, 576-580.
- 190 Horinaka, J., Yasuda, R., & Takigawa, T. (2011)a. Entanglement properties of cellulose and
191 amylose in an ionic liquid. *J. Polym. Sci. B: Polym. Phys.*, 49, 961-965.
- 192 Horinaka, J., Yasuda, R., & Takigawa, T. (2011)b. Entanglement network of agarose in various
193 solvents. *Polymer J.*, 43, 1000-1002.
- 194 Horinaka, J., Yasuda, R., & Takigawa, T. (2012). Rheological properties of concentrated
195 solutions of agarose in ionic liquid. *J. Appl. Polym. Sci.*, 123, 3023-3027.
- 196 Masuda, T., Toda, N., Aoto, Y., & Onogi, S. (1972). Viscoelastic properties of concentrated
197 solutions of poly(methyl methacrylate) in diethyl phthalate. *Polym. J.*, 3, 315-321.
- 198 McCleary, B. V., Amado, R., Waibel, R., & Neukom, H. (1981). Effect of galactose content on
199 the solution and interaction properties of guar and carob galactomannans. *Carbohydr. Res.*,

- 200 92, 269-285.
- 201 Morris, E. R., Cutler, A. N., Ross-Murphy, S. B., & Rees, D. A. (1981). Concentration and shear
- 202 rate dependence of viscosity in random coil polysaccharide solutions. *Carbohydr. Polym.*, 1,
- 203 5-21.
- 204 Nemoto, N., Ogawa, T., Odani, H., & Kurata, M. (1972). Shear creep studies of
- 205 narrow-distribution poly(cis-isoprene). III. concentrated solutions. *Macromolecules*, 5, 641-644.
- 206 Onogi, S., Masuda, T., & Kitagawa K.(1970). Rheological properties of anionic polystyrenes. I.
- 207 dynamic viscoelasticity of narrow-distribution polystyrenes. *Macromolecules*, 3, 109-116.
- 208 Richardson, R. K., & Ross-Murphy, S. B. (1987). Non-linear viscoelasticity of polysaccharide
- 209 solutions. 1: guar galactomannan solutions. *Int. J. Biol. Macromol.*, 9, 250-256.
- 210 Robinson, G., Ross-Murphy, S. B., & Morris, E. R. (1982). Viscosity-molecular weight
- 211 relationships, intrinsic chain flexibility, and dynamic solutions properties of guar
- 212 galactomannan. *Carbohydr. Res.*, 107, 17-32.
- 213 Sanderson, G. R. (1990). Imeson, A. (Ed.) *Food gels*. New York: Elsevier Applied Science.
- 214 Sittikijyothin, W., Torres, D., & Goncalves, M. P. (2005). Modeling the rheological behavior of
- 215 galactomannan aqueous solutions. *Carbohydr. Polym.*, 59, 339-350.
- 216 Urlacher, B., & Dalbe, B. (1994). Imeson, A. (Ed.) *Thickening and gelling agents for food*.
- 217 London: Blackie Academic and Professional, 257-273.

- 218 Wientjes, R. H. W., Duit, M. H. G., Jongschaap, R. J. J., & Mellema, J. (2000). Linear rheology
219 of guar gum solutions. *Macromolecules*, 33, 9594-9605.
- 220 Wu, Y., Cui, W., Eskin, N. A. M., & Goff, H. D. (2009). An investigation of four commercial
221 galactomannan on their emulsion and rheological properties. *Food Res. Int.*, 42, 1141-1146.
- 222 Wu, Y., Li, W., Cui, W., Eskin, N. A. M., & Goff, H. D. (2012). A molecular modeling approach
223 to understand conformation-functionality relationships of galactomannans with different
224 mannose/galactose ratios. *Food Hydrocolloids*, 26, 359-364.

Figure Captions

Figure 1 Master curves of ω dependence of G' and G'' for 5.4×10^1 and $2.1 \times 10^2 \text{ kgm}^{-3}$ solutions of (a) g-gum, (b) t-gum, and (c) lb-gum. $T_r = 80 \text{ }^\circ\text{C}$. The $\tan\delta$ curve is also included.

Figure 2 Shift factor for (a) g-gum, (b) t-gum, and (c) lb-gum solutions of c from 5.4×10^1 to $2.1 \times 10^2 \text{ kgm}^{-3}$ plotted against the reciprocal of T . In each figure, all data points fall on a single line

Figure 3 Double-logarithmic plot of M_e against c for galactomannans in solution. Each line is the best fit with a slope of ≈ 1 . $M_{e,\text{melt}}$ for galactomannans are determined as M_e at $c = 10^3 \text{ kgm}^{-3}$.

Fig. 1(a)

Fig. 1(b)

Fig. 1(c)

Fig. 2(a)

Fig. 2(b)

Fig. 2(c)

Fig. 3

Table 1. Material constants for galactomannans

sample	M_{unit}	$M_{\text{e,melt}}$	N_{unit}^*
g-gum	486	4.6×10^3	19
t-gum	648	3.2×10^3	15
lb-gum	810	2.7×10^3	13

* excluding a galactose side group