TITLE:

Redox reaction in two-dimensional porous coordination polymers based on ferrocenedicarboxylates.

AUTHOR(S):

Hirai, Kenji; Uehara, Hiromitsu; Kitagawa, Susumu; Furukawa, Shuhei

CITATION:

Hirai, Kenji ...[et al]. Redox reaction in two-dimensional porous coordination polymers based on ferrocenedicarboxylates.. Dalton transactions 2012, 41(14): 3924-3927

ISSUE DATE:

2012-02-29

URL:

<http://hdl.handle.net/2433/172095>

RIGHT:

© The Royal Society of Chemistry 2012.; この論文は出版社版ではありません。引用の際には出版社版をご確認ご利用ください。; This is not the published version. Please cite only the published version.

Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxxx

Communications

Redox reaction in two-dimensional porous coordination polymers based on ferrocenedicarboxylates

Kenji Hirai,^a Hiromitsu Uehara,^b Susumu Kitagawa,^{*a,b,c} and Shuhei Furukawa^{*b,c}

Received (in XXX, XXX) Xth XXXXXXXXXX 20XX, Accepted Xth XXXXXXXXXX 20XX

DOI: 10.1039/b000000x

A series of 1,1'-ferrocenedicarboxylate-based two-dimensional porous coordination polymers were synthesized by incorporating different diamine coligands. These compounds immobilized on electrodes, exhibited reversible redox reactions, arising from ferrocenyl moiety.

Porous coordination polymers (PCPs), assembled from metal ions and organic ligands, are an interesting class of crystalline materials¹. They have been extensively studied for applications in gas storage², separation³ and chemical sensing⁴. Compared with these porous properties, only a few studies on the electronic properties of the frameworks have been reported⁵. The synergetic collaboration between the electronic properties of the framework and the intrinsic porous properties has led to new applications of PCPs in a wide range of important fields. In particular, a redox-active PCP may be useful material for electrochemical applications such as ion storage⁶ or electrocatalysis⁷. The key to successful implementation is not only to construct the redox-active framework itself, but also to hybridize the framework with an electrode, which allows the investigation of redox process in the pores.

Although the judicious choice of metal ion and organic linker provides the redox activity within PCP frameworks⁸, the redox reaction often changes the coordination environment of metal ions, thus leading to destruction of the framework. One way to overcome the issues is to construct the framework with stable ligands for the redox reaction. In this context, 1,1'-ferrocenedicarboxylate (Fcde) is an excellent candidate because it contains the stable ferrocene moiety and two carboxylate coordination sites⁹. Some research groups have reported on the syntheses of ferrocene-based coordination polymers¹⁰, but there are only a few reports of the solid-state electrochemical properties of coordination polymers containing the Fcde ligand¹¹.

Recently we reported on a series of two-dimensional (2D) PCPs, so-called coordination polymers with an interdigitated structure (CID), of which the three components, namely the metal ions, V-shaped dicarboxylate ligands, and diamine pillar ligands, participate in the construction¹². Their porous properties and chemical functionalities can be easily modulated by varying the components. Although there is a limit to the angle of two carboxylates in the V-shaped ligand in the range 118°–152°, the rotational freedom of the ferrocenyl moiety enables the ligand to mimic the V-shape, thus providing CID frameworks with stable redox properties.

Here we report the rational synthesis of ferrocene-based CID frameworks by incorporating different diamine pillar ligands. The length of the pillar ligand determines the configuration of the 2D sheets, resulting in different thermal stabilities. The electrochemical properties were elucidated by the immobilization of these crystals on gold electrodes.

A coordination framework of $\{[\text{Zn}(\text{Fcde})(\text{bpy})] \cdot (\text{DMF})_{0.5}(\text{MeOH})_{0.5}\}_n$ (1; solvents) was synthesized via the reaction of $\text{Zn}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$, H_2Fcde and bpy in a DMF/MeOH solution at 353 K (bpy = 4,4'-bipyridyl). As shown in Fig. 1a and b, the Zn ion has a distorted octahedral N_2O_4 geometry; it is coordinated by two bpy molecules at the axial positions, one chelating carboxylate of Fcde and two other monodentate carboxylates of Fcde in the equatorial plane. The coordination of Fcde ligands to the Zn ions constructed a one-dimensional (1D) chain structure as shown in Fig. 1a, followed by the linkage of the adjacent chains through bpy in the axial positions, leading to the formation of a 2D sheet. Alternatively assembled are two types of sheet structures, sheets A and B, which are mirror images of each other. It should be noted that the length of bpy (7.1 Å) is too short to form the interdigitation because of the bulkiness of the ferrocenyl moiety (the distance between cyclopentadienyl rings is 6.8 Å), compared with the phenyl ring, seen in the reported CID structure. Therefore, the noninterdigitation between the sheets provided 1D channels with a window size of $4.4 \times 6.0 \text{ Å}^2$ (Fig. 2a–b, Fig. S1).

Elongation of the pillar ligands from bpy to dpb or dpndi created a space between the 1D chains and allowed them to form

Fig. 1 Crystal structures of (a) the 1D chain structure composed of Zn ions and Fcde, and (b) the sheet structure of **1**. Gray, blue, red, orange, and purple are C, N, O, Fe and Zn, respectively. The hydrogen atoms and guest molecules are omitted for clarity.

Fig. 2 Crystal structures showing (a) the side view, (b) the top view of assembled structure of **1**⊃solvents, (c) the side view, (d) the top view of assembled structure of **2**⊃solvents, (e) the side view, (f) the top view of assembled structure of **3**⊃solvents.

the interdigitation (dpb = 1,4-di(pyridin-4-yl)benzene, dpndi = *N,N'*-di(4-pyridyl)-1,4,5,8-naphthalenetetracarboxydiimide).

These analogous frameworks were synthesized by the solvothermal reaction of $\text{Zn}(\text{NO}_3)_2 \cdot 6\text{H}_2\text{O}$ with H_2Fcdc and dpb or dpndi in a DMF/MeOH solution: $\{[\text{Zn}(\text{Fcdc})(\text{dpb})] \cdot (\text{DMF})_{0.5}(\text{MeOH})_{0.5}\}_n$ (**2**⊃solvents) or $\{[\text{Zn}(\text{Fcdc})(\text{dpndi})] \cdot (\text{DMF})_{0.5}(\text{MeOH})_{0.5}\}_n$ (**3**⊃solvents), respectively. Although the compound **2** formed the alternative assembly of sheet structures as seen in **1**, only one type of 2D sheet (sheet A) was found in the compound **3**. The expansion of the interchain distance in **2** and **3** resulting from the incorporation of the longer pillar ligands (dpb (11.4 Å) or dpndi (15.5 Å)) enables the 2D sheets to form the interdigitation. Whereas the 1D channels with a window size of $4.4 \times 4.9 \text{ Å}^2$ extend along the *c* axis in compound **2**, the 1D channels with a window size of $4.8 \times 4.5 \text{ Å}^2$ runs along the *a* axis in compound **3** (Fig. S1-S3).

Thermogravimetric analysis indicated that **1**, **2** and **3** released the guest molecules up to 200 °C (Fig. S4). Although **1** started to decompose around 250 °C, **2** and **3** were stable up to 350 °C. The difference in the collapse temperature between **1**, **2** and **3** is probably because of the interdigitation of the 2D sheets in **2** and **3**, which lends further thermal stability to the frameworks.

X-ray powder diffraction (XRD) analysis of the evacuated

frameworks was carried out to confirm the stability of the open structures in the absence of guest molecules. All the compounds retained their crystallinity, as shown in Figs S5-7. Adsorption measurements of ferrocene-based PCPs were performed for CO_2 , N_2 , and O_2 , as shown in Fig. S8-10. The adsorption isotherms of all compounds showed a Type I steep uptake for CO_2 at the low-pressure region, indicating the preservation of the ordered porous structure, but no eventual uptake for N_2 and O_2 . Generally, PCPs preferentially adsorb CO_2 over other small gases because of its small kinetic diameter¹³.

To date, the redox properties of coordination polymers containing ferrocenes have been reported after either dissolving the crystals in solvent or by depositing the crystals on a working electrode. In both cases, however, it is very difficult to elucidate the redox property of the framework itself. These methods most likely led to the determination of the electrochemical activity of the solute species (soluble oligomers or metal complexes)¹⁴. To overcome this issue and to determine the redox properties of the PCPs themselves, we immobilized the crystals of ferrocene-based PCPs on gold electrodes.

A gold substrate was placed in the reaction solution for four days to grow the PCP crystals directly on the surface, in a perpendicular fashion to avoid coating by sedimentation¹⁵. The

Fig. 3 SEM images of a) **1** b) **2**, c) **3** on Au substrates

Fig. 4 XRD patterns of a) in-plane diffraction, b) out-of-plane diffraction of **1**/Au, c) simulation of **1**.

substrates were rinsed with DMF and dried in air. The plate-like crystals of **1** were densely grown on the electrode surface, whereas the crystals of **2** and **3** partially covered the substrates (Fig.3). The low solubility of the diamine ligands, dpb and dpndi, most likely prevented the dense growth of **2** and **3**.

XRD results of the substrate samples revealed that crystals were preferentially oriented on the substrates (Fig. 4 and Figs S11-14). The out-of-plane XRD scans of **1** and **3** on the gold electrodes (denoted as **1**/Au and **3**/Au) demonstrated the presence of a preferentially oriented crystalline material perpendicular to 020 and 011 respectively. The oriented crystal growth of **1** and **3** on the substrates can be explained by the coordination bond of carboxylates to the gold atoms. Together with the in-plane data, the PCP crystals of **1** and **3** were successfully immobilized on the gold electrodes. Compound **2** on the gold electrode (denoted as **2**/Au) showed rather weak diffraction because of the low crystallinity on the substrate.

The electrochemical behavior of **1**/Au was investigated by cyclic voltammetry (CV) in CH_2Cl_2 solution with 0.1 mol L^{-1} $n\text{-Bu}_4\text{NBF}_4$ as electrolyte. A reversible redox wave was observed at 0.95 V. It was assigned to a Ferrocene/Ferrocenium cation in the PCP crystals (Fig. 5). Compared with the redox potential of $\text{H}_2\text{Fc}^{\text{d}c}$ in $n\text{-Bu}_4\text{NBF}_4$ solution (0.88 V), that of **1**/Au (0.95 V) is shifted to a more positive potential (Fig. 5a and Table 1). The reason for this is the electron-withdrawing property of the carboxylates from the cyclopentadienyl rings and the coordination bond between carboxylate and Zn ions¹⁶. Unfortunately, **2**/Au and **3**/Au did not show clear CV profiles, probably because of the low density of crystals on the electrodes.

A negative shift of the redox potential was observed (0.78 V) when changing the electrolyte from $n\text{-Bu}_4\text{NBF}_4$ to $n\text{-Bu}_4\text{NNO}_3$, which suggests that NO_3^- forms the stronger ion pair with the positively charged oxidized compounds of ferrocenium (Table 1). This can be explained by the smaller ionization energy of NO_3^- resulting in a higher degree of ion-pair formation¹⁷.

It is interesting that the peak currents show a linear dependence on the square roots of the scan rate, as shown in Fig. 5b. The linearity in the plots indicates that the charge transfer in the redox process is controlled by the diffusion of charges in the PCPs as described by the empirical Randles-Sevcik equation¹⁸.

Fig. 5 (a) Cyclic voltammograms of $\text{H}_2\text{Fc}^{\text{d}c}$ and **1** at 100mV/s scan rates. The dispersed $\text{H}_2\text{Fc}^{\text{d}c}$ in CH_2Cl_2 was deposited onto the gold electrode. The current intensity of $\text{H}_2\text{Fc}^{\text{d}c}$ is magnified twice for clarify. (b) Dependence of peak currents on scan rates. Closed and open circles show oxidation and reduction, respectively.

Table. 1 Electrochemical data of **1** and $\text{Fc}^{\text{d}c}$ on an Au substrate at 100mV/s scan rates

compounds	$E_{1/2}^{[a]}$ (V)	$\Delta E^{[b]}$ (V)	$\Gamma^{[c]}$ (mol cm^{-2})	electrolytes
$\text{H}_2\text{Fc}^{\text{d}c}$	0.88	0.099	—	$n\text{-Bu}_4\text{NBF}_4$
1 /Au	0.95	0.412	6.82×10^{-10}	$n\text{-Bu}_4\text{NBF}_4$
1 /Au	0.78	0.301	2.09×10^{-9}	$n\text{-Bu}_4\text{NNO}_3$

[a] The half wave potential, $E_{1/2} = (E_{\text{ox}} + E_{\text{red}})/2$. [b] The difference of the oxidation potential and reduction potential, $\Delta E = E_{\text{ox}} - E_{\text{red}}$. [c] Surface concentration of redox active species.

Since the PCP crystals are immobilized on the electrode surface, the current is most likely limited by the diffusion of counteranions in the pores¹⁷. The contribution of the solute species to the redox reaction could be ignored because there was no dissolution of the $\text{Fc}^{\text{d}c}$ ligands from the framework under the conditions used, as confirmed by the CV measurement of the residual solution. Therefore, the redox reaction observed here was subsequently attributed to the ferrocene moiety embedded into the framework.

In summary, we have demonstrated the redox reaction of ferrocene-based PCPs achieved by creating crystals on gold substrates. Although the crystals are immobilized on the substrate,

the redox process is controlled by the diffusion of charges. The CV results were interpreted as the diffusion of counteranions into the channels. This results indicates that Fcdc ligand allows for the incorporation of the redox activity into PCP frameworks and opens the way for their use in a wide range of electronic applications.

Notes and references

^a Department of Synthetic Chemistry and Biological Chemistry, Graduate School of Engineering, Kyoto University, Katsura, Nishikyo-ku, Kyoto, 615-8510, Japan. E-mail: kitagawa@sbchem.kyoto-u.ac.jp; Fax: +81-75-383-2732; Tel: +81-75-383-2733

^b ERATO Kitagawa Integrated Pores Project, Japan Science and Technology Agency (JST), Kyoto Research Park bldg #3, Shimogyo-ku, Kyoto, 600-8815, Japan. E-mail: shuhei.furukawa@kip.jst.go.jp; Fax: +81-75-325-3572; Tel: +81-75-322-4711

^c Institute for Integrated Cell-Material Sciences, Kyoto University, Yoshida, Sakyo-ku, Kyoto, 606-8501, Japan

† Electronic Supplementary Information (ESI) available: [details of any supplementary information available should be included here]. See DOI: 10.1039/b000000x/

‡ Crystal data for **1**⊃solvents: C₂₂H₁₆FeN₂O₄Zn *M_w* = 493.61 gmol⁻¹, monoclinic, space group *P*2₁/*c*, (#14), *a* = 11.367(5) Å, *b* = 24.599(9) Å, *c* = 9.050(4) Å, β = 112.970(5), *V* = 2330.0(16) Å³, *Z* = 4, *T* = 223 K, ρ_{calcd} = 1.407 gcm⁻³, μ(MoK_α) = 1.679 cm⁻¹, 5308 reflections measured, 2538 observed (*I* > 2.00σ(*I*)) 271 parameters; *R*₁ = 0.0763, *wR*₂ = 0.2108, GOF = 0.914. CCDC 852944.

Crystal data for **2**⊃solvents: C₂₈H₂₀FeN₂O₄Zn *M_w* = 569.70 gmol⁻¹, monoclinic, space group *P*2₁/*c*, (#14), *a* = 9.072(6) Å, *b* = 21.526(12) Å, *c* = 14.375(9) Å, β = 99.212(12), *V* = 2771(3) Å³, *Z* = 4, *T* = 223 K, ρ_{calcd} = 1.365 gcm⁻³, μ(MoK_α) = 1.422 cm⁻¹, 6166 reflections measured, 3789 observed (*I* > 2.00σ(*I*)) 325 parameters; *R*₁ = 0.0792, *wR*₂ = 0.2253, GOF = 1.016. CCDC 852945.

Crystal data for **3**⊃solvents: C₃₆H₂₀FeN₄O₈Zn *M_w* = 757.80 gmol⁻¹, triclinic, space group *P*-1, (#2), *a* = 8.940(5) Å, *b* = 12.349(6) Å, *c* = 15.288(8) Å, α = 78.383(18), β = 87.636(18), γ = 87.59(2), *V* = 1650.9(15) Å³, *Z* = 2, *T* = 223 K, ρ_{calcd} = 1.524 gcm⁻³, μ(MoK_α) = 1.225 cm⁻¹, 7192 reflections measured, 3822 observed (*I* > 2.00σ(*I*)) 451 parameters; *R*₁ = 0.0731, *wR*₂ = 0.1885, GOF = 0.936. CCDC 852946.

- 1 (a) O. M. Yaghi, M. O'Keeffe, N. W. Ockwing, H. K. Chae, M. Eddaoudi and J. Kim, *Nature*, 2003, **423**, 705; (b) S. Kitagawa, R. Kitaura and S. Noro, *Angew. Chem. Int. Ed.*, 2004, **43**, 2334; (c) G. Férey, C. Mellot-Draznicks, C. Serre and F. Millange, *Acc. Chem. Res.*, 2005, **38**, 217; (d) S. Batten and R. Robson, *Angew. Chem. Int. Ed.*, 1998, **37**, 1460; (e) U. Mueller, M. Schubert, F. Teich, H. Puetter, K. Schierle-Armdt and J. Pastré, *J. Mater. Chem.*, 2006, **16**, 626.
- 2 (a) M. Dincă, A. Dailly, Y. Liu, C. M. Brown, D. A. Neumann and J. R. Long, *J. Am. Chem. Soc.*, 2006, **128**, 16876; (b) S. Ma, D. Sun, J. M. Simmons, C. D. Collier, D. Yuan, and H. C. Zhou, *J. Am. Chem. Soc.*, 2008, **130**, 1012; (c) R. Matsuda, R. Kitaura, S. Kitagawa, Y. Kubota, R. V. Belosludov, T. C. Kobayashi, H. Sakamoto, T. Chiba, M. Takata, Y. Kawazoe, Y. Mita, *Nature*, 2005, **436**, 238.
- 3 (a) B. Wang, A. P. Côté, H. Furukawa, M. O'Keeffe and O. M. Yaghi, *Nature*, 2008, **453**, 207; (b) L. Alaerts, C. E. A. Kirschhock, M. Maes, M. A. van der Veen, V. Finsy, A. Depla, J. A. Martens, G. V. Baron, P. A. Jacobs, J. F. M. Denayer, and D. E. De Vos, *Angew. Chem. Int. Ed.*, 2007, **46**, 4293; (c) B. Chen, C. Liang, J. Yang, D. S. Contreras, Y. L. Clancy, E. B. Lobkovsky, O. M. Yaghi, and S. Dai, *Angew. Chem. Int. Ed.* 2006, **45**, 1390.
- 4 (a) M. D. Allendorf, C. A. Bauer, R. K. Bhakta and R. J. T. Houk, *Chem. Soc. Rev.*, 2009, **38**, 1330. (b) G. J. McManus, J. J. Perry IV, M. Perry, B. D. Wagner, and M. J. Zaworotko, *J. Am. Chem. Soc.*, 2007, **129**, 9094. (c) K. C. Stylianou, R. Heck, S. Y. Chong, J. Bacsá, J. T. A. Jones, Y. Z. Khimyak, D. Bradshaw and M. J. Rosseinsky, *J. Am. Chem. Soc.*, 2010, **132**, 4119; (d) Y. Takashima, V. M. Martinez, S. Furukawa, M. Kondo, S. Shimomura, H. Uehara, M. Nakahama, K. Sugimoto, S. Kitagawa, *Nature Commun.*, 2011, **2**, 168.
- 5 (a) S. Takaishi, M. Hosoda, T. Kajiwara, H. Miyasaka, M. Yamashita, Y. Nakanishi, Y. Kitagawa, K. Yamaguchi, A. Kobayashi, and H. Kitagawa, *Inorg. Chem.*, 2009, **48**, 9048; (b) M. H. Zeng, Q. X. Wang, Y. X. Tan, S. Hu, H. X. Zhao, L. S. Long and M. Kurmoo, *J. Am. Chem. Soc.*, 2010, **132**, 2561; (c) S. Shimomura, M. Higuchi, R. Matsuda, K. Yoneda, Y. Hijikata, Y. Kubota, Y. Mita, J. Kim, M. Takata and S. Kitagawa, *Nature Chem.*, 2010, **2**, 633.
- 6 G. Férey, F. Millange, M. Morcrette, C. Serre, M. L. Doublet, J. M. Grenéche and J. M. Tarascon, *Angew. Chem. Int. Ed.*, 2007, **46**, 3259.
- 7 L. Yang, S. Kinoshita, T. Yamada, S. Kanda, H. Kitagawa, M. Tokunaga, T. Ishimoto, T. Ogura, R. Nagumo, A. Miyamoto and M. Koyama, *Angew. Chem. Int. Ed.*, 2010, **49**, 5348.
- 8 (a) H. R. Moon, J. H. Kim and M. P. Suh, *Angew. Chem. Int. Ed.*, 2005, **44**, 1261; (b) L. M. Rodriguez-Albelo, A. R. Ruiz-Salvador, A. Sampieri, D. W. Lewis, A. Gómez, B. Nohra, P. Mialane, J. Marrot, F. Sécheresse, C. Mellot-Draznicks, R. N. Biboum, B. Keita, L. Nadjio and A. Dolbecq, *J. Am. Chem. Soc.*, 2009, **131**, 16078; (c) Y. Kobayashi, B. Jacobs, M. D. Allendorf and J. R. Long, *Chem. Mater.*, 2010, **22**, 4120.
- 9 (a) R. Horikoshi and T. Mochida, *Eur. J. Inorg. Chem.*, 2010, 5355; (b) V. Chandrasekhar and R. Thirumoorathi, *Dalton Trans.*, 2010, **39**, 2684; (c) L. Wang, X. Meng, E. Zhang, H. Hou, Y. Fan, *J. Organomet. Chem.*, 2007, **692**, 4367.
- 10 (a) M. Meilikhov, K. Yusenko and R. A. Fischer, *J. Am. Chem. Soc.*, 2009, **131**, 9644; (b) J. E. Halls, A. Hernán-Gómez, A. D. Burrows and F. Marken, *Dalton Trans.*, 2011, Advance Article; (c) K. J. Wei, J. Ni and Y. Liu, *Inorg. Chem.*, 2010, **49**, 1834.
- 11 Although some studies on electrochemical properties of Fcdc-based coordination polymers have been reported, the compounds were dissolved in solutions or no detailed experimental condition was described. (a) J. Yang, J. F. Ma, Y. Y. Liu, S. L. Li and G. L. Zheng, *Eur. J. Inorg. Chem.*, 2005, 2174; (b) Y. Xu, C. Ran, L. Zhu and Y. Fan, *J. Coord. Chem.*, 2009, **62**, 410.
- 12 (a) S. Horike, D. Tanaka, K. Nakagawa and S. Kitagawa, *Chem. Commun.* 2007, 3395; (b) D. Tanaka, K. Nakagawa, M. Higuchi, S. Horike, Y. Kubota, T. C. Kobayashi, M. Takata and S. Kitagawa, *Angew. Chem. Int. Ed.*, 2008, **47**, 3914 (c) K. Nakagawa, D. Tanaka, S. Horike, S. Shimomura, M. Higuchi and S. Kitagawa, *Chem. Commun.* 2010, 4258.
- 13 D. N. Dybtsev, H. Chun, S. H. Yoon, D. Kim and Kimoon Kim, *J. Am. Chem. Soc.*, 2004, **32**, 126.
- 14 (a) B. Q. Liu, P. F. Yan, J. Zhang, P. Chen, G. M. Li, *J. Organomet. Chem.* 2010, **695**, 2441; (b) J. Kühnert, T. Ruffer, P. Ecorchard, B. Bräuer, Y. Lan, A. K. Powell and H. Lang, *Dalton Trans.*, 2009, 4499.
- 15 (a) S. Hermes, F. Schröder, R. Chelmoski, C. Wöll and R. A. Fischer, *J. Am. Chem. Soc.*, 2005, **127**, 13744; (b) O. Shekhah, H. Wang, S. Kowarik, F. Schreiber, M. Paulus, M. Tolan, C. Sternemann, F. Evers, D. Zacher, R. A. Fischer and C. Wöll, *J. Am. Chem. Soc.*, 2007, **129**, 15118; (c) E. Biemmi, C. Scherb and T. Bein, *J. Am. Chem. Soc.*, 2007, **129**, 8054.
- 15 D. Warren, H. Charles, D. Russell, *J. Am. Chem. Soc.*, 1967, **89**, 2316.
- 16 (a) K. Uosaki, Y. Sato, H. Kita, *Langmuir*, 1991, **7**, 1510; (b) M. Péter, R. G. H. Lammertink, M. A. Hempenius and G. J. Vancsoion, *Langmuir*, 2005, **21**, 5115.
- 17 K. Itaya, I. Uchida and V. D. Neff, *Acc. Chem. Res.*, 1986, **19**, 162.
- 18 M. Strømme, G. A. Niklasson and C. G. Granqvist, *Solid State Commun.*, 1995, **96**, 151.

Graphical Abstract

A series of ferrocene-based porous coordination polymers was synthesized. The electrochemical properties were elucidated by the immobilization of the crystals on gold electrodes.