TITLE:

In situ NMR observation of the lithium extraction/insertion from LiCoO₂ cathode

AUTHOR(S):

Shimoda, Keiji; Murakami, Miwa; Takamatsu, Daiko; Arai, Hajime; Uchimoto, Yoshiharu; Ogumi, Zempachi

CITATION:

Shimoda, Keiji ...[et al]. In situ NMR observation of the lithium extraction/insertion from LiCoO₂ cathode. *Electrochimica Acta* 2013, 108: 343-349

ISSUE DATE:

2013-10

URL:

<http://hdl.handle.net/2433/179277>

RIGHT:

© 2013 The Authors. Published by Elsevier Ltd.; This is an open-access article distributed under the terms of the Creative Commons Attribution-NonCommercial-No Derivative Works License, which permits non-commercial use, distribution, and reproduction in any medium, provided the original author and source are credited.

In situ NMR observation of the lithium extraction/insertion from LiCoO_2 cathode[☆]

Keiji Shimoda^{a,*}, Miwa Murakami^a, Daiko Takamatsu^a, Hajime Arai^a,
Yoshiharu Uchimoto^b, Zempachi Ogumi^a

^a Office of Society-Academia Collaboration for Innovation, Kyoto University, Uji, Kyoto 611-0011, Japan

^b Graduate School of Human and Environment Studies, Kyoto University, Kyoto 606-8501, Japan

ARTICLE INFO

Article history:

Received 27 March 2013

Received in revised form 13 June 2013

Accepted 18 June 2013

Available online xxx

Keywords:

Nuclear magnetic resonance

In situ NMR

Lithium-7

Lithium ion battery

LiCoO_2 cathode

Lithium dendrite

ABSTRACT

Rechargeable lithium-ion batteries (LIBs) are currently accepted to be one of the most suitable energy storage resources in portable electronic devices because of their high gravimetric and volumetric energy density. To understand the behavior of Li^+ ions on electrochemical lithium extraction/insertion process, we performed *in situ* ^7Li nuclear magnetic resonance (NMR) measurements for LiCoO_2 cathode in a plastic cell battery, and the spectral evolutions of the ^7Li NMR signal of Li_xCoO_2 ($0 \leq x \leq 1$) were well investigated. Very narrow solid solution region of Li_xCoO_2 ($\sim 0.99 \leq x < 1$) was explicitly defined from the large intensity reduction of LiCoO_2 signal at ~ 0 ppm, which is related to the localized nature of the electronic spin of paramagnetic Co^{4+} ion formed at the very early delithiation stage. With further decreasing the signal intensity of LiCoO_2 , a Knight-shifted signal corresponding to an electrically conductive Li_xCoO_2 phase emerged at $x = 0.97$, which then monotonously decreased in intensity for $x < 0.75$ in accordance with the electrochemical lithium de-intercalation from Li_xCoO_2 . These observations acquired *in situ* fully confirm the earlier studies obtained in *ex situ* measurements, although the present study offers more quantitative information. Moreover, it was shown that the peak position of the NMR shift for Li_xCoO_2 moved as a function of lithium content, which behavior is analogous to the change in its *c* lattice parameter. Also, the growth and consumption of dendritic/mossy metallic lithium on the counter electrode was clearly observed during the charge/discharge cycles.

© 2013 The Authors. Published by Elsevier Ltd. All rights reserved.

1. Introduction

Rechargeable lithium-ion batteries (LIBs) have attracted much attention as a preferred energy storage resource not only for portable electronics devices but also for electric vehicles, which further demand high voltage, high capacity, long cycle life, high rate performance, and safety. To enhance such battery performances, it is necessary to follow the chemical state of the positive/negative electrode materials and electrolyte solution in electrochemical operation. Considerable efforts have been made for understanding what occurs during the electrochemical reactions by *in situ* techniques using X-ray diffraction (XRD) and X-ray absorption spectroscopy (XAS). Layered LiCoO_2 -based materials are widely

used as a positive electrode in commercially available LIBs, and several authors reported its changes in crystal structure and electronic structure on electrochemical cycling [1–6]. *In situ* XRD measurements showed the multistep phase transitions in Li_xCoO_2 ($x < 1.0$) during electrochemical delithiation [1–4]. The first transition occurs at a characteristic voltage plateau of ~ 3.9 V versus Li/Li^+ ($0.75 \leq x \leq 0.93$ in Li_xCoO_2), where a newly appeared rhombohedral phase (called O3-II) coexists with the pristine LiCoO_2 (O3-I). The O3-II phase is a single component in the region of $0.5 < x \leq 0.75$. At $x \approx 0.5$ corresponding to a voltage of 4.2 V, the O3-II phase transforms to a monoclinic phase, where the in-plane Li and its vacancy positions align with each other in an ordered sequence. This monoclinic phase is short-lived and transformed again to a rhombohedral O3-II phase upon further lithium extraction. Next phase separation occurs at the voltage of ~ 4.6 V. The new phase is called H1-3, which is considered to be a hybrid of two layers, O3-type stacking Li_xCoO_2 layer and CoO_2 (O1) layer. Finally, the H1-3 phase totally becomes CoO_2 at $x \approx 0$. Recently, *in situ* neutron diffraction (ND) technique was developed and also confirmed the coexistence of O3-I and II phases at 3.9 V plateau and the formation of monoclinic phase at $x \approx 0.5$ [5]. These studies showed the expansion of *c*-axis of the layered Li_xCoO_2 with the lithium extraction from O3-I,

[☆] This is an open-access article distributed under the terms of the Creative Commons Attribution-NonCommercial-No Derivative Works License, which permits non-commercial use, distribution, and reproduction in any medium, provided the original author and source are credited.

* Corresponding author at: Center for Advanced Science and Innovation, Kyoto University, Gokashou, Uji 611-0011, Japan. Tel.: +81 774 38 4967; fax: +81 774 38 4996.

E-mail address: k-shimoda@saci.kyoto-u.ac.jp (K. Shimoda).

O3-II, to monoclinic phase. While XRD and ND provide crystal structure information, XAS offers valence state information on a specific atom. Nakai et al. have reported an *in situ* XAS study of Li_xCoO_2 at Co K-edge [6]. The positive shift of the main peak in the X-ray absorption near edge structure (XANES) region was observed with the lithium extraction from $x = 1$ to 0.2, which would correspond to the valence change (oxidation) between Co^{3+} in LiCoO_2 and Co^{4+} in CoO_2 [7].

It is very important to directly observe the Li^+ ions moving in the battery cell, which is hardly attained or technically demanding with XRD, ND or XAS methods. Nuclear magnetic resonance (NMR) spectroscopy is a promising tool for this purpose. ^6Li NMR spectra have been acquired *ex situ* for the LIB positive and negative electrode materials to obtain structural information on Li^+ ions [8–23]. A ^7Li magic-angle spinning (MAS) NMR study revealed that the Li_xCoO_2 O3-II phase obtained by the electrochemical delithiation showed a Knight shift at 60–100 ppm [10]. Recently, some researchers have tackled on real time NMR investigations during electrochemical cycling [24–32]. Although *in situ* NMR measurement is performed under static condition, and therefore it is not expected to give high-resolution signals as in MAS technique, this technique has an advantage that the spectral (structural) changes can be evaluated quantitatively in a single experiment in a non-destructive manner. This may clarify thermodynamically unstable transient phases during electrochemical cycling (non-equilibrium behavior). Also, it is not necessary to consider undesirable contaminations and possible lithium loss coming from disassembling the batteries and rinsing the electrodes, which are more or less inevitable for *ex situ* measurements. *In situ* NMR measurements have been reported mostly for anode materials. Letellier et al. showed that Li^+ ions were intercalated in graphitic carbon with a successive staging from LiC_{36} , LiC_{27} , LiC_{18} , LiC_{12} , and finally to LiC_6 , whereas they were intercalated in disorganized carbon in a different manner [25–28]. Similarly, Grey's group has indicated the lithium insertion into the silicon electrode [29]. However, there has been almost no report focusing on the lithium extraction/insertion behavior of the cathode materials *in situ* upon charging/discharging reactions because it is difficult to clearly observe their very broad signals in static NMR spectra [32]. We here performed *in situ* ^7Li NMR measurements for a $\text{Li}|\text{LiCoO}_2$ plastic cell battery during the electrochemical charge/discharge cycling, and successfully observed the lithium extraction/insertion behavior of the LiCoO_2 cathode material by optimizing the cell components and by using relatively high magnetic field. The dynamic growth and consumption of dendritic/mossy lithium on the Li anode was also clearly shown during the cycles.

2. Experimental

2.1. Electrochemical cell

We used a commercial LiCoO_2 (average particle size of 12 μm , Li/Co ratio = 1.01, Nichia) as a cathode active material. A mixture of LiCoO_2 powder, acetylene black (Denki Kagaku Kogyo), and polyvinylidene difluoride (PVDF, Kureha) with a weight ratio of 80:10:10 was spread with N-methylpyrrolidone (NMP) onto aluminum foil, and then dried at 80 °C under vacuum overnight to constitute a positive electrode. The electrode was cut with the dimensions of 15 mm $\times$ 5 mm, which included $\sim$ 13 mg of LiCoO_2 . A foil of metallic lithium (0.2 mm in thickness, >99.9%, Honjo Metal) was used as a counter electrode. We used the Celgard 2500 as a separator. The electrolyte applied here was 1 M LiClO_4 dissolved in anhydrous ethylene carbonate (EC) and diethyl carbonate (DEC) with a volumetric ratio of 1:1 (Kishida Chemical). Aluminum and copper strips were used as current collectors for positive and

negative electrodes, respectively. Then, the cell components were assembled together and soaked with the liquid electrolyte in a transparent silica-deposited gas-barrier film cell, which was hermetically sealed in an argon-filled glove box (<1.0 ppm oxygen). The assembly was designed according to the previous studies (Fig. S1) [28].

2.2. Electrochemical measurements

The charge–discharge curves were measured at room temperature on an automatic cycling/data recording system (HJ1001SD8, Hokuto Denko) in a galvanostatic operating mode. Two different runs were performed; the first run was carried out at a voltage window between 3.0 and 4.3 V for 3 charging/discharging cycles to examine the reversibility of the NMR signals in the cell during cycles. The charging was done with a rate of 0.12 C (32.0 mA/g) up to 4.3 V, at which voltage a short constant voltage process was included (total of 5 h). Similarly, the discharging was done with a rate of 32.0 mA/g down to 3.0 V with a constant voltage process (total of 5 h). The second run was separately carried out up to 5.0 V with a slower rate of 0.02 C (5.5 mA/g) for 50 h for a charging process to achieve the complete delithiation from LiCoO_2 .

2.3. *In situ* ^7Li NMR

The plate-like battery cell was packed into a polyethylene tube, which was horizontally placed in the center of 10 mm diameter solenoidal coil of a wide-bore static probe. The ^7Li NMR measurements were carried out at room temperature on a JNM-ECA600 spectrometer (JEOL) at a magnetic field of 14.1 T (^7Li working frequency of 233.2 MHz). A low-pass filter was connected on the wire for battery cycling to suppress the undesirable high-frequency noise components and improve the signal-to-noise ratio of the NMR signals. The battery cell was cycled galvanostatically during the spectral acquisitions.

A single pulse sequence was used with the $\pi/2$ pulse width of 3.5 μs optimized for LiCoO_2 and a preacquisition delay of 5.0 μs was applied prior to a relaxation delay of 1 s. It should be noted that the delay of 5.0 μs before the signal acquisition, which is required to suppress probe ringing background, lead to a small signal loss of $\sim$ 5% compared to the acquisition without the delay, but we emphasized that a series of spectra acquired in a single experiment can be treated quantitatively. We also note that spectra acquired with single pulse and echo sequences were essentially the same in linewidth and shape, indicating that the broad signal of LiCoO_2 is fully observable, but with higher intensity, by using the single pulse sequence. A total of 880 scans were collected for each spectrum. It takes $\sim$ 15 min over which the acquired spectrum is averaged, corresponding to the change of 0.03Li and 0.005Li per LiCoO_2 in the first and second run, respectively. Each acquisition was automatically run every half an hour. 1 M LiCl aqueous solution was used as ^7Li chemical shift reference at 0.0 ppm.

3. Results and discussion

3.1. Spectral evolutions on charging/discharging cycles

Fig. 1 shows the charge/discharge profile up to 4.3 V during 3 cycles. The capacities obtained during the cycles were 151/146 mAh/g (1st charging/discharging cycle), 147/144 mAh/g (2nd cycle), and 145/141 mAh/g (3rd cycle), respectively, indicating that about a half of Li^+ ion (0.52–0.55) in LiCoO_2 were reversibly involved in the electrochemical reactions between 3.0 and 4.3 V. ^7Li NMR spectra of the battery cell on the first charging/discharging cycle are shown in Fig. 2. A sharp peaks at $\sim$ 0 and $\sim$ 250 ppm are assigned to LiClO_4 in the liquid electrolyte and Li metal as negative

Fig. 1. Electrochemical profile of the Li||LiCoO₂ plastic cell battery during 3 charge/discharge cycles.

electrode, respectively. Here, it is noted that the radio frequency (rf) field applied to excite nuclear spin can penetrate into the bulk metal in a finite depth (skin-depth problem) [33]. In our experiments, the skin-depth of the ⁷Li rf pulse was estimated to be $\sim 8.4 \mu\text{m}$ [30], indicating that only the surface part of the lithium electrode could be excited for NMR signal detection. The broad peak centered at ~ 0 ppm, which covers from -100 to 100 ppm, is found to be the LiCoO₂ active material in the positive electrode [8]. We here emphasize that the ⁷Li signal of the cathode material can be successfully observed, and therefore that all the lithium components including cathode, anode, and electrolyte in the cell are visible simultaneously using ⁷Li NMR spectroscopy. Fig. 2a indicates that the intensity of LiCoO₂ peak decreases on charging

Fig. 2. *In situ* ⁷Li NMR spectra of the Li||LiCoO₂ plastic cell battery during the first charge/discharge cycle. (a) Charging; $x = 1.0$ prior to electrochemical measurements (black line), 0.97 (red) to 0.45 (blue), and (b) discharging; from 0.45 (blue) to 0.98 (black). The other spectra were drawn in gray lines. (For interpretation of the references to color in this figure legend, the reader is referred to the web version of the article.)

process. This is consistent with the electrochemical lithium extraction from LiCoO₂. It is noteworthy that the LiCoO₂ peak intensity immediately decreases to about a half of its original height on the first 15 min of charging process (corresponding to Li_{0.97}CoO₂, from black to red spectra in Fig. 2a) and then slowly decreases after the next 15 min. Here, it should be mentioned that the spectrum acquired for 15 min (corresponding to $\Delta x = 0.03\text{Li}$ in the first run) shows the average spectrum during 880 transients. Therefore, the spectrum accumulated during the first 15 min corresponds to the average on decreasing x from 1.00 to 0.97, and might be described as Li_{0.97 $\leq x < 1.00$} CoO₂ in a precise sense. However, we use the notation Li_{0.97}CoO₂ for simplification keeping in mind that the subscript value has a margin of $\Delta x \sim 0.03$ above the value. The growth of a broad signal was also observed at ~ 90 ppm, and this will be discussed in the next section. Concurrently, a new peak grows on the left side of the anodic lithium peak, which has been attributed to the dendritic and/or mossy metallic lithium on the lithium electrode [30]. Grey and coworkers have showed the peak shift of metallic lithium from 272 to 244 ppm with the lithium metal strip placed at the varying angle from 0° (vertical setting in the coil) to 90° (horizontal) with respect to the external magnetic field B_0 [34]. Such shifts in peak position are considered to come from the bulk magnetic susceptibility (BMS) effect that depends on the bulk shape (flat or spherical) of a metallic or paramagnetic material with respect to B_0 . It is noted that the battery cell is horizontally placed in the first run, and therefore the lithium electrode gives the Knight shift signal at ~ 250 ppm (Fig. S2). The newly appeared lithium peak has the signal at ~ 270 ppm, possibly indicating that the dendritic/mossy lithium is vertically attached on the horizontally placed lithium electrode as illustrated in Ref. [30]. It should be stressed that this is a clear indication of the dendritic/mossy lithium, which grows on the negative electrode during the charging process.

On discharging process, the reactions seem to be reversible; the broad peak centered at ~ 0 ppm increases in intensity with decreasing the 270 ppm peak intensity (Fig. 2b). This indicates that the Li⁺ ions are re-inserted in the layered Li _{x} CoO₂ structure, while the dendritic/mossy lithium on the surface of Li electrode would be dissolved into the liquid electrolyte. The spectral changes during the second and third charging/discharging cycles are still reversible and consistent with the electrochemical profile (Fig. S3). It should be noted that the spectra of LiCoO₂ at the end of each discharging process did not fully recover the intensity of the pristine LiCoO₂ observed before the electrochemical measurement, but similar to the one during the first 15 min of charging process, which corresponds to the lithium extraction of ~ 0.03 from LiCoO₂, i.e., Li_{0.97}CoO₂ in the positive electrode (Fig. S3h). This fact suggests that the discharged Li _{~ 1.00} CoO₂ holds a very small amount of paramagnetic Co⁴⁺, and that some Li⁺ ions ($\leq 0.03\text{Li}$) cannot be inserted back to be Li_{1.00}CoO₂ on discharging, being consistent with the irreversible capacity estimated from the electrochemical measurement. The possible deposition of solid electrolyte interface (SEI) on Li _{x} CoO₂ can cause an irreversible lithium loss and imperfect lithium re-insertion to Li _{x} CoO₂. Alternatively, the low electrical conductivity of Li_{1.00}CoO₂ (non-metallic nature [10]) may prevent the further insertion of Li⁺ ions into Li _{~ 0.97} CoO₂. It is emphasized that *in situ* ⁷Li NMR enables us to obtain unique information about such a small amount of lithium deficiency in LiCoO₂ on lithium re-insertion, which information is not accessible with XRD and ND. In turn, we found that a small amount of dendritic/mossy lithium is left at the end of each discharging process, and that increases with increasing cycle number (Fig. 3). The amount of dendritic/mossy lithium remains almost constant for 12 h after the electrochemical measurement. These results indicate that the dendritic/mossy lithium builds up dynamically with cycling the charge/discharge processes.

Fig. 3. Peak height evolution of the ^7Li signal for dendritic/mossy lithium during the charge/discharge cycles.

Fig. 4. Electrochemical profile of the plastic cell battery on charging process up to 5.0V.

3.2. Spectral evolutions of LiCoO_2 cathode on charging process up to 5.0V

The detailed spectral changes in $\text{LiCoO}_2/\text{Li}_x\text{CoO}_2$ signals were examined with decreasing x from 1 to 0 with a rate of 0.02 C in a separate run. The charging profile is shown in Fig. 4, which is similar to the previous studies [3,4]. Fig. 5 shows the spectral evolution of $\text{LiCoO}_2/\text{Li}_x\text{CoO}_2$ signals in the *in situ* ^7Li NMR spectra acquired at horizontal cell setting. Same measurements were performed at vertical setting in a separate run, and the spectra are shown in Fig. 6. The spectral evolutions in Figs. 5 and 6 are significantly different because of the BMS effect of electric conductive Li_xCoO_2 . We found that the spectral separation between LiCoO_2 and Li_xCoO_2 signals was clear at vertical setting. Therefore, we will discuss the structural changes of LiCoO_2 cathode material based on the spectral evolutions shown in Fig. 6. As observed in the 3-cycled run shown in Fig. 2, the peak intensity of LiCoO_2 immediately decreases to about a half of its original height on the first 45 min (2 acquisitions) of the charging process (Figs. 5a and 6a). This time period corresponds to the build-up of the charging profile from ~ 3.13 V (open circuit voltage) to 3.92 V (plateau voltage for O3-I/II biphasic region [1,35]), and the lithium removal of ~ 0.01 , i.e., $\text{Li}_{0.99}\text{CoO}_2$ in the positive electrode. The difference spectrum between the first 2 acquisitions showed a broad peak similar to that of pristine LiCoO_2 , indicating that the intensity loss is clearly related to the delithiation of LiCoO_2 . Ménétrier et al. have performed *ex situ* ^7Li MAS NMR measurements for the electrochemically delithiated Li_xCoO_2 , and reported a similar intensity reduction for the samples with $0.94 \leq x < 1.0$ [10]. It is considered that the diamagnetic Co^{3+} ion (electronic configuration, $3d^6$) should be oxidized to paramagnetic Co^{4+} ion ($3d^5$) for the charge compensation on the lithium extraction from LiCoO_2 . The paramagnetic Co^{4+} has the unpaired electronic spin(s), which induces the spin density transferred on Li nuclei near the Co^{4+} ion

Fig. 5. *In situ* ^7Li NMR spectra acquired at horizontal setting for Li_xCoO_2 cathode material ($0 \leq x \leq 1$) during the charging process from (a) $x = 1.0$ (black line), 0.99 (red) to 0.74 (green), and (b) from 0.72 (green) to 0.0 (blue). The other spectra were drawn in gray lines. (For interpretation of the references to color in this figure legend, the reader is referred to the web version of the article.)

Fig. 6. *In situ* ^7Li NMR spectra acquired at vertical setting for Li_xCoO_2 cathode material ($0 \leq x \leq 1$) during the charging process from (a) $x = 1.0$ (black line), 0.99 (red) to 0.74 (green), and (b) from 0.72 (green) to 0.0 (blue). (For interpretation of the references to color in this figure legend, the reader is referred to the web version of the article.)

Fig. 7. (a) Peak area ratio and (b) peak position of the deconvolved $\text{LiCoO}_2/\text{Li}_x\text{CoO}_2$ signals in the vertical setting ^7Li NMR spectra as a function of lithium content x in Li_xCoO_2 (Peak_1: LiCoO_2 component, Peak_2: Li_xCoO_2 component).

[10,16]. This would cause a strong transferred hyperfine interaction and a severe electron-nuclear dipolar interaction on a Li nucleus, which involves the apparent ^7Li intensity loss. The large reduction at the very early lithium extraction stage ($x \geq \sim 0.95$ in Li_xCoO_2) is believed to be due to the localized nature of the electron on Co^{4+} and its nearby Li^+ ions at this stage, which would reflect the very narrow solid solution region of LiCoO_2 O3-I phase [10].

With further lithium removal from Li_xCoO_2 , a new broad signal centered at ~ 90 ppm appears in accordance with the intensity decreases of LiCoO_2 signal (Fig. 6a) [8]. Fig. 7a shows the peak area ratio of the ~ 0 ppm- and ~ 90 ppm-centered signals by fitting the spectra (acquired at vertical setting) with one and two pseudo-Voigt functions for each (the fitting includes 8 additional components for the overlapping electrolyte and metallic lithium signals; examples of the spectral deconvolution are shown in Fig. S4, and the details are described in its caption). The new signal increased in intensity with the lithium removal down to $x \approx 0.75$, whereas the LiCoO_2 signal continued to decrease. According to Ménétrier *et al.*, the new signal can be associated with the Li_xCoO_2 O3-II phase [10]. This phase shows the Knight shift above 60 ppm associated with its high electrical conductivity, indicating the metallic behavior of Li^+ ions at this stage [10]. Fig. 7a suggests the coexistence of O3-I (LiCoO_2) and O3-II (Li_xCoO_2) phases in the region of $\sim 0.75 \leq x < 0.99$, supporting the previous studies [1–4,10,35]. An isosbestic point observed in the spectra for $0.86 \leq x \leq 0.98$ is also a clear indication of the coexistence of these two phases (Fig. 6a). It is interesting to note that the total ^7Li signal, which had been lost at $x \approx 0.99$, seems recovered in this electrochemical stage ($\sim 0.75 \leq x < 0.99$ in Fig. 7a). This comes from the intensity increase of the Knight shift signal. This indicates that the localized nature of electronic spins, which causes the apparent signal loss due to the strong dipolar interactions, changes to the

delocalized one of conductive electrons, leading to the apparent re-increase of the total ^7Li signal [10].

Li_xCoO_2 becomes a single component for $x < 0.75$. This phase starts to monotonically decrease in intensity with further delithiation (Figs. 6b and 7a). The signal reduction is consistent with decreasing the lithium content in Li_xCoO_2 estimated from the electrochemical measurement, indicating that it is quantitative below $x \approx 0.75$. Such intensity changes of the NMR signals can be quantitatively evaluated in principle in a suite of *in situ* measurements, demonstrating its advantage over the *ex situ* measurements.

Fig. 7b plots the ^7Li NMR peak position of the $\text{LiCoO}_2/\text{Li}_x\text{CoO}_2$ signals as a function of lithium content x in Li_xCoO_2 . It should be noted that the peak position may not strictly correspond to the isotropic shift especially for Li_xCoO_2 signal [8], because of its complex peak shape depending on the BMS effect with respect to B_0 as mentioned above [34]. We here discuss the evolution in peak position as a function of x . The peak position of the Li_xCoO_2 signal moves to higher frequency with decreasing x down to 0.5, which agrees with the previous *ex situ* NMR result [8,10]. However, it was shown that further delithiation lead to the peak shift of the Li_xCoO_2 signal to lower frequency. It is interesting to point out that the behavior of the ^7Li NMR shift for Li_xCoO_2 is analogous to the variation of the c lattice parameter of Li_xCoO_2 as a function of x reported by Amatucci *et al.* [2]. Li^+ ions are sandwiched in between CoO_2 layers in Li_xCoO_2 . It is therefore reasonable to consider that the ^7Li NMR shift of Li_xCoO_2 is correlated with the distance of the interlayer where Li^+ ions are placed (equal to one-third of the c lattice parameter). The NMR peak shifts to higher frequency for Li_xCoO_2 at $x \leq \sim 0.8$ correspond to the fact that the interlayer Li^+ ions are monotonously removed from Li_xCoO_2 O3-II phase. The removal of Li^+ ions increases the electrostatic repulsion between oxygen atoms in adjacent CoO_2 layers, which results in the expansion of c -axis of Li_xCoO_2 [2,10]. We believe that the apparent NMR peak positions for Li_xCoO_2 at $0.95 < x < 0.99$ will be fictitious because the $\text{LiCoO}_2/\text{Li}_x\text{CoO}_2$ signal separation was not well clear in this x range, which may provide unreliable fitting results (see also Fig. S4b). The monoclinic phase at $x \approx 0.5$ has the maximum c lattice parameter with the largest Knight shift. The monoclinic phase converts back to an O3-II phase for $x < 0.5$, again decreasing the c lattice parameter and the NMR peak position with further lithium removal. Unfortunately, it is not straightforward to explain the reason why the lattice parameter and the NMR shift seem correlated with each other. The Knight-shifted nature of ^7Li signal of Li_xCoO_2 indicates that Li 2s electrons partially act as delocalized conduction electrons. The Knight shift peak position is proportional to the number of the conduction electrons [25]. The higher frequency in Knight shift suggests the larger contribution of Li 2s to conduction band, which may be related to the increasing electric conductivity of Li_xCoO_2 with decreasing x down to ~ 0.5 [10]. If it is true, further delithiation should result in the decrease in electric conductivity.

The information of the electrolyte is also available in the *in situ* ^7Li NMR measurements. The ^7Li signal of LiClO_4 electrolyte shows a complicated feature because it is perturbed by the magnetic susceptibility of metallic lithium anode [33]. The signal did not show appreciable alterations in shape, position, and intensity up to 5.0 V (Figs. S5 and S6). This may indicate that the decomposition of liquid electrolyte is not significant (at least with respect to ^7Li) below 5.0 V with a constant current mode, although more detailed work should be needed to confirm it definitely with longer relaxation delays ($\gg 1$ s). We note that a new sharp peak was emerged in the electrolyte signal at 5.0 V with a constant voltage operation for several hours where the overall capacity was overcharged up to ~ 300 mAh/g (Fig. S5d). This would be the indication of the decomposition of electrolyte and/or the concomitant possible formation of SEI. This suggests that although the less resolved nature of the signals should be taken into account in static NMR condition, the

in situ NMR technique may be available for the investigation of the degradation of electrolyte and SEI formation during electrochemical operation, which gives useful information to improve the battery performance.

4. Conclusions

We performed *in situ* ^7Li NMR measurements for a $\text{Li}||\text{LiCoO}_2$ cell battery on electrochemical operation to investigate the spectral evolutions of the ^7Li NMR signal of Li_xCoO_2 ($0 \leq x \leq 1$) in detail. We observed the apparent ^7Li signal loss of LiCoO_2 at the very early period of the charging process, which is considered due to the severe signal broadening by the electron-nuclear dipolar interactions on the Li nuclei nearby the paramagnetic Co^{4+} ions. *In situ* NMR measurements confirmed that the ^7Li signal is highly sensitive to the appearance of only a small amount of paramagnetic center. Based on the present *in situ* NMR results, we defined the very narrow O3-I region of Li_xCoO_2 ($\sim 0.99 \leq x \leq 1$). Below $x = 0.99$, a broad Knight-shifted signal was emerged between 0 and 200 ppm. This signal showed a monotonous decrease in intensity below $x \approx 0.75$ in accordance with the electrochemical lithium de-intercalation from Li_xCoO_2 . It was suggested that the ^7Li NMR shift (Knight shift) for Li_xCoO_2 seemed correlated with the interlayer distance between the CoO_2 layers, where Li^+ ions are intercalated. Also, it was clearly observed that the dendritic/mossy lithium increased and decreased in intensity on charging and discharging process, respectively. A small amount of dendritic/mossy lithium was irreversibly left, and grew up with increasing cycle number. We stress that the *in situ* NMR/MRI (magnetic resonance imaging) monitoring of the dendritic/mossy lithium provides critical information for full understanding the condition of the dendrite formation [30,36,37] that will be also applicable to, for example, lithium-air or lithium-sulfur battery research. This study underscores the potency of *in situ* ^7Li NMR in parallel with electrochemical measurement, which provides quantitative information on lithium environments in cathode, anode, and electrolyte simultaneously. We believe that *in situ* NMR technique will be a good alternative to be considered to the other *in situ* analytical tools [38].

Acknowledgments

This work was supported by the Research and Development Innovative for Scientific Innovation of New Generation Battery (RISING) project from New Energy and Industrial Technology Development Organization (NEDO), Japan. The authors thank Dr. Yukinori Koyama at Kyoto University for his fruitful suggestions, and Mr. Takahiro Kakei for his experimental supports.

Appendix A. Supplementary data

Supplementary data associated with this article can be found, in the online version, at <http://dx.doi.org/10.1016/j.electacta.2013.06.120>.

References

- [1] J.N. Reimers, J.R. Dahn, Electrochemical and *in situ* X-ray diffraction studies of lithium intercalation in Li_xCoO_2 , *Journal of the Electrochemical Society* 139 (1992) 2091.
- [2] G.G. Amatucci, J.M. Tarascon, L.C. Klein, CoO_2 , the end member of the Li_xCoO_2 solid solution, *Journal of the Electrochemical Society* 143 (1996) 1114.
- [3] Z. Chen, Z. Lu, J.R. Dahn, Staging phase transitions in Li_xCoO_2 , *Journal of the Electrochemical Society* 149 (2002) A1604.
- [4] Z. Chen, J.R. Dahn, Methods to obtain excellent capacity retention in LiCoO_2 cycled to 4.5 V, *Electrochimica Acta* 49 (2004) 1079.
- [5] N. Sharma, V.K. Peterson, M.M. Elcombe, M. Avdeev, A.J. Studer, N. Blagojevic, R. Yusoff, N. Kamarulzaman, Structural changes in a commercial lithium-ion battery during electrochemical cycling: an *in situ* neutron diffraction study, *Journal of Power Sources* 195 (2010) 8258.
- [6] I. Nakai, K. Takahashi, Y. Shiraishi, T. Nakagome, F. Nishikawa, Study of the Jahn-Teller distortion in LiNiO_2 , a cathode material in a rechargeable lithium battery, by *in situ* X-ray absorption fine structure analysis, *Journal of Solid State Chemistry* 140 (1998) 145.
- [7] Y. Koyama, H. Arai, Z. Ogumi, I. Tanaka, Y. Uchimoto, Co K-edge XANES of LiCoO_2 and CoO_2 with a variety of structures by supercell density functional calculations with a core hole, *Physical Review B* 85 (2012) 075129.
- [8] B. Ouyang, X. Cao, H.W. Lin, S. Slane, S. Kostov, M. denBoer, S.G. Greenbaum, Lithium-7 NMR studies of $\text{Li}_{1-x}\text{CoO}_2$ battery cathodes, *Materials Research Society Symposium Proceedings* 369 (1995) 59.
- [9] P. Mustarelli, V. Massarotti, M. Bini, D. Capsoni, Transferred hyperfine interaction and structure in LiMn_2O_4 and Li_2MnO_3 coexisting phases: A XRD and ^7Li NMR-MAS study, *Physical Review B* 55 (1997) 12018.
- [10] M. Ménétrier, I. Saadoune, S. Levasseur, C. Delmas, The insulator-metal transition upon lithium deintercalation from LiCoO_2 : electronic properties and ^7Li NMR study, *Journal of Materials Chemistry* 9 (1999) 1135.
- [11] S. Levasseur, M. Ménétrier, E. Suard, C. Delmas, Evidence for structural defects in non-stoichiometric HT- LiCoO_2 : electrochemical, electronic properties and ^7Li NMR studies, *Solid State Ionics* 128 (2000) 11.
- [12] K. Guérin, M. Ménétrier, A. Févrière-Bouvier, S. Flandrois, B. Simon, P. Biensan, A ^7Li NMR study of a hard carbon for lithium-ion rechargeable batteries, *Solid State Ionics* 127 (2000) 187.
- [13] Y.J. Lee, C.P. Grey, Determining the lithium local environments in the lithium manganates $\text{LiZn}_{0.5}\text{Mn}_{1.5}\text{O}_4$ and Li_2MnO_3 by analysis of the ^6Li MAS NMR spinning sideband manifolds, *The Journal of Physical Chemistry B* 106 (2002) 3576.
- [14] M.C. Tucker, M.M. Doeff, T.J. Richardson, R. Fiñones, J.A. Reimer, E.J. Cairns, ^7Li and ^{31}P Magic angle spinning nuclear magnetic resonance of LiFePO_4 -type materials, *Electrochemical and Solid-State Letters* 5 (2002) A95.
- [15] P. Azais, L. Duclaux, A.-M. Faugère, F. Béguin, Reactive milling of graphite with lithium: application to lithium batteries, *Applied Physics Letters* 81 (2002) 775.
- [16] C.P. Grey, N. Dupré, NMR studies of cathode materials for lithium-ion rechargeable batteries, *Chemical Reviews* 104 (2004) 4493.
- [17] B.M. Meyer, N. Leifer, S. Sakamoto, S.G. Greenbaum, C.P. Grey, High field multinuclear NMR investigation of the SEI layer in lithium rechargeable batteries, *Electrochemical and Solid-State Letters* 8 (2005) A145.
- [18] K. Gotoh, M. Maeda, A. Nagai, A. Goto, M. Tansho, K. Hashi, T. Shimizu, H. Ishida, Properties of a novel hard-carbon optimized to large size Li ion secondary battery studied by ^7Li NMR, *Journal of Power Sources* 162 (2006) 1322.
- [19] J. Cabana, J. Shirakawa, G. Chen, T.J. Richardson, C.P. Grey, MAS NMR study of the metastable solid solutions found in the $\text{LiFePO}_4/\text{FePO}_4$ system, *Chemistry of Materials* 22 (2010) 1249.
- [20] L.J.M. Davis, I. Heinmaa, B.L. Ellis, L.F. Nazar, G.R. Goward, Influence of particle size on solid solution formation and phase interfaces in $\text{Li}_{0.5}\text{FePO}_4$ revealed by ^{31}P and ^7Li solid state NMR spectroscopy, *Physical Chemistry Chemical Physics* 13 (2011) 5171.
- [21] B. Key, M. Morcrette, J.-M. Tarascon, C.P. Grey, Pair distribution function analysis and solid state NMR studies of silicon electrodes for lithium ion batteries: understanding the (de)lithiation mechanisms, *Journal of the American Chemical Society* 133 (2011) 503.
- [22] M. Murakami, H. Yamashige, H. Arai, Y. Uchimoto, Z. Ogumi, Association of paramagnetic species with formation of LiF at the surface of LiCoO_2 , *Electrochimica Acta* 78 (2012) 49.
- [23] H. Hain, M. Scheuermann, R. Heinzmann, L. Wünsche, H. Hahn, S. Indris, Study of local structure and Li dynamics in $\text{Li}_{4+x}\text{Ti}_5\text{O}_{12}$ ($0 \leq x \leq 5$) using ^6Li and ^7Li NMR spectroscopy, *Solid State Nuclear Magnetic Resonance* 42 (2012) 9.
- [24] R.E. Gerald II, J. Sanchez, C.S. Johnson, R.J. Klingler, J.W. Rathke, *In situ* nuclear magnetic resonance investigations of lithium ions in carbon electrode materials using a novel detector, *Journal of Physics: Condensed Matter* 13 (2001) 8269.
- [25] M. Letellier, F. Chevallier, C. Clinard, E. Frackowiak, J.-N. Rouzaud, F. Béguin, M. Morcrette, J.-M. Tarascon, The first *in situ* ^7Li nuclear magnetic resonance study of lithium insertion in hard-carbon anode materials for Li-ion batteries, *The Journal of Chemical Physics* 118 (2003) 6038.
- [26] M. Letellier, F. Chevallier, F. Béguin, E. Frackowiak, J.-N. Rouzaud, The first *in situ* ^7Li NMR study of the reversible lithium insertion mechanism in disorganised carbons, *Journal of Physical Chemistry of Solids* 65 (2004) 245.
- [27] M. Letellier, F. Chevallier, F. Béguin, *In situ* ^7Li NMR during lithium electrochemical insertion into graphite and a carbon/carbon composite, *Journal of Physical Chemistry of Solids* 67 (2006) 1228.
- [28] M. Letellier, F. Chevallier, M. Morcrette, *In situ* ^7Li nuclear magnetic resonance observation of the electrochemical intercalation of lithium in graphite: 1st cycle, *Carbon* 45 (2007) 1025.
- [29] B. Key, R. Bhattacharyya, M. Morcrette, V. Seznéc, J.-M. Tarascon, C.P. Grey, Real-time NMR investigations of structural changes in silicon electrodes for lithium-ion batteries, *Journal of the American Chemical Society* 131 (2009) 9239.
- [30] R. Bhattacharyya, B. Key, H. Chen, A.S. Best, A.F. Hollenkamp, C.P. Grey, *In situ* NMR observation of the formation of metallic lithium microstructures in lithium batteries, *Nature Materials* 9 (2010) 504.
- [31] F. Poli, J.S. Kshetrimayum, L. Monconduit, M. Letellier, New cell design for *in situ* NMR studies of lithium-ion batteries, *Electrochemical Communications* 13 (2011) 1293.
- [32] B. Key, R. Bhattacharyya, H. Chen, C.P. Grey, *In-situ* solid state NMR studies on high rate lithium-ion batteries, in: *The 214th ECS Meeting Abstract*, 2008, #1210.

- [33] C. Kittel, Introduction to Solid State Physics, 8th edn, John Wiley, New York, 2004.
- [34] N.M. Trease, L. Zhou, H.J. Chang, B.Y. Zhu, C.P. Grey, In situ NMR of lithium ion batteries: bulk susceptibility effects and practical considerations, *Solid State Nuclear Magnetic Resonance* 42 (2012) 62.
- [35] T. Ohzuku, A. Ueda, Solid-state redox reactions of LiCoO_2 (R-3m) for 4 Volt secondary lithium cells, *Journal of the Electrochemical Society* 141 (1994) 2972.
- [36] R.E. Gerald II, R.J. Klingler, G. Sandí, C.S. Johnson, L.G. Scanlon, J.W. Rathke, ^7Li NMR study of intercalated lithium in curved carbon lattices, *Journal of Power Sources* 89 (2000) 237.
- [37] S. Chandrashekar, N.M. Trease, H.J. Chang, L.-S. Du, C.P. Grey, A. Jerschow, ^7Li MRI of Li batteries reveals location of microstructural lithium, *Nature Materials* 11 (2012) 311.
- [38] S.F. Amalraj, D. Aurbach, The use of in situ techniques in R&D of Li and Mg rechargeable batteries, *Journal of Solid State Electrochemistry* 15 (2011) 877.