TITLE:

Substantial appearance of origin of conductivity decrease in Y-doped BaZrO₃ due to Ba-deficiency

AUTHOR(S):

Han, Donglin; Kishida, Kyosuke; Inui, Haruyuki;
Uda, Tetsuya

CITATION:

Han, Donglin ...[et al]. Substantial appearance of origin of conductivity decrease in Y-doped BaZrO₃ due to Ba-deficiency. RSC Advances 2014, 4(60): 31589-31593

ISSUE DATE:

2014-07-16

URL:

<http://hdl.handle.net/2433/198562>

RIGHT:

© The Royal Society of Chemistry 2014.; 許諾条件により本文ファイルは2015-07-16に公開; この論文は出版社版ではありません。引用の際には出版社版をご確認ご利用ください。; This is not the published version. Please cite only the published version.

To: **RSC Advances**

Communication

Substantial Appearance of Origin of Conductivity Decrease in Y-Doped BaZrO₃ due to Ba-Deficiency

Donglin Han ^{a *}, Kyosuke Kishida ^a, Haruyuki Inui ^a, Tetsuya Uda ^{a *}

^a Department of Materials Science and Engineering, Kyoto University,

Yoshida Honmachi, Sakyo-ku, Kyoto 606-8501, Japan

* Corresponding authors: Donglin Han (han.donglin.8n@kyoto-u.ac.jp)

and Tetsuya Uda (materials_process@aqua.mtl.kyoto-u.ac.jp)

TEL: +81-75-753-5445, FAX: +81-75-753-5284

Abstract

Y-doped BaZrO₃ (BZY) is getting attention due to its high proton conductivity. But the proton conductivity decreased when Ba-deficiency was introduced. And we recently found that the system with an atomic ratio of Ba : Zr : Y of 0.9 : 0.8 : 0.2 contained two perovskite phases (Ba_{0.74}Zr_{0.55}Y_{0.45}O_{3-δ} and Ba_{0.90}Zr_{0.88}Y_{0.12}O_{3-δ}). In this work, by scanning transmission electron microscopy (STEM), accumulation of stacking faults with higher content of Zr, Y or vacancies than Ba was observed in the Ba_{0.74}Zr_{0.55}Y_{0.45}O_{3-δ} phase. We discuss the influence of the phase on the conductivity based on the results of water content and conductivity measurements, and therefore assume that the proton conduction in the Ba_{0.74}Zr_{0.55}Y_{0.45}O_{3-δ} phase might be very small.

Keywords: barium zirconate; perovskite; proton conductor; stacking fault; HAADF-STEM

1. Introduction

Y-doped BaZrO₃ (BZY), with a cubic perovskite structure (ABO₃), is a promising candidate as an electrolyte in protonic ceramic fuel cells (PCFCs) due to its high proton conductivity in a humid atmosphere at around 600 °C [1-3], and significant stability against reaction with CO₂ [4, 5]. Due to a highly refractory nature of BZY, heat-treatment at temperature higher than 1600 °C is necessary for its densification and grain growth [6, 7]. However, such high temperature treatment causes an unexpected evaporation of BaO [8], resulting in deficiency of Ba which negatively influences the proton conductivity of BZY [8, 9]. Several works have been conducted, and suggested a possible explanation that it was the partitioning of Y over A and B-sites which resulted in a decreased capability of water incorporation, and thereby lowered proton concentration and proton conductivity. [9, 10] In our recent work using X-ray diffraction (synchrotron radiation) and transmission electron microscopy, we found that a sample with a nominal atomic ratio of Ba : Zr : Y of 0.9 : 0.8 : 0.2 contained two compositionally different perovskite phases at 1600 °C. One has a composition of Ba_{0.90±0.04}Zr_{0.88±0.06}Y_{0.12±0.06}O_{3-δ}, and another is greatly Ba-deficient and Y-rich (Ba_{0.74±0.01}Zr_{0.55±0.03}Y_{0.45±0.03}O_{3-δ}) [11]. It is highly necessary to acquire more detailed information about this sample. In this work, conductivity and water content measurements were performed, and scanning transmission electron microscopy (STEM) was applied for microstructure observation.

2. Experimental

Samples with nominal atomic ratios of Ba : Zr : Y of 1.0 : 0.8 : 0.2 and 0.9 : 0.8 : 0.2, which were stoichiometric and nonstoichiometric (Ba-deficient), respectively, were prepared by a conventional solid state reaction method. Readers are referred to [11] for detailed information about processes for the sample preparation. Chemical compositions of Ba : Y : Zr for these samples were determined to be 0.97 : 0.81 : 0.19 and 0.89 : 0.81 : 0.19, respectively, by inductively coupled plasma atomic emission spectroscopy (ICP-AES) with SPS4000 (Seiko Instruments Inc., Japan) [11]. Pellet-like specimens, which were preliminarily sintered at 1600 °C, were re-heated to 1600 °C at 4 °Cmin⁻¹, then kept for 24 h, and finally quenched to room temperature. Microstructure was observed by STEM with JEM-2100F (JEOL, Japan) operated at 200 keV.

Conductivity measurement of pellet-like samples with electroless plated palladium electrodes was performed in wet H₂ atmosphere ($p_{\text{H}_2\text{O}} = 0.05 \text{ atm}$). The impedance spectra were collected by A. C. impedance spectroscopy in the frequency range from 10 Hz to 7 MHz using a frequency response analyzer (Solartron SI 1260, Solartron Analytical, UK) with applied A. C. voltage of 100 mV at temperature from 600 to 100 °C.

Karl-Fischer titration method was applied to determine water content in the samples. The pellet-like samples were broken into pieces about 2 mm in length, and hydrated in wet Ar atmosphere ($p_{\text{H}_2\text{O}} = 0.05 \text{ atm}$) for 72 h at the desired temperature. Readers are referred to our previous work [12-14] for detailed procedures.

3. Results

3.1 Conductivity and water content measurements

Fig. 1 shows bulk and grain boundary conductivities measured in wet H₂. Representative electrochemical impedance spectra collected at 150 °C are given in Fig. 2. Since semicircles belonging to the conduction of bulk (intra-grain) and grain boundary usually have capacitances with the order around 10⁻¹¹ and 10⁻⁹, respectively [13, 15], the conduction of bulk and grain boundary are thereby separated. The bulk conductivity of the stoichiometric sample (Ba : Zr : Y = 1.0 : 0.8 : 0.2) is estimated to be about three times higher than that of the Ba-deficient one (Ba : Zr : Y = 0.9 : 0.8 : 0.2), which is in agreement with the results reported by Yamazaki *et al.* [9]. In addition, the grain boundary conductivity of the Ba-deficient sample is about two orders smaller than that of the stoichiometric one. It is mainly attributed to the much smaller grain size of the Ba-deficient sample. [11] As shown in Fig. 3, the water content of the Ba-deficient sample is also about three times smaller than that of the stoichiometric one.

3.2 STEM observation

A low-magnification high-angle annular dark-field (HAADF)-STEM image of the nonstoichiometric sample (Ba : Zr : Y = 0.9 : 0.8 : 0.2) with lower bulk conductivity, taken along a [110] incidence, is shown in Fig. 4(a), in which existence of black lines can be clearly seen. These black lines were confirmed to be stacking faults from an atomic resolution HAADF-STEM image shown in Fig. 4(b).

The stacking faults were not perfectly straight at an atomic scale, since certain parts contained steps (marked as “A” in Fig. 4(b)), or terminated (marked as “B” in Fig. 3(b)). An atomic resolution HAADF-STEM image of this nonstoichiometric sample with a higher magnification is shown in Fig. 5(a). It can be determined that the stacking faults were mostly on $(\bar{1}11)$. Due to a strong contrast dependence on atomic number in the HAADF-STEM image [16, 17], atomic columns containing heavy Ba cations are imaged as brighter spots than those of Zr and Y cations. And brightest spots in Fig. 5(a) correspond to vertical Ba/O columns. A schematic of perspective view of unit cell of BZY (cubic structure, $Pm\bar{3}m$), and a projection of the unit cell along the $[110]$ direction which is corresponding to the area highlighted by a square in Fig. 5(a), were given in Fig. 5(b) and (c), respectively. From Fig. 5(a), it can be seen that along the $[1\bar{1}0]$ direction, there are seven to ten brightest spots, which depend on the place for observation, between adjacent stacking faults (two examples are given in Fig. 5(a)). And these spot rows shifted for $1/2 a$ at the two sides of the stacking faults along the $[001]$ direction.

In the area of the stacking faults, darker spots were seen, indicating a higher content of lighter atoms (Zr and Y) or vacancies. As shown in Fig. 4(a), in addition to the regions where stacking faults were observed to be arranged at an almost regular interval, regions containing small amount of stacking faults obviously coexisted. We also observed the stacking faults in the nominally stoichiometric sample (Ba : Zr : Y = 1.0 : 0.8 : 0.2) which had higher bulk conductivity, but the amount is very small (Fig. 6).

4. Discussion

Existence of superstructure in stoichiometric 20% Y-doped BaZrO₃ was suggested by Cervera *et al.* [18] due to the observation of superstructure reflection by XRD measurement. But in our previous powder XRD experiments using synchrotron radiation to study the sample with the same nominal composition [11], we did not observe any superstructure reflection corresponding to their superstructure phase. Although the stacking faults observed in this work appear to have an almost regular interval, as has been illustrated, the interval is not strictly equal (Fig. 5(a)). Therefore, it is reasonable to consider that these stacking faults should not be equalized as the reported superstructure.

In the nonstoichiometric sample, besides the coexistence of yttria, the ratio was previously determined to be 76.9 wt% (76.5 vol%) and 16.1 wt% (15.5 vol%) for the phases of Ba_{0.90}Zr_{0.88}Y_{0.12}O_{3-δ} and Ba_{0.74}Zr_{0.55}Y_{0.45}O_{3-δ}, which were thereby named as major and minor phases, respectively. [11] The minor phase is highly Y-rich and Ba-poor. Such minor phase is hardly to be found in the stoichiometric sample. [11] We therefore consider that the minor phase is the region where stacking faults concentrate. It is also reasonable to believe that the formation of stacking faults should be promoted by insufficient amount of Ba in the whole composition.

Proton conductivity decreased when Ba-deficiency was introduced, which was also confirmed by Yamazaki *et al.* using the samples with the same composition as this study. [9] Due to the lack of the information of the coexistence of two perovskite phases (namely the major and minor phases),

they considered that Y was driven to the A-site with an increasing Ba-deficiency, resulting in a homogeneous decrease in proton conductivity.

But based on the observation in this study, we consider that the reason might be attributed to the very low conductivity in the $\text{Ba}_{0.74}\text{Zr}_{0.55}\text{Y}_{0.45}\text{O}_{3-\delta}$ minor phase. It is because that the conductivity and water content of the nonstoichiometric sample are both estimated to be about three times smaller than those of the stoichiometric one, implying that the difference in conductivity is mainly resulted from the difference in proton concentration. Since proton concentration decreases with the decreasing Y content [19], and the volume ratio of the major phase is 76.5 vol%, it is quite reasonable that the measured proton conductivity and water content of the nonstoichiometric sample attributed mainly to the $\text{Ba}_{0.90}\text{Zr}_{0.88}\text{Y}_{0.12}\text{O}_{3-\delta}$ phase (major phase), in which the Y content is 0.12, almost half of that of the stoichiometric sample (0.2). In addition, it is also quite possible that protons cannot move across the stacking faults smoothly to generate high conductivity. That is, we assume that proton conduction is almost negligible in the minor phase. In addition to the minor phase, yttria (7.0 wt%) is not a good conductive phase. Such much less conductive phases also decrease the conductivity by their existence ratio and topology.

Schematics of proton conduction are given in Fig. 6. Detailed analysis of these stacking faults, especially clarification of the relationship between the stacking faults and proton conduction, is no doubt highly valuable in future.

5. Conclusions

Stacking faults were observed in the minor phase ($\text{Ba}_{0.74}\text{Zr}_{0.55}\text{Y}_{0.45}\text{O}_{3-\delta}$) in the sample with Ba-deficiency (nominal atomic ratio of Ba : Zr : Y = 0.9 : 0.8 : 0.2). These stacking faults accommodated a higher content of Zr, Y or vacancies than Ba. We assume that the proton conduction is negligibly small in the minor phase.

Acknowledgement

This study was supported by the Industrial Technology Research Grant Program in 2006 from the New Energy and Industrial Technology Development Organization (NEDO) of Japan.

References

1. K. Kreuer, *Annu. Rev. Mater. Res.*, 2003, 33, 333.
2. Y. Yamazaki, R. Hernandez-Sanchez and S.M. Haile, *Chem. Mater.*, 2009, 21, 2755.
3. D. Pergolesi, E. Fabbri, A. D'Epifanio, E.D. Bartolomeo, A. Tebano, S. Sanna, S. Licoccia, G. Balestrino and E. Traversa, *Nat. Mater.*, 2010, 9, 846.
4. K. Katahira, Y. Kohchi, T. Shimura and H. Iwahara, *Solid State Ionic*, 2000, 138, 91.
5. Y. Guo, Y. Lin, H. Shi, R. Ran and Z. Shao, *Chin. J. Catal.*, 2009, 30, 479.
6. P. Babilo and S.M. Haile, *J. Am. Ceram. Soc.*, 2005, 88, 2362.
7. S. Imashuku, T. Uda, Y. Nose, K. Kishida, S. Harada, H. Inui and Y. Awakura, *J. Electrochem.*

- Soc.*, 2008, 155, B581.
8. P. Babilo, T. Uda and S.M. Haile, *J. Mater. Res.*, 2007, 22, 1322.
9. Y. Yamazaki, R. Hernandez-Sanchez and S.M. Haile, *J. Mater. Chem.*, 2010, 20, 8158.
10. A.K. Azad, C. Savaniu, S. Tao, S. Duval, P. Holtappels, R.M. Ibberson and J.T.S. Irvine, *J. Mater. Chem.*, 2008, 18, 3414.
11. D. Han, K. Kishida, K. Shinoda, H. Inui and T. Uda, *J. Mater. Chem. A*, 2013, 1, 3027.
12. D. Han, Y. Okumura, Y. Nose and T. Uda, *Solid State Ionics*, 2010, 181, 1601.
13. D. Han, Y. Nose, K. Shinoda and T. Uda, *Solid State Ionics*, 2012, 213, 7.
14. D. Han, K. Shinoda, S. Tsukimoto, H. Takeuchi, C. Hiraiwa, M. Majima, and T. Uda, *J. Mater. Chem. A*, DOI: 10.1039/C4TA01689K.
15. S.M. Haile, D.L. West, and J. Campbell, *J. Mater. Res.*, **13**, 1576 (1998).
16. H. Yokobayashi, K. Kishida, H. Inui, M. Yamasaki and Y. Kawamura, *Acta Mater.*, 2011, 59, 7287.
17. K. Kishida, H. Yokobayashi, H. Inui, M. Yamasaki and Y. Kawamura, *Intermetallics*, 2012, 31, 55.
18. R.B. Cervera, Y. Oyama, S. Miyoshi, K. Kobayashi, T. Yagi and S. Yamaguchi, *Solid State Ionic*, 2008, 179, 236.
19. Y. Yamazaki, P. Babilo and S.M. Haile, *Chem. Mater.*, 2008, 20, 6352.

Fig. 1 Bulk and grain boundary conductivity of the samples with nominal atomic ratios of Ba : Zr : Y of 1.0 : 0.8 : 0.2 and 0.9 : 0.8 : 0.2 in wet H₂ ($p_{\text{H}_2\text{O}} = 0.05$ atm). The samples were sintered at 1600 °C in air for 24 h, and finally quenched in ambient atmosphere.

Fig. 2 Representative electrochemical impedance spectra of the samples with the nominal compositions of (a) $\text{BaZr}_{0.8}\text{Y}_{0.2}\text{O}_{3-\delta}$ and (b) $\text{Ba}_{0.9}\text{Zr}_{0.8}\text{Y}_{0.2}\text{O}_{3-\delta}$, collected in $\text{H}_2 - 5\% \text{H}_2\text{O}$ at 150°C . The insets show the spectra at high frequency range belonging to the bulk conduction. S and L are the surface area and thickness of the sample, respectively. R_{bulk} , R_{GB} , C_{bulk} and C_{GB} are the resistance and capacitance for bulk and grain boundary conduction.

Fig. 3 Weight gain of the samples with nominal atomic ratios of Ba : Zr : Y of 1.0 : 0.8 : 0.2 and 0.9 : 0.8 : 0.2 due to hydration in wet Ar ($p_{\text{H}_2\text{O}} = 0.05 \text{ atm}$) at various temperature for 72 h. The samples were sintered at 1600 °C in air for 24 h, and finally quenched in ambient atmosphere.

Fig. 4 (a) Low-magnification and (b) atomic resolution HAADF images of the stacking faults in the sample with nominal atomic ratio of Ba : Zr : Y of 0.9 : 0.8 : 0.2, taken along a [110] incidence. Some specific areas of stacking faults, which (A) contain steps or (B) terminate, are highlighted by dashed circles.

Fig. 5 (a) An atomic resolution HAADF-STEM image of the stacking faults in the sample with nominal atomic ratio of Ba : Zr : Y of 0.9 : 0.8 : 0.2 taken along a $[110]$ incidence. (b) A perspective view, and (c) a projection taken along the $[110]$ direction of the unit cell of Y-doped BaZrO_3 (cubic structure, $Pm\bar{3}m$) are also given. Rows of bright spots, corresponding to atomic columns containing Ba/O and Zr/Y cations, shifted for $1/2 a$ (a : lattice constant of this Y-doped BaZrO_3 phase with a cubic perovskite structure) along the $[001]$ direction at the two sides of the stacking faults.

Fig. 6 An atomic resolution HAADF-STEM image of the sample with the nominal atomic ratio of Ba : Zr : Y of 1.0 : 0.8 : 0.2, taken along a $[110]$ incidence. The stacking faults were highlighted by arrows.

Fig. 7 Schematics of proton conduction in the samples with (a) stoichiometric (Ba : Zr : Y = 1.0 : 0.8 : 0.2), and (b) nonstoichiometric (Ba : Zr : Y = 0.9 : 0.8 : 0.2) composition. It is considered to be highly possible that the proton conduction in the minor phase of the nonstoichiometric sample is very low.