TITLE:

Stability of α' -Fe₁₆N₂ in hydrogenous atmospheres

AUTHOR(S):

Yamamoto, Shinpei; Gallage, Ruwan; Isoda, Seiji; Ogata, Yasunobu; Kusano, Yoshihiro; Kobayashi, Naoya; Ogawa, Tomoyuki; Hayashi, Naoaki; Takahashi, Migaku; Takano, Mikio

CITATION:

Yamamoto, Shinpei ...[et al]. Stability of α' -Fe₁₆N₂ in hydrogenous atmospheres. Chemical communications 2014, 50(53): 7040-7043

ISSUE DATE:

2014-05-22

URL:

<http://hdl.handle.net/2433/198772>

RIGHT:

This journal is © The Royal Society of Chemistry 2014.; この論文は出版社版ではありません。引用の際には出版社版をご確認ご利用ください。;
This is not the published version. Please cite only the published version.

Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxxx

ARTICLE TYPE

Stability of α'' -Fe₁₆N₂ in hydrogenous atmospheres

Shinpei Yamamoto^{*a}, Ruwan Gallage^{a,b}, Seiji Isoda^a, Yasunobu Ogata^c, Yoshihiro Kusano^d, Naoya Kobayashi^b, Tomoyuki Ogawa^e, Naoaki Hayashi^a, Migaku Takahashi^c, and Mikio Takano^a

Received (in XXX, XXX) Xth XXXXXXXXX 20XX, Accepted Xth XXXXXXXXX 20XX

DOI: 10.1039/b000000x

We revealed inherent instability of α'' -Fe₁₆N₂ in hydrogenous atmospheres due to denitrification toward α -Fe by forming NH₃ at the particle surface. Coating the particle surface with SiO₂ to suppress formation of NH₃ has proven to be a simple yet powerful method to enhance stability in hydrogenous atmospheres.

Utilization of hydrogen energy, which can be produced from various renewable energy sources and emits no greenhouse gases in use, has potential to contribute to the formation of sustainable society. Replacement of fossil fuels by hydrogen gas thus has been studied for all levels of social systems covering from infrastructures to consumer devices. As we prepare to start the hydrogen society, development of materials stable in hydrogenous atmospheres is highly needed.¹ Here we examine the stability of a new powerful magnetic material, α'' -Fe₁₆N₂, which may potentially be applied to, e.g., motors to be used for supply and transportation of hydrogen gas.² As α'' -Fe₁₆N₂ has to be prepared and processed under reducing conditions, it is also important to understand behaviors in hydrogen gas.

α'' -Fe₁₆N₂ is a meta-stable compound with body-centered tetragonal (bct) structure, which is essentially α -Fe containing the nitrogen atoms ordered on interstitial sites. This material has attracted much interest since the first report of a 'giant' magnetic moment.³ Although the formation of this phase was already reported in 1951,⁴ it was difficult to obtain monophasic samples, and this made the reported saturation magnetization (M_s) widely scattered.⁵ We recently have succeeded in preparing high-purity powdered samples in a large size of 10 g/batch and reported that the M_s and the uniaxial magnetocrystalline anisotropy, K_u , were as high as 234 emu/g and 1×10^7 erg/cm³ at 5 K, respectively.⁶ Potential use of this material for magnetic recording and microwave absorption has attracted much attention.⁷ Recently, another possible application as a permanent magnet has emerged.^{8,9} The maximum energy product (BH_{max}), the figure of merit that measures the performance of a permanent magnet, calculated using the experimentally determined M_s and K_u values reaches more than 100 MGOe,[‡] which is about 1.6 times larger than that of the currently strongest Nd-Fe-B magnet (~ 64 MGOe).

For practical applications quantitative understanding of stability-related matters is highly needed for this meta-stable material. We recently reported detailed studies about the stability in inert atmospheres, nitrogen and argon, where decomposition

Fig. 1 Schematic representation of decomposition of α'' -Fe₁₆N₂ in hydrogenous atmospheres. Formation of NH₃ (k_{Reac}) and diffusion of the interstitial nitrogen atoms (k_{Diff}) determine the overall reaction rate in the early and the latter stage of the decomposition, respectively.

proceeds by intra-solid atomic rearrangements to form a 4 : 1 molar mixture of α -Fe and γ' -Fe₄N, without releasing nitrogen.¹⁰ Decomposition in reactive atmospheres like hydrogen gas could be very different because of possible dominance of solid-gas reactions. Here, we report a quantitative study on stability of α'' -Fe₁₆N₂ in hydrogenous atmospheres using *in-situ* powder X-ray diffraction (XRD). Based on the understanding about the decomposition process gained, we have succeeded in developing a simple yet powerful method for enhancing the stability. The current results will open ways to wide applications of α'' -Fe₁₆N₂ in hydrogenous atmospheres.

The α'' -Fe₁₆N₂ samples used in this study were prepared in two steps, oxide-to-metal reduction in a H₂ stream and subsequent metal-to-nitride conversion using an NH₃ stream, within a reactor chamber attached to the X-ray diffractometer used (see Electric Supplementary Information (ESI)).⁶ In the starting samples, only α'' -Fe₁₆N₂ and ~ 7 wt% of α -Fe were detected by XRD (see Run#0 in Figures and Tables S1 ~ S7 in ESI). The average crystallite size of the nitride estimated by using the Scherrer formula was *ca.* 28 ~ 36 nm (see Table S8 in ESI). For the *in-situ* XRD measurements, each sample was kept at a constant temperature of $T = 393, 398, 403, 413$ or 423 K for a certain period of time (t) in a hydrogenous atmosphere (see ESI for details). Figures S1 ~ S5 in ESI show those collected in pure hydrogen atmosphere (Experiments A ~ E). With increasing heating time, α'' -Fe₁₆N₂ decreased while α -Fe increased. No other crystalline phases were detected, revealing that the decomposition proceeded via loss of the interstitial nitrogen atoms. As evidenced by the mass spectroscopic analyses done in the same atmosphere, the interstitial nitrogen atoms were removed in the form of NH₃ although simultaneous evolution of a

Table 1: Apparent rate constants.

Experiment ^{a)}	A	B	C	D	E	F
T (K)	393	398	403	413	423	413
k_{Reac} (h^{-1})	0.10	0.14	0.23	0.45	0.69	0.28
k_{Diff} (10^{-2} h^{-1})	0.25	0.42	0.66	0.76	2.25	0.91

a) Experiments A~E and F were carried out in H_2 and H_2/He mixture, respectively. See also ESI for details.

trace amount of N_2 was also detected (Figure S8 in ESI). Thus, it can be said that the decomposition essentially proceeds via a solid-gas reaction pathway represented as:

This is totally different from the situations in inert atmospheres (N_2 , Ar) where no solid-gas reactions take place and the decomposition proceeds via intra-solid atomic rearrangements to form the 4 : 1 molar mixture of $\alpha\text{-Fe}$ and $\gamma\text{-Fe}_4\text{N}$.¹⁰

In order to estimate the decomposition kinetics quantitatively, the relative weight fractions of $\alpha''\text{-Fe}_{16}\text{N}_2$ ($w_{\text{Fe}_{16}\text{N}_2}$) and $\alpha\text{-Fe}$ (w_{Fe}) were estimated by the Rietveld analysis of the XRD patterns (see Tables S1 ~ S5 in ESI). The fraction of decomposition, D , can be expressed as:

$$D = 1 - w_{\text{Fe}_{16}\text{N}_2}(T, t) / w_{\text{Fe}_{16}\text{N}_2}(T, 0), \quad (2)$$

where $w_{\text{Fe}_{16}\text{N}_2}(T, 0)$ and $w_{\text{Fe}_{16}\text{N}_2}(T, t)$ represent the fractions of $\alpha''\text{-Fe}_{16}\text{N}_2$ before and after the H_2 treatment at T [K] for a certain period of time (t), respectively. Figure S9 in ESI show the time dependence of decomposition at various temperatures collected in pure hydrogen atmosphere.

It seems that the process is divided into two main parts with a boundary region centered at around $D = 0.6 \sim 0.9$. Irrespective of the heating temperature the early stage is well represented by the zero order reaction model formulated as:

$$D = k_{\text{Reac}} \cdot t, \quad (3)$$

where k_{Reac} is the apparent rate constant¹¹, while the 3-dimensional diffusion model formulated as below applies to the latter stage:

$$[1 - (1 - D)^{1/3}]^2 = k_{\text{Diff}} \cdot t, \quad (4)$$

where k_{Diff} is an apparent rate constant¹¹ (see the red and green lines in Figures S9a ~ e in ESI and the least-squares fitting values of k_{Reac} and k_{Diff} in Table 1).

As mentioned above, $\alpha''\text{-Fe}_{16}\text{N}_2$ decomposes by losing the interstitial nitrogen atoms in the form of NH_3 . The applicability of the zero order reaction model to the early stage strongly suggests the rate determining process being the formation of NH_3 on the particle surface[#]; the supply of nitrogen atoms from the inside to the particle surface is fast enough. On the other hand, for the latter stage the rate determining process is switched to the diffusion of nitrogen atoms to the surface. As schematically illustrated in Fig. 1, as the surface $\alpha\text{-Fe}$ slab becomes thicker the supply of nitrogen to the surface becomes short. It should be noted here that lattice parameters of the nitride phase change with prolonged H_2 -treatment; a increases while c decreases. This tendency is prominent at higher temperatures and probably due to less N atom content than in the ideal composition.

The apparent rate constants of these processes, k_{Reac} and k_{Diff} , can be expressed as below using an Arrhenius-type equation ($M = \text{Reac, Diff}$):

$$k_M = k_{0,M} \cdot \exp(-\Delta E_M / RT), \quad (5)$$

Fig. 2 Plots of (a) $\ln(k_{\text{Reac}})$ and (b) $\ln(k_{\text{Diff}})$ vs. inverse temperature ($1/T$). The solid and open symbols represent the experimental data collected in H_2 and H_2/He mixture, respectively. The solid lines represent the least-squares fittings.

Fig. 3 D of the SiO_2 -coated (red symbols) and the uncoated (black symbols) $\alpha''\text{-Fe}_{16}\text{N}_2$ plotted against t at 423 K. Inset shows typical TEM images of the SiO_2 -coated $\alpha''\text{-Fe}_{16}\text{N}_2$. The surface is uniformly coated with SiO_2 layer (thickness, ca. 10 nm). For details of the SiO_2 -coating, see ESI.

where $k_{0,M}$, ΔE_M , R , and T are the frequency factor, apparent activation energy, gas constant and absolute temperature, respectively. The results of the Arrhenius plot are shown in Fig. 2. The values of $k_{0,\text{Reac}}$ and ΔE_{Reac} thus determined are $1.77 \times 10^{11} \text{ h}^{-1}$ and 92 kJ/mol, respectively. Formation of NH_3 from atomic nitrogen and gaseous H_2 on the surface must be multi-staged, including adsorption of H_2 molecule on the surface, scission of H-H bond, formation of N-H bonds, and desorption of NH_3 molecules from the surface. Determination of the stage most responsible for these kinetic parameters is beyond the scope of this paper. Similarly, $k_{0,\text{Diff}}$, and ΔE_{Diff} have been determined to be $3.24 \times 10^9 \text{ h}^{-1}$ and 91 kJ/mol, respectively. Apparent activation energy for diffusion of nitrogen atoms in $\alpha\text{-Fe}$ and Fe-N martensites have been reported to be ca. 71 kJ/mol for $\alpha\text{-Fe}$,¹² 87 and 95 kJ/mol for 1.1 and 2.46 ~ 2.71 wt% nitrogen-doped Fe-N martensites, respectively.^{13,14} Actual concentration of nitrogen in the denitrified layer may vary depending on, e.g., reaction time (t) and depth from the surface. However, it should be in between 0 ($\alpha\text{-Fe}$) and 3 wt% ($\alpha''\text{-Fe}_{16}\text{N}_2$). The obtained ΔE_{Diff} of 91 kJ/mol seems to be a reasonable value for diffusion of nitrogen atoms in such a concentration range.

To test the validity of the above analyses, we additionally studied decomposition in the equivolume mixture of hydrogen and helium gases (Experiment F, see Figure and Table S6 in ESI). Partial pressure of hydrogen gas should have a strong effect on the rate of NH_3 formation on the particle surface but have little effect on the intra-particle diffusion of the interstitial nitrogen atoms. Figure S10a in ESI shows a plot of D vs. t together with

that collected in pure hydrogenous atmosphere at the same temperature (Experiment D). Decomposition seems to slow down only in the earlier stage. The apparent rate constants, *i.e.*, k_{Reac} and k_{Diff} , determined by using eqs.(3) and (4) strongly support the validity of these models (see Figure S10b in ESI for the analyses); only k_{Reac} decreases while k_{Diff} remains almost unchanged (the open symbols in Figures 2a and b).

Apparent activation energy for decomposition is known to be a good measure of stability. The values for hydrogenous atmospheres, which are *ca.* 90 kJ/mol at most, are less than half that for inert atmospheres (199 kJ/mol),¹⁰ indicating the inherent instability of $\alpha''\text{-Fe}_{16}\text{N}_2$ in hydrogenous atmospheres. For practical application we need a method to improve the stability. Considering the crucial importance of NH_3 -forming reaction on the surface, we carried out a proof-of-concept experiment, protection of surface from hydrogen by SiO_2 -coating (Experiment G, see Figure and Table S7 in ESI). The time dependences of decomposition rate, D , at 423 K before and after the coating are compared in Fig. 3. It is definitely evident that the decomposition was markedly suppressed by the coating. Understanding of the surface coating effects in terms of coating materials and their thicknesses would be topics of forthcoming papers.

In conclusion, we have successfully revealed the decomposition processes and kinetics of $\alpha''\text{-Fe}_{16}\text{N}_2$ in hydrogenous atmospheres. The decomposition proceeds via a solid-gas reaction mechanism, *i.e.*, loss of the interstitial nitrogen atoms by forming NH_3 on the surface to give $\alpha\text{-Fe}$. This is very different from the situations in inert atmospheres where decomposition proceeds by intra-solid atomic rearrangements to form 4 : 1 molar mixture of $\alpha\text{-Fe}$ and $\gamma'\text{-Fe}_4\text{N}$. The process is divided into two main parts with a boundary region centered at around $D = 0.6\sim 0.9$; formation of NH_3 on the particle surface and intra-particle diffusion of the interstitial nitrogen atoms are the rate determining processes in the early and the latter stage of the decomposition, respectively. Activation energies for these processes are *ca.* 90 kJ/mol at most, revealing the inherent instability of $\alpha''\text{-Fe}_{16}\text{N}_2$ in hydrogenous atmosphere. It is thus crucially important to enhance the stability for applications in hydrogenous atmospheres. Coating with SiO_2 is proven to be a simple yet powerful method for this purpose. The current results will open ways to wide applications of $\alpha''\text{-Fe}_{16}\text{N}_2$ in a coming hydrogen society.

This work was partly supported by the Research and Development of Alternative New Permanent Magnetic Materials to Nd-Fe-B Magnets Project from NEDO of Japan, the Japanese national project of Technology Research Association of Magnetic Materials for High-Efficiency Motors for Next-Generation Cars, and JSPS KAKENHI (No. 21226007).

Notes and references

^a Institute for Integrated Cell-Material Sciences (iCeMS), Kyoto University, Yoshida Ushinomiya, Sakyo, Kyoto 606-8501, Japan

^b T&T Innovations Inc., 1-4 Meijishinkai, Otake, Hiroshima 739-0652, Japan

^c New Industry Creation Hatchery Center (NICHe), Tohoku University, 6-6-10 Aza-Aoba, Aramaki, Aoba, Sendai 980-8579, Japan.

^d Department of Fine & Applied Arts, Kurashiki University of Science and the Arts, 2640 Nishinoura, Tsurajima, Kurashiki, Okayama 712-8505, Japan

^e Department of Electronic Engineering, Graduate School of Engineering, Tohoku University, 6-6-05 Aza-Aoba, Aramaki, Aoba, Sendai 980-8579, Japan

[†] Electronic Supplementary Information (ESI) available: Details of the *in-situ* XRD, SiO_2 -coating, and the other characterization methods, *in-situ* XRD patterns (Figures S1 ~ S7), mass spectroscopic data (Figure S8), analyses of $D - t$ data collected in H_2 (Figure S9) and in H_2/He mixture (Figure S10), Rietveld refinement results (Tables S1 ~ S7) and average crystallite size of the $\alpha''\text{-Fe}_{16}\text{N}_2$ sample (Table S8). See DOI: 10.1039/b000000x/

[‡] Calculated by using the following parameters under the assumption of 100 % orientation; M_s at room temperature (226 emu/g)⁶, specific gravity of $\alpha''\text{-Fe}_{16}\text{N}_2$ (7.44), and K_u (1×10^7 erg/cm³)⁶. Coercivity was assumed to be equal to the anisotropy field, H_a , defined as $H_a = 2K_u / M_s$.

[#] Volume ratio of $\alpha\text{-Fe}$ to $\alpha''\text{-Fe}_{16}\text{N}_2$ is *ca.* 0.92 by using the following lattice constants of $\alpha''\text{-Fe}_{16}\text{N}_2$ ($a = 0.572$ nm, $c = 0.630$ nm) and $\alpha\text{-Fe}$ ($a = 0.287$ nm) (see Tables S1 ~ S7 in ESI), which leads to the expected decrease in surface area to be *ca.* 5 % by assuming a spherical sample shape. Thus, it is reasonable to assume that NH_3 forms on the surface whose area is almost constant during the decomposition. Accordingly, the linear $D - t$ relationship under these reaction conditions strongly indicates that the rate determining process of this stage is formation of NH_3 .

1 (a) M. Kappes, M. Iannuzzi and R. M. Carranza, *J. Electrochem. Soc.*, 2013, **160**, C168. (b) T. Onuma and L. Nakamura, *ISIJ International*, 2012, **52**, 234. (c) E. T.-Gutelmacher and D. Eliezer, *JOM*, 2005, **57**, 46. (d) N. Eliaz, A. Shachar, B. Tal and D. Eliezer, *Eng. Failure Anal.*, 2002, **9**, 167. (e) M. Nagumo, *ISIJ International*, 2001, **41**, 590.

2 (a) K. Ohshima, P2003-166080A(Japan). (b) S. Morishima, P2007-66552A(Japan). (c) K. Yamamiya, P2008-14459A(Japan). (d) D. Mori, P2007-303547A(Japan). (e) H. Kato, P2007-24015A(Japan). (f) Y. Jufuku, P2007-154787A(Japan). (g) N. Yamagishi, P2009-138713A (Japan). (h) N. Yamagishi, *Phys. Lett.*, 2010-48215A(Japan).

3 T. K. Kim and M. Takahashi, *Appl. Phys. Lett.*, 1972, **20**, 492.

4 K. H. Jack, *Proc. R. Soc. A* 1951, **208**, 216.

5 (a) M. Takahashi and H. Shoji, *J. Magn. Magn. Mater.*, 2000, **208**, 145. (b) K. Nakajima and S. Okamoto, *Appl. Phys. Lett.*, 1990, **56**, 92. (c) M. Komuro, Y. Kozono, N. Hanazono and Y. Sugita, *J. Appl. Phys.*, 1990, **67**, 5126. (d) C. Gao, W. D. Doyle and M. Shamasuzzoha, *J. Appl. Phys.*, 1993, **73**, 6579. (e) M. Q. Huang, W. E. Wallace, S. Simizu and S. G. Sankar, *J. Magn. Magn. Mater.*, 1994, **135**, 226. (f) H. Jiang, K. Tao and H. Li, *J. Phys. Condens. Mater.*, 1994, **6**, L279. (g) C. Ortiz, G. Dumpich and A. H. Morrish, *Appl. Phys. Lett.*, 1994, **65**, 2737. (h) X. Bao, R. M. Metzger and M. Carbuticchio, *J. Appl. Phys.*, 1994, **75**, 5870. (i) J. M. D. Coey, K. O'Donnel, Q. Qinian, E. Touchais and H. K. Jack, *J. Phys. Condens. Mater.*, 1994, **6**, L23. (j) N. Ji, L. F. Alard, E. Lara-Curzio and J.-P. Wang, *Appl. Phys. Lett.*, 2011, **98**, 092506. (k) T. Hattori, N. Kamiya and Y. Kato, *J. Mag. Soc. Jpn.*, 2001, **25**, 927. (l) S. Kikkawa, A. Yamada, Y. Masubuchi and T. Takeda, *Mater. Res. Bull.*, 2008, **43**, 3352. (m) K. Shibata, Y. Sasaki, M. Kishimoto, H. Yanagihara and E. Kita, *J. Magn. Soc. Jpn.*, 2006, **30**, 501. (n) T. Ogi, A. B. D. Nandiyanto, Y. Kisakibaru, T. Iwaki, K. Nakamura and K. Okuyama, *J. Appl. Phys.*, 2013, **113**, 164301. (o) M. Widenmeyer, T. C. Hansen and R. Niewa, *Z. Anorg. Allg. Chem.*, 2013, **639**, 2851.

6 T. Ogawa, Y. Ogata, R. Gallage, N. Kobayashi, N. Hayashi, Y. Kusano, S. Yamamoto, K. Kohara, M. Doi, M. Takano and M. Takahashi, *Appl. Phys. Express*, 2013, **6**, 073007-1.

7 (a) Y. Sasaki, N. Usuki, K. Matsuo and M. Kishimoto, *IEEE Trans. Magn.*, 2005, **41**, 3241. (b) M. Takahashi, D. Djayaprawira and H. Shoji, US Patent 6,841,259. (c) K. Shimba, N. Tezuka and S. Sugimoto, *J. Japan Inst. Metals*, 2010, **74**, 209.

8 J. M. D. Coey, *IEEE Trans. Magn.*, 2011, **47**, 4671.

9 K. Bourzac, *MIT Technol. Rev.*, 2011, **114**, 58.

10 S. Yamamoto, R. Gallage, T. Ogata, Y. Kusano, N. Kobayashi, T. Ogawa, N. Hayashi, K. Kohara, M. Takahashi and M. Takano, *Chem. Commun.*, 2013, **49**, 7708.

11 A. Khawam and D. R. Flanagan, *J. Phys. Chem. B* 2006, **110**, 17315.

12 C. Wert and C. Zener, *Phys. Rev.*, 1949, **76**, 1169.

13 E. J. Mittermeijer, L. Cheng, P. J. van der Schaaf, C. M. Brakman and B. M. Korevaar, *Metall. Trans. A*, 1988, **19A**, 925.

14 J. Fall and J. M. R. Genin, *Metall. Trans. A*, 1996, **27A**, 2160.

Graphical and Textual Abstract for the Table of Content

Coating the particle surface with SiO_2 has proven to be a simple yet powerful method to enhance stability of α'' - Fe_{16}N_2 in hydrogenous atmospheres.