TITLE:

Thermo-reversible supramolecular hydrogels of trehalose-type diblock methylcellulose analogues

AUTHOR(S):

Yamagami, Mao; Kamitakahara, Hiroshi; Yoshinaga, Arata; Takano, Toshiyuki

CITATION:

Yamagami, Mao ...[et al]. Thermo-reversible supramolecular hydrogels of trehalose-type diblock methylcellulose analogues. Carbohydrate Polymers 2018, 183: 110-122

ISSUE DATE:

2018-03-01

URL:

<http://hdl.handle.net/2433/231416>

RIGHT:

© 2018. This manuscript version is made available under the CC-BY-NC-ND 4.0 license <http://creativecommons.org/licenses/by-nc-nd/4.0/>. The full-text file will be made open to the public on 1 March 2019 in accordance with publisher's 'Terms and Conditions for Self-Archiving'. This is not the published version. Please cite only the published version. この論文は出版社版ではありません。引用の際には出版社版をご確認ください。

1 Thermo-reversible supramolecular hydrogels of trehalose-type diblock 2 methylcellulose analogues

3
4 Mao YAMAGAMI, Hiroshi KAMITAKAHARA, Arata YOSHINAGA, Toshiyuki TAKANO

5 Graduate School of Agriculture, Kyoto University, Sakyo-ku, Kyoto 606-8502, Japan

6 Corresponding Author: hkamitan@kais.kyoto-u.ac.jp

7 Phone: +81-75-753-6257

8 Fax: +81-75-753-6300

9

10 ABSTRACT:

11 This paper describes the design and synthesis of new trehalose-type diblock methylcellulose
12 analogues with nonionic, cationic, and anionic cellobiosyl segments, namely

13 1-(tri-*O*-methyl-cellulosyl)-4-[β -D-glucopyranosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosyloxymethyl]-1*H*-1,2,3-
14 -triazole (**1**), 1-(tri-*O*-methyl-cellulosyl)-4-[(6-amino-6-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-
15 6-amino-6-deoxy- β -D-glucopyranosyloxymethyl]-1*H*-1,2,3-triazole (**2**), and

16 4-(tri-*O*-methyl-cellulosyloxymethyl)-1-[β -D-glucopyranuronosyl-(1 $\rightarrow$ 4)- β -D-glucopyranuronosyl]-
17 1*H*-1,2,3-triazole (**3**), respectively. Aqueous solutions of all of the 1,2,3-triazole-linked diblock
18 methylcellulose analogues possessed higher surface activities than that of industrially produced
19 methylcellulose and exhibited lower critical solution temperatures, that allowed the formation of
20 thermoresponsive supramolecular hydrogels at close to human body temperature. Supramolecular
21 structures of thermo-reversible hydrogels based on compounds **1**, **2**, and **3** were investigated by
22 means of scanning electron microscopy (SEM) and transmission electron microscopy (TEM).
23 Detailed structure-property-function relationships of compounds **1**, **2**, and **3** were discussed. Not
24 only nonionic hydrophilic segment but also ionic hydrophilic segments of diblock methylcellulose
25 analogues were valid for the formation of thermo-reversible supramolecular hydrogels based on
26 end-functionalized methylcellulose.

27

28 Keywords: methylcellulose; polysaccharides; diblock copolymer; end-functionalization; surface
29 activity; thermo-reversible supramolecular hydrogels.

30

31 1. Introduction

32 Methylcellulose (MC) is one of the more common cellulose ethers and has been of particular
33 interest for the investigation of its structure–property relationships, such as the surface activity of its
34 aqueous solution and its thermo-reversible gelation properties at elevated temperature. These
35 properties of industrial and academic interest are attributed to the chemical structure of the
36 methylcellulose skeleton. Therefore, many researchers have previously investigated MC.
37 Commercial MC prepared under heterogeneous conditions is an alternating block copolymer
38 composed of densely substituted hydrophobic and less densely substituted hydrophilic block
39 sequences (Savage, 1957). The highly methylated region—a sequence of
40 2,3,6-tri-*O*-methyl-glucosyl residues—of the cellulose skeleton is said to cause micelles, that is,
41 liquid–liquid phase separations in aqueous solution (Rees, 1972). These micelles are known as
42 “crosslinking loci” (Kato, Yokoyama, & Takahashi, 1978). In addition, it is well known that
43 reversible crosslinks must exist in any reversible gel (Kato et al., 1978).

44 We have reported diblock methylcellulose derivatives with regioselective functionalization patterns
45 (Nakagawa, Fenn, Koschella, Heinze, & Kamitakahara, 2011b). We found direct evidence that a
46 sequence of 2,3,6-tri-*O*-methyl-glucopyranosyl units causes thermo-reversible gelation of aqueous
47 MC solution and that an idealized diblock structure consisting of 2,3,6-tri-*O*-methyl-glucopyranosyl
48 and unmodified cello-oligosaccharides caused gelation (Nakagawa, Fenn, Koschella, Heinze, &
49 Kamitakahara, 2011a). However, we had to simplify a synthetic route for new methylcellulose
50 derivatives possessing lower critical solution temperature (LCST) behaviors in aqueous solution.
51 Glycosylation of a cellobiose derivative with a polymeric methyl tri-*O*-methylcelluloside having
52 one hydroxy group at the C-4 position of the glucosyl residue at the non-reducing end consumed a
53 large amount of cellobiosyl trichloroacetimidate derivative to afford only the diblock
54 methylcellulose. To improve the efficiency of the coupling reaction between the hydrophobic and
55 hydrophilic segments, we synthesized a diblock methylcellulose analogue via Huisgen 1,3- dipolar
56 cycloaddition (Nakagawa, Kamitakahara, & Takano, 2012). A 2-propynyl group was introduced to
57 the C-4 hydroxy group at the non-reducing end of the methyl tri-*O*-methylcelluloside. Huisgen
58 1,3-dipolar cycloaddition was more efficient than glycosylation for connecting the hydrophobic and
59 hydrophilic segments.

60 Recently, we have reported a versatile pathway to heterobifunctional/telechelic cellulose ethers,
61 such as tri-*O*-methylcellulosyl azide and propargyl tri-*O*-methylcelluloside, with one free C-4
62 hydroxy group attached to the glucosyl residue at the non-reducing end for the use in the Huisgen
63 1,3-dipolar cycloaddition (Hiroshi Kamitakahara et al., 2016). This new method enables us to
64 prepare a hydrophobic segment for the Huisgen 1,3-dipolar cycloaddition from

65 tri-*O*-methylcellulose in a one-step reaction.

66 If the chemical structure of trehalose-type diblock polysaccharide analogues exhibited the same
67 physical properties as those of the original diblock polysaccharides, the Huisgen 1,3-dipolar
68 cycloaddition of azido and alkyne derivatives could produce a variety of diblock polysaccharide
69 analogues more easily than a glycosylation method, to afford, for instance,
70 cellobiosyl-(1→4)-methylcelluloses. As an example, cellobiosyl-(1↔1)-methylcelluloside, a
71 trehalose-type diblock copolymer, possesses an analogous structure to
72 cellobiosyl-(1→4)-methylcellulose. Moreover,
73 1-methylcellulosyl-4-cellobiosyloxymethyl-1*H*-1,2,3-triazole and
74 4-methylcellulosyloxymethyl-1-cellobiosyl-1*H*-1,2,3-triazole have analogous structures to
75 cellobiosyl-(1↔1)-methylcelluloside. Therefore,
76 1-methylcellulosyl-4-cellobiosyloxymethyl-1*H*-1,2,3-triazole and
77 4-methylcellulosyloxymethyl-1-cellobiosyl-1*H*-1,2,3-triazole exhibit analogous structures to
78 cellobiosyl-(1→4)-methylcellulose, a diblock methylcellulose. These triazole-linked diblock
79 methylcellulose analogues would allow us to gain deep insights into not only fundamental but also
80 potential properties of methylcelluloses.

81 A hydrophilic segment would be chosen to tune the properties of the methylcellulose, thereby
82 producing new functional methylcellulose derivatives. Methylcellulose is nonionic. Cationic and
83 anionic cellulose ethers are also of industrial importance. Commercial cationic hydroxyethyl
84 cellulose (QC-10), *O*-[2-hydroxy-3-(trimethylammonio)]propyl hydroxyethyl cellulose chloride, is
85 well known as a conditioning polymer for hair-care products (Hossel, Dieing, Norenberg, Pfau, &
86 Sander, 2000). Chitosan, poly(2-amino-2-deoxy-glucopyranose), an analogous structure to cellulose,
87 is the second most abundant natural polymer (Rinaudo, 2006). 6-Amino-6-deoxycellulose
88 (Teshirogi, Yamamoto, Sakamoto, & Tonami, 1979) is an analogous polymer to chitosan.
89 Carboxymethyl cellulose (Heinze, Erler, Nehls, & Klemm, 1994) is an anionic cellulose ether, and
90 its application fields are widely spread. Recently, cellouronic acid (Isogai & Kato, 1998) and
91 cellulose nanofibers prepared by TEMPO (2,2,6,6-tetramethylpiperidinyloxy) oxidation (Saito,
92 Kimura, Nishiyama, & Isogai, 2007; Saito, Nishiyama, Putaux, Vignon, & Isogai, 2006) have
93 gained increasing attention as anionic cellulosic materials.

94 To gain deep insights into the influence of the hydrophilic segments of the diblock methylcellulose
95 analogues on the general properties of the original methylcellulose, we chose three hydrophilic
96 segments: β-D-glucopyranosyl-(1→4)-β-D-glucopyranose,
97 (6-amino-6-deoxy-β-D-glucopyranosyl)-(1→4)-6-amino-6-deoxy-β-D-glucopyranose, and
98 (β-D-glucopyranuronosyl)-(1→4)-β-D-glucopyranuronic acid.

99 Methylcellulose-based diblock copolymers bearing cationic or anionic hydrophilic segments would
100 enhance the physical performance of commercially available methylcellulose. Thus, we describe, in
101 this paper, the synthesis and structure–property relationships of
102 1-(tri-*O*-methyl-cellulosyl)-4-(β -D-glucopyranosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosyloxymethyl)-1*H*-1,2,3
103 -triazole (**1**),
104 1-(tri-*O*-methyl-cellulosyl)-4-((6-amino-6-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-6-amino-6-deoxy- β -
105 D-glucopyranosyloxymethyl)-1*H*-1,2,3-triazole (**2**), and
106 4-(tri-*O*-methyl-cellulosyloxymethyl)-1-((β -D-glucopyranuronosyl)-(1 $\rightarrow$ 4)- β -D-glucopyranuronosyl
107)-1*H*-1,2,3-triazole (**3**). In particular, their surface activities, thermal properties, and
108 thermoresponsive gelation properties will be discussed.

109 2. Experimental

110 2.1. General measurements

111 ^1H - and ^{13}C -NMR spectra were recorded with Varian 500 NMR (500 MHz) or Varian INOVA300
112 (300 MHz) spectrometer in chloroform-*d* with tetramethylsilane as an internal standard or in
113 deuterium oxide with 3-(trimethylsilyl)-1-propanesulfonic acid sodium salt as an external standard.
114 Chemical shifts (δ) and coupling constants (*J*) are given in ppm and Hz, respectively.
115 Matrix-assisted laser desorption/ionization time-of-flight mass spectrometry (MALDI-TOF MS)
116 analysis was performed with a Bruker MALDI-TOF MS Autoflex III in the positive ion and linear
117 modes. For ionization, a smartbeam laser was used. All spectra were measured in the linear mode
118 by using external calibration. MALDI-TOF MS used 2,5-dihydroxybenzoic acid as a matrix. A
119 Shimadzu liquid chromatography injector (LC-10ATvp), Shimadzu column oven (CTO-10Avp),
120 Shimadzu ultraviolet visible detector (SPD-10Avp), Shimadzu refractive index detector (RID-10A),
121 Shimadzu communication bus module (CBM-10A), Shimadzu LC workstation (CLASS-LC10),
122 and Shodex columns (KF802, KF802.5, and KF805) were used. Number- and weight-averaged
123 molecular weights (M_n , M_w) and polydispersity indices (M_w/M_n) were estimated by using
124 polystyrene standards (Shodex). A flow rate of 1 mL/min at 40 °C was chosen. Chloroform was
125 used as the eluent.

126 2.2. Differential scanning calorimetry (DSC) measurements

127 DSC thermograms were recorded on a DSC823[°] instrument (Mettler Toledo, Zurich, Switzerland)
128 with an HSS7 sensor under a nitrogen atmosphere during a heating/cooling cycle (0 $\rightarrow$ 90 $\rightarrow$ 0 °C)
129 with a heating and cooling rate of 3.5 °C/min. Each temperature cycle was sequentially repeated
130 three times in order to ensure and check the reproducible response of the instrument. The sample
131 concentration for DSC measurements was 2.0 wt. %.

132 2.3. Dynamic light scattering (DLS) measurements

133 DLS measurements were performed with an ELS-Z zeta-potential and particle-size analyzer
134 (Otsuka Electronics Co., Ltd, Osaka, Japan) and observed in the temperature range from 10 to
135 90 °C. The sample solutions were kept for 5 min at the required temperature before each
136 measurement. The sample concentration for DLS measurements was 0.2 or 2.0 wt. %. The
137 hydrodynamic diameters were obtained by Cumulant method. Intensity and number size
138 distributions were obtained by Marquardt method.

140 2.4. Surface tension measurements

141 Surface tension was measured by the Wilhelmy method by using a CBVP-A3 surface tensiometer
142 (Kyowa Interface Science, Co. Ltd., Tokyo, Japan) at 25 °C. A Teflon cell containing 700 µL of
143 solution was used for the measurement. The surface tension gradually decreased during the
144 measurements. The values were stable after 30 min and were recorded.

145 2.5. Scanning electron microscopy (SEM) and transmission electron microscopy (TEM)

146 The three kinds of hydrogels from aqueous solutions of compounds **1**, **2** and **3** were frozen with
147 liquid nitrogen, lyophilized, and cut with a razor blade. The cut surfaces of the hydrogels were
148 sputter-coated with gold with an ion-coater (JFC-1100E, JEOL, Tokyo, Japan) and observed under
149 a scanning electron microscope (JSM-6060, JEOL) at an accelerating voltage of 5 kV.

150 A drop of aqueous dispersion of compound **1** was mounted on a copper grid with an elastic carbon
151 supporting film (Oken Shoji, Tokyo, Japan) and observed under a transmission electron microscope
152 (JEM1400, JEOL) at an accelerating voltage of 100 kV after negative staining with uranyl acetate.

153 2.6. Syntheses

154 Cellobiose octaacetate (**12**):

155 Cellobiose was acetylated to give cellobiose octaacetate (**12**) according to the method in our
156 previous paper (H. Kamitakahara, Nakatsubo, & Klemm, 2006). Cellobiose (12.04 g, 35.17 mmol)
157 and sodium acetate were added in acetic anhydride (60 mL). The reaction mixture was stirred at
158 55 °C over night and 100 °C for 3 h. The reaction mixture was poured into water with ice (600 mL).
159 Crude crystals were filtered and washed with distilled water and recrystallized with EtOH to give
160 colorless crystals. (20.8 g, 30.65 mmol, 87% yield). CAS Registry No. 5346-90-7

161
162 2-Propynyl (2,3,6-tri-*O*-acetyl-β-D-glucopyranosyl)-(1→4)-2,3,6-tri-*O*-acetyl-β-D-glucopyranoside
163 (**9**) (Moni et al., 2013):

164 2-Propyne-1-ol (1.05 mL, 18.2 mmol, 1.2 equiv.) was added to a solution of compound **12** (10.3 g,
165 15.2 mmol) in anhydrous dichloromethane (40 mL). The reaction mixture was cooled to 0 °C.
166 Boron trifluoride diethyl ether complex (2.86 mL, 22.8 mmol, 1.5 equiv.) was added to the reaction
167 mixture at 0 °C. The mixture was stirred for about one day. Solid NaHCO₃ was then added to the
168 reaction mixture. The reaction mixture was extracted with dichloromethane, washed with water, sat.
169 aq. NaHCO₃ solution, and brine, dried with Na₂SO₄, and concentrated to dryness. The obtained
170 crude crystals were recrystallized with dichloromethane/*n*-hexane to produce 2-propynyl
171 (2,3,6-tri-*O*-acetyl-β-D-glucopyranosyl)-(1→4)-2,3,6-tri-*O*-acetyl-β-D-glucopyranoside (**9**, 10.1223
172 g, 99% yield).

173 ¹H NMR (Moni et al., 2013) (400 MHz): δ 5.21 (dd, 1H, *J*_{2,3} = *J*_{3,4} = 9.2 Hz, H-3), 5.14 (dd, 1H, *J*_{2',3'} = *J*_{3',4'} =
174 9.1 Hz, H-3'), 5.06 (dd, 1H, H-4'), 4.93 (2 dd, 2H, H-2, H-2') 4.73 (d, 1H, *J*_{1,2} = 8.0 Hz, H-1), 4.54 (dd, 1H, *J*_{5,6a} = 2.0
175 Hz, *J*_{6a,6b} = 12.0 Hz, H6a), 4.51 (d, 1H, *J*_{1',2'} = 8.0 Hz, H-1'), 4.37 (dd, 1H, *J*_{5',6'a} = 4.5 Hz, *J*_{6'a,6'b} = 12.5 Hz, H6'a),
176 4.33 (d, 2H, *J* = 2.5 Hz, OCH₂CCH), 4.10 (dd, 1H, *J*_{5,6b} = 4.7 Hz, H-6b), 4.14 (dd, 1H, *J*_{5',6'b} = 2.0 Hz, H-6'b), 3.79
177 (dd, 1H, H-4), 3.68–3.60 (m, 2H, H-5, H-5'), 2.45 (t, 1H, OCH₂CCH), 2.19–2.01 (7 s, 21H, 7 Ac).
178 ¹³C-NMR (125 MHz, CDCl₃): δ 20.5, 20.6, 20.7, 20.8, 55.9 (–CH₂CCH), 61.5 (C6'), 61.7 (C6), 67.8
179 (C4'), 71.2 (C2), 71.6 (C2'), 71.9 (C5'), 72.4 (C3), 72.8 (C5 or C3'), 72.9 (C5 or C3'), 75.4
180 (CH₂CCH), 76.3 (C4), 78.0 (CH₂CCH), 97.9 (C1), 100.7 (C1'), 169.0, 169.3, 169.7, 169.7, 170.2,
181 170.3, 170.5

182

183 2-Propynyl β-D-cellobioside (**13**) (Moni et al., 2013):

184 Sodium methoxide (28%) in methanol (0.48 mL, 8.37 mmol, 1.4 equiv.) was added to a solution of
185 compound **9** (4.0010 g, 5.93 mmol) in tetrahydrofuran (THF; 100 mL) and methanol (50 mL). The
186 reaction mixture was stirred for 3.3 h at room temperature. Amberlyst H⁺ was added to neutralize
187 the mixture and was then filtered off. The combined filtrate and washings were then concentrated to
188 dryness to give 2-propynyl β-D-cellobioside (**13**, 2.17 g, 96% yield).

189 ¹H NMR (400 MHz, D₂O) (Moni et al., 2013): δ 4.50 (d, 1H, *J*_{1,2} = 8.0 Hz, H-1), 4.34 (d, 1H, *J*_{1',2'} = 7.5 Hz,
190 H-1'), 4.31 (dd, 2H, *J* = 16.0, 2.5 Hz, OCH₂CCH), 3.82 (dd, 1H, *J*_{5,6a} = 2.0 Hz, *J*_{6a,6b} = 12.5 Hz, H-6a), 3.75 (dd, 1H,
191 *J*_{5',6'a} = 2.0 Hz, *J*_{6'a,6'b} = 12.2 Hz, H6'a), 3.65 (dd, 1H, *J*_{5,6b} = 4.5 Hz, H-6b), 3.56 (dd, 1H, *J*_{5',6'b} = 5.5 Hz, H-6b'),
192 3.51–3.42 (m, 3H, H-3, H-4, H-5), 3.36–3.12 (m, 5H, H-2, H-2', H-3', H-4', H-5'), 2.75 (t, 1H, OCH₂CCH).

193 ¹³C-NMR (125 MHz, D₂O): δ 51.5, 59.3, 62.6, 63.2, 72.1, 75.4, 75.8, 76.9, 77.5, 78.2, 78.7, 79.0,
194 81.2, 81.4, 103.0, 105.2

195

196 2-Propynyl

197 (6-*O*-*p*-toluenesulfonyl-β-D-glucopyranosyl)-(1→4)-6-*O*-*p*-toluenesulfonyl-β-D-glucopyranoside
198 (**14**):

199 Tosyl chloride (3.48 g, 18.3 mmol) was added at 0 °C to a solution of 2-propynyl β-D-cellobioside

200 (13, 2.17 g, 5.69 mmol) in pyridine (8 mL). The reaction mixture was stirred at 8 °C for 22.5 h.
201 Brine was then added to the reaction mixture. The organic phase was extracted with ethyl acetate
202 three times, and pyridine was azeotropically removed with ethanol to produce crude compound 14.
203 The crude product was purified by silica gel column chromatography (methanol/chloroform=1/5,
204 v/v) to give 2-propynyl
205 (6-*O*-*p*-toluenesulfonyl-β-D-glucopyranosyl)-(1→4)-6-*O*-*p*-toluenesulfonyl-β-D-glucopyranoside
206 (14, 1.97 g, 50.5% yield).
207 ¹H-NMR (500 MHz, CDCl₃): δ 2.40 (s, 3H, PhCH₃), 2.41 (s, 3H, PhCH₃), 2.49 (t, 1H, —CH₂CCH),
208 3.36 (t, 1H, *J*=8.5 Hz), 3.45 (t, 1H, *J*=8.5 Hz), 3.49-3.70 (m), 4.17 (dd, 1H, *J*=2 Hz, *J*=16 Hz,
209 CH₂CCH), 4.24-4.43 (H6', H6', H6, H6, CH₂CCH), 4.44 (d, 1H, *J*=8.0 Hz, H1), 4.50 (d, 1H, *J*=7.0
210 Hz, H1'), 7.3-7.8 (aromatic H)
211 ¹³C-NMR (125 MHz, CDCl₃): δ 21.7, 55.9 (—CH₂CCH), 68.9 (C6'), 69.1 (C6), 69.4 (C3'), 72.1,
212 72.4, 73.0 (C2), 73.5, 73.7, 75.7, 75.7 (CH₂CCH), 77.0, 78.8 (CH₂CCH), 100.0, 101.3 (C1'), 128.0,
213 129.8, 130.0, 132.2, 132.6, 144.9, 145.2 (aromatic C)
214
215 2-Propynyl
216 (2,3,4-tri-*O*-acetyl-6-*O*-*p*-toluenesulfonyl-β-D-glucopyranosyl)-(1→4)-2,3-di-*O*-acetyl-6-*O*-*p*-tolue
217 nesulfonyl-β-D-glucopyranoside (15):
218 Acetic anhydride (1 mL) was added to a solution of 2-propynyl
219 (6-*O*-*p*-toluenesulfonyl-β-D-glucopyranosyl)-(1→4)-6-*O*-*p*-toluenesulfonyl-β-D-glucopyranoside
220 (14, 0.763 g) in pyridine (5 mL). The reaction mixture was stirred at room temperature overnight.
221 The reaction mixture was extracted with ethyl acetate, washed with 1 N HCl, sat. aq. NaHCO₃, and
222 brine, dried over Na₂SO₄, and concentrated to dryness to give 2-propynyl
223 (2,3,4-tri-*O*-acetyl-6-*O*-*p*-toluenesulfonyl-β-D-glucopyranosyl)-(1→4)-2,3-di-*O*-acetyl-6-*O*-*p*-tolue
224 nesulfonyl-β-D-glucopyranoside (15, 0.9409 g, 94.6% yield).
225 ¹H-NMR (300 MHz, CDCl₃): δ 1.91, 1.98, 1.99, 2.00, 2.03 (COCH₃), 2.45 (t, 1H, —CH₂CCH),
226 2.47 (s, 3H, PhCH₃), 2.48 (s, 3H, PhCH₃), 3.55 (m, 1H, *J*=2.0, *J*=3.5 Hz, *J*=9.5 Hz, H5), 3.65 (m,
227 1H, *J*=2.5 Hz, *J*=4.5 Hz, *J*=10.0 Hz, H5'), 3.71 (t, 1H, *J*=10.0 Hz, H4), 4.10 (dd, 1H, *J*=5.0 Hz,
228 *J*=11.5 Hz, H6'), 4.14-4.28 (H6', H6, CH₂CCH), 4.33 (dd, 1H, *J*=2.0 Hz, *J*=11.0 Hz, H6), 4.38 (d,
229 1H, *J*=7.5 Hz, H1'), 4.65 (d, 1H, *J*=8.5 Hz, H1), 4.80 (t, 1H, *J*=9.5 Hz, H2), 4.81 (t, 1H, *J*=8.5 Hz,
230 H2'), 4.93 (t, 1H, *J*=10.0 Hz, H4'), 5.03 (t, 1H, *J*=9.0 Hz, H3'), 5.11 (t, 1H, *J*=9.0 Hz, H3),
231 7.39-7.84 (aromatic H)
232 ¹³C-NMR (75 MHz, CDCl₃): δ 20.5, 20.5, 20.6, 20.7, 21.6, 21.7, 55.7 (—CH₂CCH), 66.3 (C6'), 66.8
233 (C6), 68.0 (C4'), 70.8 (C2), 71.4 (C2'), 71.5 (C5'), 71.8 (C3), 72.4 (C5), 72.8 (C3'), 74.9 (C4), 75.6
234 (CH₂CCH), 77.9 (CH₂CCH), 97.7 (C1), 100.0 (C1'), 128.0, 128.1, 130.1, 130.1, 132.3, 132.6,
235 145.4, 145.5 (aromatic C), 168.8, 169.3, 169.5, 169.9, 170.1 (COCH₃)

236

237 2-Propynyl

238 (2,3,4-tri-*O*-acetyl-6-azido-6-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl-6-azido-6-deoxy- β -
239 -D-glucopyranoside (**16**):

240 Sodium azide (0.3731 g) was added to a solution of 2-propynyl

241 (2,3,4-tri-*O*-acetyl-6-*O*-*p*-toluenesulfonyl- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl-6-*O*-*p*-tolue
242 nesulfonyl- β -D-glucopyranoside (**15**, 1.2888 g) in *N,N*-dimethylformamide (DMF; 5 mL). The

243 reaction mixture was stirred overnight at 50 °C. The mixture was then poured into distilled water

244 with ice. The organic phase was extracted with dichloromethane four times, dried over sodium

245 sulfate, and concentrated to dryness. The crude product was purified by silica gel column

246 chromatography (eluent: ethyl acetate/*n*-hexane=2/1, v/v) to afford 2-propynyl

247 (2,3,4-tri-*O*-acetyl-6-*O*-azido-6-*O*-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl-6-*O*-azido-6-
248 *O*-deoxy- β -D-glucopyranoside (**16**, 0.8904 g, 97% yield).

249 ¹H-NMR (500 MHz, CDCl₃): δ 1.99 (s, 3H, (CO)CH₃), 2.04 (s, 3H, (CO)CH₃), 2.05 (s, 3H,

250 (CO)CH₃), 2.05 (s, 3H, (CO)CH₃), 2.08 (s, 3H, (CO)CH₃), 2.47 (s, 1H, *J*=2.5 Hz, CH₂CCH), 3.37

251 (dd, 1H, *J*=5.0 Hz, *J*=13.0 Hz, H6'), 3.40 (dd, 1H, *J*=4.5 Hz, *J*=13.0 Hz, H6), 3.43 (dd, 1H, *J*=3.0

252 Hz, *J*=13.5 Hz, H6'), 3.58 (dd, 1H, *J*=2.0 Hz, *J*=13.0 Hz, H6), 3.60-3.64 (2H, m, H5, H5'), 3.85 (t,

253 1H, *J*=9.5 Hz, H4), 4.36 (d, 2H, *J*=2.5 Hz, CH₂CCH), 4.57 (d, 1H, *J*_{1,2}=8.0 Hz, H1'), 4.79 (d, 1H,

254 *J*_{1,2}=8.0 Hz, H1), 4.89 (dd, 1H, *J*=8.0 Hz, *J*=9.5 Hz, H2'), 4.94 (dd, 1H, *J*=8.0 Hz, *J*=9.5 Hz, H2),

255 4.99 (t, 1H, *J*=9.5 Hz, H4'), 5.16 (t, 1H, *J*=9.5 Hz, H3'), 5.22 (t, 1H, *J*=9.5 Hz, H3)

256 ¹³C-NMR (125 MHz, CDCl₃): δ 20.5, 20.6, 20.6, 20.7, 20.8 ((CO)CH₃), 50.2 (C6), 50.9 (C6'), 55.8

257 (CH₂CCH), 69.1 (C4'), 71.3 (C2), 71.7 (C2'), 72.4 (C3), 72.6 (C3'), 72.7 (C5), 74.5 (C5'), 75.6

258 (CH₂CCH), 75.9 (C4), 78.0 (CH₂CCH), 97.8 (C1), 100.1 (C1'), 168.9, 169.4, 169.6, 169.8, 170.2

259 ((CO)CH₃)

260 Mw=640.5, MALDI-TOF MS: *m/z* [M+Na]⁺=663.6, *m/z* [M+K]⁺=679.6

261

262 2-Propynyl (6-azido-6-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-6-azido-6-deoxy- β -D-glucopyranoside
263 (**17**):

264 Sodium methoxide (28%) in methanol (28 μ L) was added to 2-propynyl

265 (2,3,4-tri-*O*-acetyl-6-azido-6-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl-6-azido-6-deoxy- β -
266 -D-glucopyranoside (**16**, 0.3028 g) in methanol (1.5 mL) and THF (1.5 mL). The reaction mixture

267 was stirred at room temperature for overnight. The mixture was neutralized with Amberlyst H⁺. The

268 Amberlyst H⁺ was removed by filtration and washed with methanol. The filtrate and washings were

269 concentrated to dryness to produce 2-propynyl

270 (6-*O*-azido-6-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-6-*O*-azido-6-deoxy- β -D-glucopyranoside (**17**,

271 0.1805 g, 87% yield).

272 ¹H-NMR (500 MHz, D₂O): δ 2.92 (t, 1H, *J*=2.5 Hz, CH₂CCH), 3.30 (dd, 1H, *J*=8.0 Hz, *J*=9.0 Hz,
273 H2'), 3.35 (dd, 1H, *J*=8.0 Hz, *J*=9.5 Hz, H2), 3.43 (t, 1H, *J*=9.0 Hz, H4'), 3.48 (t, 1H, *J*=9.0 Hz, H3'),
274 3.52 (dd, 1H, *J*=5.5 Hz, *J*=13.0 Hz, H6'), 3.58 (m, 1H, *J*=9.25 Hz, *J*=2.3 Hz, 5.5 Hz, H5'), 3.61-3.66
275 (3H, m, H3, H4, H6), 3.75 (dd, 1H, *J*=2.5 Hz, *J*=14.0 Hz, H6), 3.75-3.79 (1H, m, H5), 3.78 (dd, 1H,
276 *J*=2.5 Hz, *J*=13.5 Hz, H6'), 4.46 (2H, (CH₂CCH)), 4.49 (d, 1H, *J*=8 Hz, H1'), 4.68 (d, 1H, *J*=7.5 Hz,
277 H1)

278 ¹³C-NMR (D₂O): δ 50.2 (C6 (b)), 50.8 (C6 (a)), 56.7 (CH₂CCH), 70.0 (C4'), 72.6 (C2), 73.0 (C2'),
279 73.6 (C5), 73.9 (C3), 74.2 (C5'), 75.2 (C3'), 76.4 (CH₂CCH), 78.5 (CH₂CCH), 79.1 (C4), 100.4
280 (C1), 102.5 (C1')

281 Mw=430.4 MALDI-TOF MS: *m/z* [M+Na]⁺=453.1, *m/z* [M+K]⁺=469.1

282

283 2-Propynyl (6-amino-6-deoxy-β-D-glucopyranosyl)-(1→4)-6-amino-6-deoxy-β-D-glucopyranoside
284 (**18**):

285 Triphenylphosphine (132.1 mg) was added to a solution of 2-propynyl
286 (6-azido-6-deoxy-β-D-glucopyranosyl)-(1→4)-6-azido-6-deoxy-β-D-glucopyranoside (**17**, 54.2 mg)
287 in methanol (3 mL), THF (3 mL), and distilled water (0.7 mL). The reaction mixture was stirred at
288 room temperature for 14 days. The reaction product was extracted with distilled water and washed
289 with dichloromethane three times. The water layer was concentrated to dryness to afford 2-propynyl
290 (6-amino-6-deoxy-β-D-glucopyranosyl)-(1→4)-6-amino-6-deoxy-β-D-glucopyranoside (**18**, 46.8
291 mg, 98% yield).

292 ¹H-NMR (D₂O): δ 2.79 (dd, 1H, *J*=7.5 Hz, *J*=13.5 Hz, H6), 2.80 (dd, 1H, *J*=7.5 Hz, *J*=14.0 Hz, H6'),
293 3.07 (dd, 1H, *J*=3.0 Hz, *J*=14.0 Hz, H6'), 3.19 (dd, 1H, *J*=2.0v, *J*=13.0 Hz, H6), 3.29 (dd, 1H, *J*=7.5
294 Hz, *J*=9.0 Hz, H2'), 3.31 (t, 1H, *J*=8.0 Hz, H4') 3.33 (t, 1H, *J*=8.0 Hz, H2), 3.39 (m, 1H, *J*=9.5 Hz,
295 *J*=2.5 Hz, *J*=7.0 Hz, H5'), 3.47 (t, 1H, *J*=9.5 Hz, H3'), 3.51-3.561 (m, 2H, H4, H5), 3.60 (t, 1H,
296 *J*=8.5 Hz, H3), 4.46 (d, 2H, *J*=1.5 Hz, CH₂CCH), 4.47 (d, 1H, *J*=8.0 Hz, H1'), 4.64 (d, 1H, *J*=8.0
297 Hz, H1)

298 ¹³C-NMR (D₂O): δ 41.1 (C6), 41.2 (C6'), 56.8 (CH₂CCH), 70.9 (C4'), 72.8 (C2), 73.3 (C2'), 74.2
299 (C3), 75.2 (C5), 75.4 (C3'), 75.6 (C5'), 75.9 (CH₂CCH), 78.4 (CH₂CCH), 80.2 (C4), 100.8 (C1),
300 102.7 (C1')

301 Mw=378.4 MALDI-TOF MS: *m/z* [M+H]⁺=379.3, *m/z* [M+Na]⁺=401.3, *m/z* [M+K]⁺=417.2

302 Note that the carbon and proton resonances of the alkyne group did not appear with a good
303 signal-to-noise ratio, although the molecular ion peak was properly detected by MALDI-TOF MS
304 analysis. Moreover, the NMR spectra of compounds **19** and **10** indicate that the propargyl group is
305 not affected by the Staudinger reaction of compound **17** to produce compound **18**.

306

307 2-Propynyl

2,3,4-tri-*O*-acetyl-6-deoxy-6-acetylamino- β -D-glucopyranosyl-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl-6-deoxy-6-acetyl- β -D-glucopyranoside (**19**):

Sodium acetate (34.0 mg) was added to a dispersion of 2-propynyl (6-*O*-amino-6-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-6-*O*-amino-6-*O*-deoxy- β -D-glucopyranoside (**18**, 157.1 mg) in acetic anhydride (3 mL). The reaction mixture was stirred at 80 °C for 3 h. The mixture was extracted with ethyl acetate, washed with distilled water and brine, dried over anhydrous sodium sulfate, and concentrated to dryness. The crude product was again acetylated with acetic anhydride (0.5 mL) in pyridine (2 mL) at 80 °C for 1 h. The reagents were azeotropically removed with toluene to afford 2-propynyl

2,3,4-tri-*O*-acetyl-6-deoxy-6-acetylamino- β -D-glucopyranosyl-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl-6-deoxy-6-acetyl- β -D-glucopyranoside (**19**, 233.4 mg, 96% yield).

¹H-NMR (CDCl₃): δ 1.98, 2.03, 2.04, 2.05, 2.07, 20.8 (21H, O(CO)CH₃, NH(CO)CH₃), 2.50 (t, 1H, $J=2.0$, CH₂CCH), 3.40 (dd, 1H, $J=6.0$ Hz, 14.0 Hz, H6), 3.43 (dd, 1H, $J=6.5$ Hz, 14.5 Hz, H6'), 3.49 (ddd, 1H, $J=3.0$ Hz, $J=6.0$ Hz, $J=14.5$ Hz, H6'), 3.58-3.62 (m, 2H, H5, H5'), 3.78 (t, 1H, $J=9.5$, H4), 3.81 (ddd, 1H, $J=3.5$ Hz, $J=6.0$ Hz, $J=14.5$ Hz, H6), 4.33 (dd, 1H, $J=2.5$ Hz, $J=16$ Hz, CH₂CCH), 4.38 (dd, 1H, $J=2.5$ Hz, $J=16$ Hz, CH₂CCH), 4.71 (d, 1H, $J=8.0$ Hz, H1), 4.78 (d, 1H, $J=7.5$ Hz, H1'), 4.91 (t, 1H, $J=9.5$ Hz, H4'), 4.94 (dd, 1H, $J=7.5$ Hz, $J=9.0$ Hz, H2'), 4.98 (dd, 1H, $J=8.0$ Hz, $J=9.0$ Hz, H2), 5.13 (t, 1H, $J=9.5$ Hz, H3), 5.18 (t, 1H, $J=9.5$ Hz, H3'), 5.97 (t, 1H, $J=6.0$ Hz, C6NH(CO)CH₃), 6.63 (t, 1H, $J=6.0$ Hz, C6'NH(CO)CH₃)

¹³C-NMR (CDCl₃): δ 20.6, 20.7, 20.7, 20.9 (CH₃ (OAc)), 23.0, 23.3 (CH₃ (NHAc)), 39.1 (C6'), 39.8 (C6), 56.4 (CH₂CCH), 68.7 (C4'), 71.4 (C2), 71.7 (C2'), 72.3 (C5'), 72.7 (C3), 72.8 (C3'), 73.5 (C5), 75.5 (CH₂CCH), 76.2 (C4), 78.3 (CH₂CCH), 98.5 (C1), 98.7 (C1'), 169.4, 169.7, 169.8, 170.1, 170.2, 170.3, 170.6 (C=O (OAc, NHAc))

Mw= 672.6 MALDI-TOF MS: m/z [M+Na]⁺=695.2, m/z [M+K]⁺=711.2

2-Propynyl

[2,3,4-tri-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy- β -D-glucopyranosyl]-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy- β -D-glucopyranoside (**10**):

4-Dimethylaminopyridine (DMAP; 2.7 mg) and di-*tert*-butyl dicarbonate (Boc₂O; 0.1 mL) were added to a solution of 2-propynyl

[2,3,4-tri-*O*-acetyl-6-*O*-(acetylamino)-6-deoxy- β -D-glucopyranosyl]-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl-6-*O*-(acetylamino)-6-deoxy- β -D-glucopyranoside (**19**, 75 mg) in THF (4 mL). The reaction mixture was stirred at reflux temperature for 5.5 h. The mixture was concentrated in vacuo to afford crude

2-propynyl

(2,3,4-tri-*O*-acetyl-6-[acetyl(*tert*-butoxycarbonyl)amino]-6-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl-6-[acetyl(*tert*-butoxycarbonyl)amino]-6-deoxy- β -D-glucopyranoside (**20**, 127.5 mg;

344 MW = 872.9, MALDI-TOF MS: m/z $[M+Na]^+ = 895.4$.
345 Sodium methoxide (28%) in methanol (13 μ L) was added to a solution of crude compound **20** (97.3
346 mg) in methanol (2 mL) and dichloromethane (1 mL). The reaction mixture was stirred at room
347 temperature for 6 h. The mixture was neutralized with Amberlyst H⁺. After filtration of the
348 Amberlyst H⁺ and washing with methanol, the combined filtrate and washings were concentrated to
349 dryness to produce crude product. The crude product was purified by preparative thin-layer
350 chromatography (PTLC; eluent: methanol/dichloromethane=1/9, v/v) to afford 2-propynyl
351 (6-(*tert*-butoxycarbonyl)amino-6-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-6-(*tert*-butoxycarbonyl)amino
352 -6-deoxy- β -D-glucopyranoside (**21**, 49.1 mg, MW = 578.6; MALDI-TOF MS: m/z $[M+Na]^+ =$
353 601.4).
354 Compound **21** (49.1 mg) was then dissolved in acetic anhydride (0.3 mL) and pyridine (2 mL). The
355 reaction mixture was stirred at 60 °C for 2 h and concentrated azeotropically with toluene to give
356 2-propynyl
357 (2,3,4-tri-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy- β -D-glucopyranosyl)-(1 $\rightarrow$ 4)-2,3-di-*O*-ac
358 etyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy- β -D-glucopyranoside (**10**, 67.9 mg, 77% yield from
359 compound **19**).
360 ¹H-NMR (CDCl₃): δ 1.44, 1.46 (18H, COOC(CH₃)₃), 1.98, 2.04, 2.04, 2.06, 2.08 (15H, m, COCH₃),
361 2.49 (t, 1H, $J=2.5$ Hz, CH₂CCH), 3.31-3.36 (m, 3H, H₆, H_{6'}, H_{6''}), 3.50-3.54 (m, 2H, H₅, H_{5'}),
362 3.63-3.65 (m, 1H, H_{6'}), 3.69 (t, 1H, $J=9.5$ Hz, H₄), 4.31-4.39 (2H, m, (CH₂CCH)), 4.71 (d, 1H,
363 $J=7.0$ Hz, H₁), 4.76 (broad d, 1H, $J=8.0$ Hz, H_{1'}), 4.90-4.96 (m, 4H, H₂, H_{2'}, H_{4'}, NH), 5.17 (t, 1H,
364 $J=9.5$ Hz, H_{3'}), 5.20 (t, 1H, $J=9.5$ Hz, H₃), 5.15-5.22 (1H, NH)
365 ¹³C-NMR (CDCl₃): δ 20.6, 20.7, 20.7, 20.8, 20.8 (COCH₃), 28.3, 28.4 (COOC(CH₃)₃), 40.6, 40.7
366 (C₆, C_{6'}), 56.4 (CH₂CCH), 68.7 (broad, C_{4'}), 71.4 (C₂), 71.6 (C_{2'}), 72.1 (broad, C₃), 72.9 (C_{3'}),
367 73.0 (C₅ or C_{5'}), 73.9 (broad, C₅ or C_{5'}), 75.4 (CH₂CCH), 75.9 (broad, C₄), 78.3 (CH₂CCH), 79.8,
368 79.8 (broad, COOC(CH₃)₃), 98.5 (C₁), 99.2 (broad, C_{1'}), 155.7 (COOC(CH₃)₃), 169.4, 169.6,
369 169.7, 170.2 (COCH₃)
370 Mw=788.8 MALDI-TOF MS: m/z $[M+Na]^+ = 811.5$, m/z $[M+K]^+ = 827.4$
371
372 2,3,4,6-Tetra-*O*-acetyl- β -D-glucopyranosyl-(1 $\rightarrow$ 4)-2,3,6-tri-*O*-acetyl- β -D-glucopyranosyl azide
373 (**22**):
374 Compound **22** was prepared according to the method in our previous report (H. Kamitakahara &
375 Nakatsubo, 2005).
376
377 β -D-Glucopyranosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosyl azide (**23**):
378 Compound **23** was prepared according to the method in previous reports (Schamann & Schafer,
379 2003; Ying & Gervay-Hague, 2003).

380

381 β -D-Glucopyranosiduronosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosiduronosyl azide (**24**):

382 Potassium bromide (18.8 mg) and TEMPO (16.7 mg) were added to a solution of

383 β -D-glucopyranosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosyl azide (**23**, 290 mg) in sat. aq. sodium

384 hydrogencarbonate (3 mL). Sodium hypochlorite (NaOCl, 3.9 mL) was then added to the reaction

385 mixture. The mixture was stirred at 0 °C for 1 h. TEMPO (8 mg) and NaOCl (3.9 mL) were further

386 added to the reaction mixture. After being stirred at 4 °C for one day, the reaction mixture was

387 extracted with distilled water and washed with dichloromethane four times. The aqueous layer was

388 adjusted to pH 2 with 2 N HCl, concentrated, and diluted with distilled water. This concentration

389 and dilution cycle was repeated several times until the color of the solution turned from yellow to

390 colorless. The aqueous layer was finally concentrated to dryness. The insoluble part was filtered off

391 and washed with methanol. The combined filtrate and washings were concentrated to dryness. This

392 procedure was repeated three times to give

393 β -D-glucopyranosiduronosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosiduronosyl azide (**24**, 278.7 mg) (Schamann

394 & Schafer, 2003; Ying & Gervay-Hague, 2003). The carboxylic acid moieties of crude compound

395 **24** were esterified without further purification.

396

397 Methyl [(methyl β -D-glucopyranosyluronate)-(1 $\rightarrow$ 4)- β -D-glucopyranosyl azide]uronate (**25**):

398 2,2-Dimethoxypropane (1.5 mL) and one drop of conc. HCl were added at room temperature to a

399 solution of β -D-glucopyranosiduronosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosiduronosyl azide (**24**, 278.7 mg)

400 in methanol (15 mL). The reaction mixture was stirred for one day and concentrated to dryness to

401 give methyl [(methyl β -D-glucopyranosyluronate)-(1 $\rightarrow$ 4)- β -D-glucopyranosyl azide]uronate (**25**,

402 273.3 mg) (Schamann & Schafer, 2003). Crude compound **25** was acetylated without further

403 purification.

404

405 Methyl [(methyl

406 2,3,4-tri-*O*-acetyl- β -D-glucopyranosyluronate)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl- β -D-glucopyranosyl

407 azide]uronate (**11**):

408 Methyl [(methyl β -D-glucopyranosyluronate)-(1 $\rightarrow$ 4)- β -D-glucopyranosyl azide]uronate (**25**, 92.5

409 mg) was dispersed in acetic anhydride (4 mL) with sodium acetate (70.8 mg). The reaction mixture

410 was stirred at 60 °C overnight. The organic layer was extracted with ethyl acetate, washed with

411 distilled water twice, aq. sodium hydrogen carbonate three times, and brine, and concentrated to

412 dryness. The crude product was purified by silica gel column chromatography (eluent: ethyl

413 acetate/*n*-hexane=1/1, v/v; methanol/dichloromethane=1/49, v/v) and by PTLC (eluent: ethyl

414 acetate/*n*-hexane=1/1, v/v) to give methyl [(methyl

415 2,3,4-tri-*O*-acetyl- β -D-glucopyranosyluronate)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl- β -D-glucopyranosyl

azide]uronate (**11**, 70 mg, total yield 11% from compound **23**).
¹H-NMR (CDCl₃): δ 1.99, 2.01, 2.01, 2.06, 2.07 (15H, COCH₃), 3.73 (s, 3H, C6'OOCH₃), 3.87 (s, 3H, C6OOCH₃), 4.0 (d, 2H, *J*=10 Hz, H5 and H5'), 4.14 (t, 1H, *J*=9.5 Hz, H4), 4.63 (d, 1H, *J*=8.0 Hz, H1'), 4.67 (d, 1H, *J*=8.5 Hz, H1), 4.88 (t, 2H, *J*=9.5 Hz, H2 and H2'), 5.13 (t, 1H, *J*=10.0 Hz, H4'), 5.19 (t, 1H, *J*=9.5 Hz, H3'), 5.20 (t, 1H, *J*=9.5 Hz, H3)
¹³C-NMR (CDCl₃): δ 20.4, 20.5, 20.5 (COCH₃), 52.8 (C6OOCH₃), 53.2 (C6'OOCH₃), 69.4 (C4'), 70.5 (C2'), 71.0 (C2), 71.5 (C3), 72.0 (C3'), 72.6 (C5'), 75.7 (C5), 76.4 (C4), 88.4 (C1), 100.4 (C1'), 166.7 (C6'OOCH₃), 167.1 (C6OOCH₃), 169.0, 169.3, 169.3, 170.0, 170.1 (COCH₃)
Mw=633.5 MALDI-TOF MS: *m/z* [M+Na]⁺=656.4, *m/z* [M+K]⁺=672.3

Tri-*O*-methyl cellulose azide (**7**):

Compound **7** was prepared according to the method in our previous paper (Hiroshi Kamitakahara et al., 2016).

Propargyl tri-*O*-methyl cellulose (**8**):

Compound **8** was prepared according to the method in our previous paper (Hiroshi Kamitakahara et al., 2016).

1-(2,3,6-Tri-*O*-methyl-cellulosyl)-4-(2,3,4,6-tetra-*O*-acetyl-β-D-glucopyranosyl-(1→4)-2,3,6-tri-*O*-acetyl-β-D-glucopyranosyloxymethyl)-1*H*-1,2,3-triazole (**4**):

Cu (I) Br (26.7 mg, MW = 143.45, 186 mmol, 10 equiv.), sodium ascorbate (73.8 mg/0.09 mL, 20 equiv., 4 M in H₂O), and *N,N,N',N'',N''*-pentamethyldiethylenetriamine (PMDETA, MW = 173.3, *d* = 0.83 g/mL, 0.04 mL, 0.0332 g, 192 mmol, 10 equiv.) were added at room temperature to a solution of 2-propynyl

(2,3,6-tri-*O*-acetyl-β-D-glucopyranosyl)-(1→4)-2,3,6-tri-*O*-acetyl-β-D-glucopyranoside (**9**) (25.1 mg, MW = 674.6, 37.2 mmol, 2.0 equiv.) and tri-*O*-methyl cellulose azide (**7**, 98.5 mg, *M_n* = 5.37×10³, *DP_n* = 26.3, 18.4 mmol, 1.0 equiv.) in MeOH/CH₂Cl₂ (4 mL, 1/4, v/v). Distilled water (0.2 mL) was added. The reaction mixture was stirred at room temperature for four days under a nitrogen atmosphere. The mixture was concentrated and passed through a silica gel chromatography column eluted with 20% MeOH/CH₂Cl₂ to give the crude product. The crude product was purified by silica gel column chromatography (eluent: EtOAc→20% MeOH/CH₂Cl₂) to give 1-(2,3,6-tri-*O*-methyl-cellulosyl)-4-(2,3,4,6-tetra-*O*-acetyl-β-D-glucopyranosyl-(1→4)-2,3,6-tri-*O*-acetyl-β-D-glucopyranosyloxymethyl)-1*H*-1,2,3-triazole (**4**, 86.8 mg, 78.5% yield).

¹H-NMR (500 MHz, CDCl₃): δ 1.97, 1.99, 2.02, 2.07, 2.13 (COCH₃), 2.94 (t, *J*=8.5 Hz, H2_{Me} (internal)), 3.20 (t, 1H, *J*=9.0 Hz, H3_{Me} (internal)), 3.27 (m, *J*=9.5 Hz, H5_{Me} (internal)), 3.37 (s, OCH₃), 3.52 (s, OCH₃), 3.56 (s, OCH₃), 3.6-3.9 (H5_{Ac}, H4_{Ac}, H5'_{Ac}), 3.65 (H6_{Me} (internal)), 3.68 (t,

452 $J=9.0$, H_{4Me} (internal)), 3.75 (m, H_{6Me} (internal)), 3.99 (m, $J=10.0$ Hz, $H_{5\alpha Me}$, α -anomer), 4.04
453 (dd, 1H, $J=2.0$ Hz, $J=12.5$ Hz, $H_{6'Ac}$), 4.11 (dd, 1H, $J=5.0$ Hz, $J=12.0$ Hz, H_{6Ac}), 4.17 (t, $J=7.5$ Hz,
454 $H_{3\alpha Me}$, α -anomer), 4.33 (d, $J=8.0$ Hz, H_{1Me} (internal)), 4.37 ($H_{6'Ac}$), 4.50 (d, $J=8.0$ Hz, $H_{1'Ac}$),
455 4.54 (dd, $J=1.5$ Hz, $J=11.5$, H_{6Ac} , β -anomer), 4.55 (dd, $J=2.0$ Hz, $J=11.5$ Hz, H_{6Ac} , α -anomer),
456 4.60 (d, $J=8.0$ Hz, H_{1Ac} , β -anomer of methylcellulose), 4.61 (d, $J=8.0$ Hz, H_{1Ac} , β -anomer of
457 methylcellulose), 4.81 (d, 1H, $J=12.5$ Hz, OCH_2 -triazole), 4.87-4.94 (d, OCH_2 -triazole), 4.87-4.94
458 (H_{2Ac} , $H_{2'Ac}$), 5.05 (t, $J=9.5$, $H_{4'Ac}$), 5.13 (t, $J=9.5$ Hz, H_{3Ac} , $H_{3'Ac}$), 5.44 (d, 1H, $J=9.0$ Hz,
459 $H_{1\beta Me}$), 6.15 (d, $J=5.5$ Hz, $H_{1\alpha Me}$), 7.69 (s, triazole, β -anomer), 7.70 (s, triazole, α -anomer) (α/β
460 ratio = 2/1)
461 ^{13}C -NMR (125 MHz, $CDCl_3$): δ 20.4, 20.5, 20.6, 20.8 ($COCH_3$), 59.1 (OCH_3), 60.2 (OCH_3), 60.5
462 (OCH_3), 61.6, 61.7 ($C_{6'Ac}$), 61.8 (C_{6Ac}), 62.8 (OCH_2 -triazole), 67.7 ($C_{4'Ac}$), 70.2 (C_{6Me} (internal)),
463 71.3 (C_{2Ac} or $C_{2'Ac}$), 71.5 (C_{2Ac} or $C_{2'Ac}$), 71.9, 72.0 (C_{5Ac}), 72.3 ($C_{5'Ac}$), 72.7 (C_{3Ac} or $C_{3'Ac}$),
464 72.8 (C_{3Ac} or $C_{3'Ac}$), 73.0, 73.3, 73.7, 74.8 (C_{5Me} (internal)), 76.2 (C_{4Ac} (reducing end)), 77.4
465 (C_{4Me} (internal)), 77.8 (C_{4Me} (reducing end)), 79.3, 79.5, 81.0 ($C_{3\alpha Me}$), 82.1 (C_{2Me} (reducing end)),
466 83.3 ($C_{1\alpha Me}$), 83.4 (C_{2Me} (internal)), 83.7, 83.7, 84.0, 84.8, 85.0 (C_{3Me} (internal)), 85.3 (C_{4Me}
467 (reducing end)), 86.1, 86.9, 87.3 ($C_{1\beta Me}$ (reducing end)), 99.6 (C_{1Ac}), 100.7 ($C_{1'Ac}$), 103.1 (C_{1Me}
468 (internal)), 103.7 (C_{1Me}), 124.5 (triazole CH), 143.2 ($O-CH_2-C=$), 168.9, 169.2, 169.6, 169.7, 170.2,
469 170.3, 170.4 ($COCH_3$)
470
471 1-(2,3,6-Tri-*O*-methyl-cellulosyl)-4-[β -D-glucopyranosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosyloxymethyl]-1
472 *H*-1,2,3-triazole (**1**):
473 Sodium methoxide (28%) in methanol (0.02 mL, 10 equiv. per AGU) was added at room
474 temperature to a solution of
475 1-(2,3,6-tri-*O*-methyl-cellulosyl)-4-(2,3,4,6-tetra-*O*-acetyl- β -D-glucopyranosyl-(1 $\rightarrow$ 4)-2,3,6-tri-*O*-a
476 cetyl- β -D-glucopyranosyloxymethyl)-1*H*-1,2,3-triazole (**4**, 76.3 mg) in MeOH (3 mL) and THF (3.5
477 mL). The mixture was stirred overnight at room temperature. The solution was neutralized with
478 Amberlyst H^+ . The Amberlyst H^+ was filtered off and washed with MeOH. The combined filtrate
479 and washings were concentrated to dryness to give
480 1-(2,3,6-tri-*O*-methyl-cellulosyl)-4-[β -D-glucopyranosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosyloxymethyl]-1*H*
481 -1,2,3-triazole (**1**, 79.3 mg, quantitative yield).
482 1H -NMR (500 MHz, D_2O): δ 3.03 (t, $J=8.5$ Hz, H_{2Me} (internal)), 3.29 (s, OCH_3), 3.34 (t, 1H, $J=8.0$
483 Hz, H_{3Me} (internal)), 3.46 (s, OCH_3), 3.47 (s, OCH_3), 4.32 (d, $J=7.0$ Hz, H_{1Me} (internal)), 4.38 (d,
484 $J=8.0$ Hz), 4.46 (d, $J=7.5$ Hz), 4.46 (d, $J=8.0$ Hz), 4.67, 4.80 (d, $J=13.0$ Hz, OCH_2 -triazole), 4.90 (d,
485 $J=12.5$ Hz, OCH_2 -triazole), 5.68 (d, 1H, $J=9.5$ Hz, $H_{1\beta Me}$), 6.42 (d, $J=5.5$ Hz, $H_{1\alpha Me}$), 8.16, 8.24,
486 8.32 (s, triazole CH)
487 ^{13}C -NMR (125 MHz, D_2O): δ 58.3 (OCH_3 (internal)), 58.5, 58.8, 58.9 (OCH_3 (internal)), 59.8,

488 60.3 (OCH₃ (internal)), 60.5, 61.1, 64.0, 68.8, 69.4, 69.8 (C6_{Me} (internal)), 70.4, 70.7, 72.7, 73.1,
489 73.6 (C5_{Me} (internal)), 74.2, 74.8, 75.4, 75.7, 76.0 (C4_{Me} (internal)), 76.9, 78.4, 82.1 (C2_{Me}
490 (internal)), 82.5, 83.0 (C3_{Me} (internal)), 85.0, 101.3 (C1_{OH}), 102.4 (C1_{Me} (internal)), 102.5 (C1'_{OH})
491 GPC analysis of acetylated compound **1**: $M_n=4.9\times 10^3$, $M_w/M_n=1.7$, $DP_n=23$ (including DP of
492 hydrophilic segment)
493
494 1-(Tri-*O*-methyl-cellulosyl)-4-(2,3,4-tri-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucop
495 yranosyl)-(1→4)-2,3-di-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucopyranosyloxy
496 methyl)-1*H*-1,2,3-triazole (**5**):
497 CuSO₄·H₂O (34.0 mg, MW = 249.69, 136 mmol, 10 equiv.), sodium ascorbate (54.0 mg/68 μL, 20
498 equiv., 4 M in H₂O), and PMDETA (MW = 173.3, $d = 0.83$ g/mL, 28 μL, 23.2 mg, 134 mmol, 10
499 equiv.) were added to a solution of 2-propynyl
500 [2,3,4-tri-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucopyranosyl]-(1→4)-2,3-di-*O*-ac
501 etyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucopyranoside (**10**, 32.2 mg, MW = 788.8, 40.8
502 mmol, 3.0 equiv.) and tri-*O*-methyl cellulosyl azide (**7**, 100 mg, $M_n = 7.34\times 10^3$, $DP_n = 35.8$, 13.6
503 mmol, 1.0 equiv.) in tetrahydrofuran (3 mL). The reaction mixture was stirred at 50 °C overnight in
504 a nitrogen atmosphere. The mixture was concentrated and passed through a silica gel
505 chromatography column eluted with 10% MeOH/CH₂Cl₂ to give the crude product. The crude
506 product was purified by silica gel column chromatography (eluent: EtOAc→10% MeOH/CH₂Cl₂)
507 to give
508 1-(tri-*O*-methyl-cellulosyl)-4-(2,3,4-tri-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucop
509 yranosyl)-(1→4)-2,3-di-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucopyranosyloxym
510 ethyl)-1*H*-1,2,3-triazole (**5**, 103.2 mg, 93% yield).
511 ¹H-NMR (500 MHz, CDCl₃): δ 1.44, 1.47 (CH₃ (NHBoc)), 1.97, 1.98, 2.00, 2.02, 2.02, 2.04, 2.05,
512 2.07 (CH₃ (OAc)), 2.95 (t, $J=8.0$ Hz, H2_{Me} (internal)), 3.11 (t, $J=9.0$ Hz, H3_{Me}), 3.21 (t, 1H, $J=9.0$
513 Hz, H3_{Me} (internal)), 3.29 (m, $J=9.0$ Hz, H5_{Me} (internal)), 3.3-3.4 (H6, H6', H6'), 3.6-3.65 (H6'),
514 3.38 (OCH₃), 3.54 (OCH₃), 3.58 (OCH₃), 3.62-3.72 (H6_{Me} (internal)), 3.69 (t, $J=9.5$ Hz, H4_{Me}
515 (internal)), 3.73-3.81 (m, H6_{Me} (internal)), 3.40 (H2_{Me}, reducing-end, α-anomer), 3.77 (H2_{Me},
516 reducing-end, α-anomer), 3.77 (H2_{Me}, reducing-end, α-anomer), 3.83 (H2_{Me}, reducing-end,
517 α-anomer), 3.89 (H6_{Me}, reducing-end, α-anomer), 4.04 (m, $J=9.5$ Hz, H5_{Me}, reducing-end,
518 α-anomer), 4.15 (t, $J=7.5$ Hz, H3_{Me}, reducing-end, α-anomer), 4.34 (d, $J=7.5$ Hz, H1_{Me}
519 (internal)), 4.39 (d, $J=8.0$ Hz, H1_{Me}), 4.6-4.64 (d, H1_{Ac}), 4.76 (broad d, 1H, $J=8.0$ Hz, H1'_{Ac}),
520 4.75-4.94 (CH₂, triazole-alkene), 4.90-4.96 (H2_{Ac}, H2'_{Ac}, H4'_{Ac}, NH), 5.1-5.2 (H3_{Ac}, H3'_{Ac}), 5.46
521 (d, $J=9.0$ Hz, H1β_{Me}), 6.15 (d, $J=5.0$ Hz, H1α_{Me}), 7.71, 7.76 (H, triazole)
522 ¹³C-NMR (125 MHz, CDCl₃): δ 20.6, 20.63, 20.65, 20.7, 20.8 (COCH₃), 28.4(COOC(CH₃)₃), 40.7
523 (C6, C6'), 59.0, 59.2 (OCH₃), 59.6, 60.1, 60.3 (OCH₃), 60.4, 60.5, 60.5 (OCH₃), 60.8, 62.8

524 (OCH₂-triazole), 68.5 (broad, C4' Ac), 70.3 (C6_{Me} (internal)), 71.6 (C2_{Ac} and C2'Ac), 72.1 (C3_{Ac}),
525 72.9 (C3'Ac), 73.0 (C5_{Ac} or C5'Ac), 73.1, 73.2, 73.9 (broad, C5_{Ac} or C5'Ac), 74.9 (C5_{Me}
526 (internal)), 75.5 (C4_{Ac}), 77.5 (C4_{Me} (internal)), 79.8 COOC(CH₃)₃, 83.3, 83.5 (C2_{Me} (internal)),
527 83.7 (C1_{αMe}), 84.9, 85.0 (C3_{Me} (internal)), 86.1, 99.1 (C1_{Ac}), 99.8 (C1'Ac), 103.2 (C1_{Me} (internal)),
528 122.2, 124.4 (triazole CH), 143.2, 144.2 (O-CH₂-C=), 155.8 (COOC(CH₃)₃), 169.3, 169.6, 169.7,
529 170.2 (COCH₃)
530
531 1-(Tri-*O*-methyl-cellulosyl)-4-[(6-amino-6-deoxy-β-D-glucopyranosyl)-(1→4)-6-amino-6-deoxy-β-
532 D-glucopyranosyloxymethyl]-1*H*-1,2,3-triazole (**2**):
533 Sodium methoxide (28%) in methanol (5.5 μL, 10 equiv. per AGU) were added at room
534 temperature to a solution of
535 1-(tri-*O*-methyl-cellulosyl)-4-[2,3,4-tri-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucop
536 yranosyl-(1→4)-2,3-di-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucopyranosyloxymet
537 hyl]-1*H*-1,2,3-triazole (**5**, 76.3 mg) in MeOH (2 mL), THF (2 mL), and CH₂Cl₂ (1 mL). The
538 mixture was stirred overnight at room temperature. The solution was neutralized with Amberlyst H⁺.
539 The Amberlyst H⁺ was filtered off and washed with MeOH. The combined filtrate and washings
540 were concentrated to dryness to give
541 1-(tri-*O*-methyl-cellulosyl)-4-[6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucopyranosyl-(1→4)-6
542 -(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucopyranosyloxymethyl]-1*H*-1,2,3-triazole (78.9 mg).
543 Trifluoroacetic acid (0.5 mL) was added at -20 °C to a solution of
544 1-(tri-*O*-methyl-cellulosyl)-4-[6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucopyranosyl-(1→4)-
545 6-(*tert*-butoxycarbonyl)amino-6-deoxy-β-D-glucopyranosyloxymethyl]-1*H*-1,2,3-triazole (84 mg)
546 in CH₂Cl₂ (1 mL). The reaction mixture was stirred for 1.2 h at -20 °C. The mixture was
547 concentrated to dryness at 4 °C to give the crude product. The crude product was purified by gel
548 filtration chromatography (Sephadex LH-20) to give
549 1-(tri-*O*-methyl-cellulosyl)-4-[6-amino-6-deoxy-β-D-glucopyranosyl-(1→4)-6-amino-6-deoxy-β-D-
550 glucopyranosyloxymethyl]-1*H*-1,2,3-triazole (**2**, 82.7 mg, quantitative yield).
551 ¹H-NMR (500 MHz, D₂O): δ 3.03 (t, *J*=8.5 Hz, H2_{Me} (internal)), 3.34 (t, 1H, *J*=8.5 Hz, H3_{Me}
552 (internal)), 3.42-3.49 (H5_{Me} (internal)), 3.29 (OCH₃), 3.46 (OCH₃), 3.47 (OCH₃), 3.57-3.68 (H4_{Me}
553 (internal), H6_{Me} (internal)), 4.32 (d, *J*=7.0 Hz, H1_{Me} (internal)), 4.40 (d, *J*=8.0 Hz), 4.44 (d, *J*=6.0
554 Hz), 4.79-4.95 (CH₂, triazole-alkene), 5.69 (H1β_{Me} (reducing end), *J*=9 Hz), 6.42 (H1α_{Me} (reducing
555 end), *J*=5.5 Hz), 8.17, 8.25 (s, triazole CH)
556 ¹³C-NMR (D₂O): δ 40.2 (C6-NH₂ or C6'-NH₂), 40.5 (C6-NH₂ or C6'-NH₂), 58.3 (OCH₃), 58.5, 58.9
557 (OCH₃), 59.8, 60.3 (OCH₃), 69.8 (C6_{Me} (internal)), 70.8, 73.0, 63.6 (C5_{Me} (internal)), 74.2, 74.5,
558 74.7, 75.1, 75.7, 76.0 (C4_{Me} (internal)), 82.0 (C2_{Me} (internal)), 82.5, 83.0 (C3_{Me} (internal)) 85.0,
559 101.2, 101.4, 102.4 (C1_{Me} (internal)), 102.8

560 GPC analysis of acetylated compound **2**: $M_n=7.1\times 10^3$, $M_w/M_n=1.6$, $DP_n=33$ (including DP of
561 hydrophilic segment)
562
563 4-(Tri-*O*-methyl-cellulosyloxymethyl)-1-[methyl {(methyl
564 (2,3,4-tri-*O*-acetyl- β -D-glucopyranosyl)uronate)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl- β -D-glucopyranosyl}uronat
565 e]-1*H*-1,2,3-triazole (**6**):
566 Cu (I) Br (5.6 mg, MW = 143.45, 39 mmol, 10 equiv.), sodium ascorbate (15.5 mg/19 μ L, 20 equiv.,
567 4 M in H₂O), and PMDETA (MW = 173.3, d = 0.83 g/mL, 8.2 μ L, 6.8 mg, 39 mmol, 10 equiv.)
568 were added at room temperature to a solution of methyl [(methyl
569 2,3,4-tri-*O*-acetyl- β -D-glucopyranosyluronate)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl- β -D-glucopyranosyl
570 azide]uronate (**11**, 7.4 mg, MW = 633.5, 11.7 mmol, 3.0 equiv.) and propargyl tri-*O*-methyl
571 cellulose (**8**, 30 mg, $M_n = 7.72\times 10^3$, $DP_n = 37.5$, 3.9 mmol, 1.0 equiv.) in MeOH/CH₂Cl₂ (2 mL,
572 1/4, v/v). The reaction mixture was stirred overnight at room temperature under a nitrogen
573 atmosphere. The mixture was concentrated and passed through a silica gel chromatography column
574 eluted with 10% MeOH/CH₂Cl₂ to give the crude product. The crude product was purified by silica
575 gel column chromatography (eluent: EtOAc $\rightarrow$ 10% MeOH/CH₂Cl₂) to give
576 4-(tri-*O*-methyl-cellulosyloxymethyl)-1-[methyl {(methyl (2,3,4-tri-*O*-acetyl- β -D-
577 glucopyranosyl)uronate)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl- β -D-glucopyranosyl}uronate]-1*H*-1,2,3-triazole (**6**,
578 29.9 mg, 92% yield).
579 ¹H-NMR (500 MHz, CDCl₃): δ 1.86, 1.86, 2.00, 2.02, 2.02, 2.09, 2.10 (COCH₃), 2.96 (t, $J=8.5$ Hz,
580 H2_{Me} (internal)), 3.22 (t, 1H, $J=9.0$ Hz, H3_{Me} (internal)), 3.29 (m, $J=9.0$ Hz, H5_{Me} (internal)),
581 3.39 (OCH₃), 3.54 (OCH₃), 3.58 (OCH₃), 3.66 (H6_{Me} (internal)), 3.70 (t, $J=9.0$ Hz, H4_{Me}
582 (internal)), 3.77 (broad dd, $J=3,5$ Hz, $J=11.0$ Hz, H6_{Me} (internal)), 3.84 (s, 3H, C6'OOCH₃), 3.85
583 (s, 3H, C6OOCH₃), 4.03 (dd, $J=3.5$, $J=10.0$, H5'_{Ac} (non-reducing end)), 4.18 (dd, $J=2.0$ Hz, $J=10.0$
584 Hz, H5_{Ac} (reducing end)), 4.29 (H4_{Ac} (reducing end)), 4.35 (d, $J=8.0$ Hz, H1_{Me} (internal)), 4.40 (d,
585 $J=8.0$ Hz, H1_{Me}), 4.67 (d, $J=13.0$ Hz, OCH₂-triazole), 4.67-4.68 (d, $J=8$, H1'_{Ac} (non-reducing end)),
586 4.82 (d, $J=13.5$ Hz, OCH₂-triazole), 4.85 (d, $J=13.0$ Hz, OCH₂-triazole), 4.90 (t, $J=8.5$ Hz, H2'_{Ac}
587 (non-reducing end)), 4.96 (d, $J=13.0$ Hz, OCH₂-triazole), 5.03 (d, $J=3.5$ Hz, H1 α _{Me} (reducing end)),
588 5.15 (t, $J=9.5$ Hz, H4'_{Ac} (non-reducing end)), 5.21 (t, $J=9.5$ Hz, H3'_{Ac} (non-reducing end)), 5.40 (t,
589 $J=9.0$ Hz, H2_{Ac} (reducing end)), 5.41 (t, $J=9.0$ Hz, H3_{Ac} (reducing end)), 5.84-5.87 (d, H1_{Ac}
590 (reducing end)), 7.81 (s, triazole CH)
591 ¹³C-NMR (125 MHz, CDCl₃): δ 20.1, 20.2, 20.4, 20.5 (COCH₃), 52.8, 53.3 (COOCH₃), 58.8, 59.0,
592 59.1 (OCH₃), 59.3, 59.6, 60.1, 60.1, 60.3 (OCH₃), 60.4, 50.4, 60.5 (OCH₃), 60.6 (OCH₂-triazole,
593 overlapped), 60.7, 60.8, 62.3 (OCH₂-triazole), 69.3 (C4'_{Ac} (non-reducing end)), 69.9, 70.0 (C3_{Ac}
594 (reducing end)), 70.3 (C6_{Me} (internal)), 70.6, 71.0 (C2'_{Ac} (non-reducing end)), 71.6 (C2_{Ac} (reducing
595 end)), 72.0 (C3'_{Ac} (non-reducing end)), 72.2, 72.7 (C5'_{Ac} (non-reducing end)), 73.2, 73.2, 74.6, 74.7,

596 74.9 (C5_{Me} (internal)), 76.2 (C4_{Ac} (reducing end)), 76.3 (C5_{Ac} (reducing end)), 77.5 (C4_{Me}
597 (internal)), 83.5 (C2_{Me} (internal)), 85.0 (C3_{Me} (internal)), 86.1 (C1_{Ac} (reducing end)), 95.7 (C1_αMe
598 (reducing end)), 100.3 (C1'_{Ac} (non-reducing end)), 103.2 (C1_{Me} (internal)), 103.4 (C1_{Me}), 121.4
599 (triazole CH), 145.1 (O-CH₂-C=), 166.6 (C6'_{Ac} OCH₃), 166.8 (C6_{Ac} OCH₃), 169.0, 169.3, 169.7,
600 169.8, 170.1 (COCH₃)

601

602 4-(Tri-*O*-methyl-cellulosityloxymethyl)-1-[β-D-glucopyranuronosyl-(1→4)-β-D-glucopyranuronosyl]
603 -1*H*-1,2,3-triazole (**3**):

604 An aqueous solution of sodium hydroxide (0.0125 M, 1.5 mL) was added at room temperature to a
605 solution of 4-(tri-*O*-methyl-cellulosityloxymethyl)-1-[methyl (methyl
606 2,3,4-tri-*O*-acetyl-β-D-glucopyranuronate)-(1→4)-2,3-di-*O*-acetyl-β-D-glucopyranuronosyl]-1*H*-1,2
607 ,3-triazole (**6**, 14.4 mg) in THF (1 mL). The reaction mixture was stirred at room temperature for 30
608 min. The solution was neutralized with Amberlyst H⁺. The Amberlyst H⁺ was filtered off and
609 washed with tetrahydrofuran. The combined filtrate and washings were concentrated to dryness to
610 give the crude product. The crude product was purified by gel filtration chromatography (Sephadex
611 LH-20) to give 4-(tri-*O*-methyl-
612 cellulosityloxymethyl)-1-[(β-D-glucopyranuronosyl)-(1→4)-β-D-glucopyranuronosyl]-1*H*-1,2,3-triaz
613 ole (**3**, 13.8 mg, 99% yield).

614 ¹H-NMR (500 MHz, D₂O): δ 3.03 (t, 1H, *J*=8.5 Hz, H2_{Me} (internal)), 3.27 (H2_{Me}), 3.34 (t, 1H,
615 *J*=9.0 Hz, H3_{Me} (internal)), 3.47 (H5_{Me} (internal)), 3.29 (OCH₃), 3.46 (OCH₃), 3.47 (OCH₃), 3.64
616 (H4_{Me} (internal)), 3.6-3.7 (H6_{Me} (internal)), 3.77 (H4_{OH}), 3.96 (H3_{OH}), 4.02 (H2_{OH}), 4.31 (d, *J*=5.5
617 Hz, C1_{Me} (internal)), 4.43 (d, *J*=7.0 Hz, H1_{Me}), 4.72 (OCH₂-triazole), 4.80 (d, *J*=14.0 Hz,
618 OCH₂-triazole), 4.88 (d, *J*=13.5 Hz, OCH₂-triazole), 5.71 (d, *J*=8.5 Hz, H1_{OH}), 8.23 (s, triazole CH)
619 ¹³C-NMR (125 MHz, D₂O): δ 58.3 (OCH₃), 58.5, 58.9 (OCH₃), 59.8, 60.3 (OCH₃), 60.4
620 (OCH₂-triazole), 62.2 (OCH₂-triazole), 68.8, 69.8 (C6_{Me} (internal)), 71.8 (C3_{OH}), 73.0, 73.6 (C5_{Me}
621 (internal)), 74.2, 74.6 (C4_{OH}), 75.9 (C4_{Me} (internal)), 78.0 (C2_{OH}), 80.3 (C2_{Me}), 82.1 (C2_{Me}
622 (internal)), 82.5, 83.0 (C3_{Me} (internal)), 85.0 (C3_{Me}), 87.0 (C1_{OH}), 101.1, 101.3, 102.3 (C1_{Me}
623 (internal)), 124.5 (triazole CH), 144.0 (O-CH₂-C=)

624 GPC analysis of acetylated compound **3**: *M*_n=9.1×10³, *M*_w/*M*_n=1.9, *DP*_n=43 (including DP of
625 hydrophilic segment)

626

627 3. Results and Discussion

628 3.1. Synthesis of trehalose-type diblock methylcellulose analogues

629 Three hydrophilic segments, nonionic, cationic, and anionic cellobiosyl residues, were coupled with
630 hydrophobic permethylated methylcellulose segments via the Huisgen 1,3-dipolar cycloaddition to
631 produce trehalose-type diblock methylcellulose analogues.

632

633 3.1.1. Synthesis of hydrophilic segments

634 2-Propynyl 2,3,6-tri-*O*-acetyl- β -D-glucopyranosyl-(1 $\rightarrow$ 4)-2,3,6-tri-*O*-acetyl- β -D-glucopyranoside635 (**9**), 2-propynyl636 2,3,4-tri-*O*-acetyl-6-(*tert*-butoxycarbonyl)amino-6-deoxy- β -D-glucopyranosyl-(1 $\rightarrow$ 4)-2,3-di-*O*-acet637 yl-6-(*tert*-butoxycarbonyl)amino-6-deoxy- β -D-glucopyranoside (**10**), and methyl [(methyl638 2,3,4-tri-*O*-acetyl- β -D-glucopyranosyluronate)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl- β -D-glucopyranosyl639 azide]uronate (**11**) were synthesized according to the synthetic routes shown in Scheme 1.640 Compound **9** was prepared from cellobiose via cellobiose octaacetate (**12**) (H. Kamitakahara &641 Nakatsubo, 2005) and is a precursor of the nonionic hydrophilic segment that gives compound **1**.642 Huisgen 1,3-dipolar cycloaddition of compounds **7** and **9** produced compound **4**. The removal of643 the acetyl groups of compound **4** afforded compound **1**. Compound **1** is analogous to644 cellobiosyl-(1 $\rightarrow$ 4)-methylcellulose, diblock methylcellulose (Nakagawa et al., 2011b), which645 possesses thermoreversible gelation properties. Nonionic compound **1** is also a standard for cationic646 compound **2** and anionic compound **3**. In other words, nonionic compound **9** is also a standard for647 cationic compound **10** and anionic compound **11**.

648

649

650 Scheme 1. Synthetic routes for trehalose-type diblock methylcellulose analogues **1**, **2**, and **3**

651

652 a) 2-propyn-1-ol/ $\text{BF}_3\text{Et}_2\text{O}$ / anhydrous CH_2Cl_2 /r.t./ 23h/99%; b) 28% NaOCH_3 in MeOH/ THF/MeOH/r.t./3h/96%; c)

653 TsCl /Pyridine/ 8°C / 2.5h/51%; d) Ac_2O /Pyridine/ r.t./overnight/ 95%; e) NaN_3 /DMF/ 50°C /overnight/97%; f)

654 28% NaOCH_3 in MeOH/ THF/MeOH/r.t./overnight/ 87%; g) Ph_3P / H_2O / THF/MeOH/r.t./14d/98%; h) Ac_2O / AcONa /

655 80°C /3h; Ac_2O /Pyridine/ 80°C /1h/ 96%; i) Boc_2O /DMAP/ THF/reflux/22.5h; j) 28% NaOCH_3 in MeOH/

656 CH_2Cl_2 /MeOH/r.t./6h; k) Ac_2O /Pyridine/ 60°C /2h/77%; l) TMSN_3 / SnCl_4 / CHCl_3 /r.t./overnight/99%; m) 28% NaOCH_3

657 in MeOH/ CH_2Cl_2 /MeOH/r.t./ quantitative yield; n) TEMPO/ KBr / NaOCl /sat. aq. NaHCO_3 / 4°C /1d; o)

658 2,2-dimethoxypropane/conc. HCl/ MeOH/r.t./ 1d; p) Ac₂O/AcONa/60°C/overnight/ total yield 11% from compound **23**;
659 q) Cu(I)Br/ sodium ascorbate in water/ PMDETA/MeOH:CH₂Cl₂ (1:4, v/v), distilled water/r.t./4 days; r) CuSO₄·H₂O/
660 sodium ascorbate in water/ PMDETA/THF/50°C/overnight; s) CuSO₄·H₂O/ sodium ascorbate in water/
661 PMDETA/THF/50°C/overnight; t) 28%NaOCH₃ in MeOH/ THF/MeOH/r.t./overnight; u) 28%NaOCH₃ in MeOH/
662 THF/MeOH/CH₂Cl₂ /r.t./overnight; trifluoroacetic acid/-20°C/1.2 h; v) 0.0125 M NaOH/THF/r.t./30 min/99% yield
663
664 The synthesis of amino-functionalized cellobiose compound **10** from 2-propynyl
665 (6-amino-6-deoxy-β-D-glucopyranosyl)-(1→4)-6-amino-6-deoxy-β-D-glucopyranoside (**18**) was
666 analogous to a method for a glucosamine derivative (Chen et al., 2010). Compound **10** was
667 converted from compound **9** in 10 reaction steps. The *N*-acetyl groups at the C-6 positions of
668 compound **19** would be relatively stable under alkali conditions. The amino groups of compound **18**
669 are reactive and labile and are therefore protected by *tert*-butoxycarbonyl (Boc) groups. The
670 primary hydroxy groups at the C-6 positions of compound **13** were tosylated with *p*-toluenesulfonyl
671 chloride to give compound **14** in 51% yield. The four secondary hydroxy groups of compound **14**
672 were acetylated with acetic anhydride in pyridine to give compound **15** in 95% yield. The tosylate
673 **15** was treated with sodium azide to give azide derivative **16** in 97% yield via a nucleophilic
674 substitution at the C-6 positions. Removal of the acetyl groups of compound **16** produced
675 compound **17** in 87% yield. A Staudinger reaction afforded amino derivative **18** from azido
676 compound **17** in 98% yield. Compound **18** is an analogous derivative of a chitosan dimer. Because
677 the reactivity and stability of compound **18**, without protective groups for the amino and hydroxy
678 groups, are unknown, the protected compound **10** was selected as the reactant for Huisgen
679 1,3-dipolar cycloaddition. Compound **18** was acetylated to give 6-(acetyl)amino derivative **19**.
680 Butoxycarbonylation of *N*-(acetyl)amino compound **19** followed by removal of the acetyl groups
681 afforded 6-(Boc)amino derivative **21** via 6-acetyl(Boc)amino derivative **20**. Compound **21** was
682 acetylated to give 2-propynyl
683 (2,3,4-tri-*O*-acetyl-6-(Boc)amino-6-deoxy-β-D-glucopyranosyl)-(1→4)-2,3-di-*O*-acetyl-6-(Boc)ami
684 no-6-deoxy-β-D-glucopyranoside (**10**). Compound **10** is a precursor of the cationic hydrophilic
685 segment that gives compound **2**.
686 Compound **11** was prepared from cellobiose octaacetate (**12**) (H. Kamitakahara & Nakatsubo,
687 2005) in five reaction steps and is a precursor of the anionic hydrophilic segment that gives
688 compound **3**. Compound **11** is a glycosyl azide derivative, although compounds **9** and **10** are
689 2-propenyl glycosides. The alkyne group was unstable under the reaction conditions for TEMPO
690 oxidation of the primary alcohol. Methyl [(methyl
691 2,3,4-tri-*O*-acetyl-β-D-glucopyranosyluronate)-(1→4)-2,3-di-*O*-acetyl-β-D-glucopyranosyl
692 azide]uronate (**11**) was therefore chosen as the hydrophilic segment and treated with 2-propynyl
693 tri-*O*-methyl-celluloside to produce compound **6**. Cellobiose octaacetate (**12**) was converted into
694 2,3,4,6-tetra-*O*-acetyl-β-D-glucopyranosyl-(1→4)-2,3,6-tri-*O*-acetyl-β-D-glucopyranosyl azide (**22**)

695 (H. Kamitakahara & Nakatsubo, 2005). Removal of the acetyl groups of compound **22** gave
696 β -D-glucopyranosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosyl azide (**23**). TEMPO oxidation of cellobiosyl azide
697 **23** gave (β -D-glucopyranuronosyl)-(1 $\rightarrow$ 4)- β -D-glucopyranuronosyl azide (**24**). The uronic acids of
698 compound **24** were esterified to give methyl [(methyl
699 β -D-glucopyranosyluronate)-(1 $\rightarrow$ 4)- β -D-glucopyranosyl azide]uronate (**25**). The remaining hydroxy
700 groups of compound **25** were acetylated to give methyl [(methyl
701 2,3,4-tri-*O*-acetyl- β -D-glucopyranosyluronate)-(1 $\rightarrow$ 4)-2,3-di-*O*-acetyl- β -D-glucopyranosyl
702 azide]uronate (**11**).
703 Figure 1A shows ^1H -NMR spectra of cellobiose derivatives **9**, **10**, and **11**. Figure S1 in the
704 Supporting Information show ^{13}C -NMR spectra of cellobiose derivatives **9**, **10**, and **11**.

3.1.2. Synthesis of trehalose-type diblock methylcellulose analogues **1**, **2**, and **3**

The Huisgen 1,3-dipolar cycloaddition followed by removal of the protective groups afforded the nonionic, cationic, and anionic diblock methylcellulose analogues 1-(tri-*O*-methyl-cellulosyl)-4-(β -D-glucopyranosyl-(1 $\rightarrow$ 4)- β -D-glucopyranosyloxymethyl)-1*H*-1,2,3-triazole (**1**), 1-(tri-*O*-methyl-cellulosyl)-4-(6-amino-6-deoxy- β -D-glucopyranosyl-(1 $\rightarrow$ 4)-6-amino-6-deoxy- β -D-glucopyranosyloxymethyl)-1*H*-1,2,3-triazole (**2**), and 4-(tri-*O*-methyl-cellulosyloxymethyl)-1-(β -D-glucopyranuronosyl-(1 $\rightarrow$ 4)-D-glucopyranuronosyl)-1*H*-1,2,3-triazole (**3**), as shown in Scheme 1.

The Huisgen 1,3-dipolar cycloaddition between the alkyne and azido derivatives was successfully carried out. An excess amount, three equivalents, of cellobiose derivatives **9**, **10**, and **11** relative to polymeric methylcellulose derivatives **7** and **8** produced trehalose-type diblock methylcellulose derivatives **4**, **5**, and **6** with no remaining **7** and **8**. In the MALDI-TOF mass spectra shown in Figure S2, we observed pseudo-molecular-ion peaks for compounds **4**, **5**, and **6** (see the Supporting Information), which means that complete end-functionalization of the methylcellulose derivatives was carried out via the Huisgen 1,3-dipolar cycloaddition.

Figure 1B shows the ^1H -NMR spectra of compounds **4**, **5**, and **6** obtained as a result of the Huisgen 1,3-dipolar cycloadditions. The proton resonances of the cellobiose segments were small relative to those of the polymeric methylcelluloses. The triazole ring proton, however, appeared at approximately 7.7–7.8 ppm, which enabled us to confirm the successful formation of the trehalose-type diblock methylcellulose analogues. The ^1H -NMR spectrum of compound **4** revealed that the C-1 proton of the α - and β -anomers of the methylcellulosyl residue appeared at 6.15 and 5.44 ppm, respectively. The α/β ratio was approx. 2/1. Two triazole protons appeared in the ^1H -NMR spectra of compounds **4** and **5**, which means that the α - and β -anomers of the methylcellulosyl residue affected the chemical shift of those 1,2,3-triazole protons. In contrast, one triazole proton appeared in the ^1H -NMR spectra of compound **6**. The proton resonance corresponding to the anomeric center of the methyl glucopyranosiduronate residue attached to the triazole unit appeared at approx. 5.8–5.9 ppm as a doublet. The anomeric center at the reducing end of the methylcelluloside appeared at 5.03 ppm as a doublet ($J=3.5$ Hz). After the removal of the acyl groups of compounds **4**, **5**, and **6**, the proton resonances of the unmodified cellobiosyl residues of compounds **1**, **2**, and **3** overlapped with those of methylcellulose (data not shown). Therefore, we were unable to conclude from the results of the NMR analysis that compounds **1**, **2**, and **3** were obtained. However, the MALDI-TOF mass spectra of compounds **1**, **2**, and **3** proved that we succeeded in establishing synthetic routes for these target compounds (Figure

S2). The MALDI-TOF mass spectrum of compound **1** shows that the pseudo-molecular-ion peaks of compound **1** appeared as sodium adducts. In contrast, the MALDI-TOF mass spectrum of compound **2** revealed that amino derivative **2** was observed as a proton adduct. The synthesis of compound **3** from compound **6** under alkali conditions did not remove the a proton (H-5) of the C-6 carbonyl carbon atom of the hydrophilic segment to promote β -elimination; therefore, there was no depolymerization of a glucuronic acid at the non-reducing end of the hydrophilic segment of compound **3**. We did not observe any evidence of the β -elimination, as shown in Figure 1, although there are unassigned peaks. Purity of compounds **1**, **2**, and **3** was confirmed by means of MALDI-TOF MS, GPC after acetylation, and analytical thin layer chromatography (TLC). In addition, the zeta potential of compounds **1**, **2**, and **3** revealed that compounds **2** and **3** involve cationic and anionic functional groups, respectively, as summarized later in Table 1. The zeta potential data also proved that compounds **1**, **2**, and **3** were produced.

3.2. Physical properties of trehalose-type diblock methylcellulose analogues **1**, **2**, and **3**

Some physical properties of compounds **1**, **2**, and **3** are summarized in Table 1. We investigated the properties of the aqueous solutions. Nonionic compound **1** shows a negative zeta potential (-6.8 mV), likely because oxygen atoms along the methylcellulose residue affect the negative charge for the whole molecule. The zeta potential of cationic compound **2** was slightly higher than that of nonionic compound **1**. Two amino groups at the end of molecule **2** affected the total zeta potential of compound **2** in water. The zeta potential of compound **3** was the lowest among compounds **1**, **2**, and **3**, which means that the carboxylic acid at the end of the molecule affected the overall zeta potential of compound **3**. Table 1 also summarizes the interfacial properties, DLS data of the aqueous solutions, DSC data, and gelation properties.

Table 1. Physicochemical properties of compounds **1**, **2**, and **3**

Compound no.	Zeta potential (mV)	Interfacial property		Aggregation temperature (°C) judged by DLS (0.2 wt%)	Thermal property detected by DSC (4.0 wt%)		Gelation property	
	0.2 wt%, 35°C	Critical Micelle Concentration (CMC) (mg/mL)	Surface tension at CMC (mN/m)		Endothermic peak (°C)	Exothermic peak (°C)	2.0 wt%	4.0 wt%
1	-6.8	6.5×10^{-3}	48.2	33	29	5	+	+
2	-3.9	2.6×10^{-3}	44.0	34	33	8	-	+
3	-28.2	3.5×10^{-3}	44.3	20-29	24	3	-	+

3.2.1. Surface activity of aqueous solutions of compounds **1**, **2**, and **3**

The trehalose-type diblock methylcellulose analogues **1**, **2**, and **3** exhibited amphiphilic properties and better surface activities than commercially available methylcellulose SM-4, as shown in Figure 2. The surface activity was in the order **2** > **3** > **1**. In particular, cationic compound **2** exhibited the best surface activity among the compounds tested, likely because its diblock structure, comprising a

775 cationic segment with amino groups and a slightly anionic methylcellulose segment, affected its
776 self-assembly behavior. Moreover, the surface-tension–concentration curve of compound **2** was
777 atypical. Namely, any phase transition of compound **2** might occur over 0.16 mg/mL. The
778 mechanism of concentration-dependent aggregation behavior for trehalose-type diblock
779 methylcellulose analogues is now under investigation.

780

781 Figure 2. Surface tension–concentration curves of compounds **1**, **2**, and **3**; blue solid square: **1**;
782 orange solid triangle: **2**; green solid circle: **3**; black solid diamond: commercially available
783 methylcellulose SM-4.

784

785 Figure 3. Hydrodynamic diameter of 0.2 wt.% aq. solution of compounds **1**, **2**, and **3** (a) and
786 expanded graph of 2.0 wt.% aq. solution of compound **3** (b) as a function of temperature; blue solid
787 square: **1**; orange solid triangle: **2**; green solid circle: **3**; black solid diamond: commercially
788 available methylcellulose SM-4.

789

790 3.2.2. Thermoresponsive aggregation behavior of compounds **1**, **2**, and **3** in water

791 The aggregation properties of compounds **1**, **2**, and **3** in 0.2 wt. % aqueous media were different, as
792 shown in Figure 3. Compounds **1** and **2** suddenly aggregated at 33 °C and 34 °C, respectively, but
793 compound **3** did not show obvious aggregation properties. In contrast, the 2.0 wt. % aqueous
794 solution of compound **3** gradually aggregated in the range from 20 to 29 °C, likely because its
795 relatively large negative zeta potential would inhibit its self-aggregation behavior. The hydrophilic
796 segments affected molecular aggregation, with the result that the nonionic, cationic, and anionic
797 compounds exhibited different thermoresponsive temperatures.

798

799 3.2.2. Thermal properties of aqueous solutions of compounds **1**, **2**, and **3**

800 Figure 4 shows DSC data for aqueous solutions of compounds **1**, **2**, and **3**. Nonionic compound **1**
801 and cationic compound **2** exhibited endothermic peaks at 29 °C and 33 °C, respectively. In contrast,
802 anionic compound **3** exhibited a broad endothermic peak in the range from 13 to 30 °C. The
803 endothermic peak indicated dehydration surrounding the methylcellulose analogues. The results of
804 DLS experiments are consistent with those of DSC analysis, indicating that a dehydration process
805 followed by self-aggregation occurred. For instance, the endothermic peak of the aqueous solution
806 of compound **1** appeared at 29 °C upon heating (heating rate: 3.5 °C/min). After the endothermic
807 temperature of compound **1** at 29 °C was detected by DSC measurements, the aggregation of
808 compound **1** was apparently observed by DLS measurements at 33 °C, as summarized in Table 1.
809 The same tendency was also observed for compound **2**. The dehydration of compound **3** occurred
810 slowly, likely because the large negative zeta potential of compound **3** would disturb the
811 intermolecular aggregation process.

812

813

814 Figure 4. DSC thermograms of 2.0 wt. % aqueous solutions of compounds **1**, **2**, and **3**. Heating rate:
815 3.5°C/min.

816

817 3.3. Observation of thermoresponsive supramolecular hydrogels comprising compounds **1**, **2**, 818 and **3**

819 3.3.1. Visual observation of thermoresponsive supramolecular hydrogels

820 Figure 5 shows photographs of dispersions of compounds **1**, **2**, and **3** in water at 0, 30, and 35 °C.
821 With increasing temperature, the trehalose-type methylcellulose analogues self-aggregated,
822 triggered by dehydration around the molecules. The multi-molecular assembly of the trehalose-type
823 methylcellulose analogues caused a macroscopic change from sol to hydrogel. A 2 wt. % aqueous
824 solution of nonionic compound **1** became a hydrogel at 30 °C. In contrast, 2 wt. % aqueous
825 solutions of cationic compound **2** and anionic compound **3** stayed in the sol state. However, 4 wt. %
826 aqueous solutions of ionic compounds **2** and **3** became hydrogels at 35 and 30 °C, respectively. A 4
827 wt. % aqueous solution of nonionic compound **1** also became a hydrogel at 30 °C.

828

829

830 Figure 5. Photographs of dispersion of compounds **1**, **2**, and **3** in water at 0, 30, and 35°C

831

832 3.3.2. Layered structure of lyophilized hydrogels from compounds **1**, **2** and **3**.

833 Scanning electron microscopy images are shown in Figure 6 a–f. The sections of the three kinds of

834 hydrogels show layered structures (Figure 6, insets b, d, and f). Short, regularly arranged
835 protuberances can be seen on one side of the layers (Figure 6 a, c and e). The surfaces of the layers
836 in the hydrogel from cationic compound **2** were very smooth relative to those in the hydrogels from
837 compounds **1** and **3**, which suggests that the chemical structure of the hydrophilic segments affects
838 the structure of the hydrogels.

839

840 Figure 6. Scanning electron microscopic images of hydrogels from compounds **1** (a, b), **2** (c, d), and
841 **3** (e, f); a transmission electron microscopic image of compound **1** (g). a, c, e were enlarged images
842 from low magnified images (b, d and f). Arrows in g indicate square and rectangular aggregated
843 particles.

844

845 3.3.3. Ultrastructures of thermoresponsive supramolecular hydrogel of compound **1**

846 A transmission electron microscopy image is shown in Figure 6 g. Square or rectangular structures
847 of approximately 20 nm × 20–55 nm (Figure 6 g, arrows) can be seen. In addition, a long linear
848 structure of approximately 20 nm width with short fine protuberances on both sides was observed.
849 The molecular length of compound **1** is approx. 10 nm. Two molecules of compound **1** exist in the
850 20 nm width for a short side of a rectangular structure. We propose a hypothesis for how the
851 molecules of compound **1** self-assembled to form square or rectangular structures in Figure S3 in
852 the Supporting Information. The thickness of those structures was approximately 1.2 nm, as

confirmed by atomic force microscopy (data not shown). The long side of the rectangular structure alters depending on the particles. Hydrophobic interactions between tri-*O*-methylcellulose segments would elongate the long side of the rectangular structure upon heating. Hydrogen bonding between hydrophilic segments would drive self-assembly between square and/or rectangular structures to form a linear structure over 1 μm . This combined structure would grow into a shish-kebab-like supramolecular structure. Finally those shish-kebab-like supramolecular structures would grow into a two-dimensional sheet structure, as shown in Figure 6 a.

4. Conclusion

We succeeded in the methylcellulose analogues end-functionalized with nonionic and ionic cellobiose derivatives via Huisgen 1,3-dipolar cycloaddition. New trehalose-type diblock methylcellulose analogues, nonionic **1**, cationic **2**, and anionic **3**, provide understanding of the detailed structure–property relationships of cellulose ether derivatives. The synthetic routes for them were shortened, relative to those we have already reported (Nakagawa et al., 2012). The methodology described in this paper allows us to synthesize a variety of diblock methylcellulose analogues with a series of hydrophilic segments, thereby developing new applications of cellulose derivatives. Cationic compound **2** exhibited higher surface activity than anionic compound **3** and nonionic compound **1**. The two amino groups at the end of the trehalose-type diblock methylcellulose analogue affected its self-assembly behavior at the interface between water and air. Not only nonionic **1** but also cationic **2** and anionic **3** formed thermoresponsive supramolecular hydrogels in water at under 37 °C, close to human body temperature. This fact means that the methylcellulose-based hydrogels including a nonionic or ionic cellobiosyl segment would respond to human body temperature and are comparable with those based on poly(*N*-isopropyl acrylamide) (Ashraf, Park, Park, & Lee, 2016). These methylcellulose-based new materials will be applicable for the similar uses as poly(*N*-isopropyl acrylamide). Trehalose-type methylcellulose analogues from natural resource would produce eco-friendly surfactant, and safe thermoresponsive hydrogel matrices for drug release.

Acknowledgements

This work was in part supported by Grants-in-Aid for Scientific Research (B) nos. 24380092 and 15H04531.

Figure Legends

Scheme 1. Synthetic routes for cellobiose derivatives

Figure 1. ¹H-NMR spectra of (A) cellobiose derivatives **9**, **10**, and **11**, and (B) compounds **4**, **5**, and **6** after CuAAC reaction

- 889 Figure 2. Surface tension-concentration curves of compounds **1**, **2**, and **3**; blue solid circle: **1**;
890 orange solid circle: **2**; green solid circle: **3**; black solid circle: commercially available
891 methylcellulose SM-4.
- 892 Figure 3. Hydrodynamic diameter of 0.2 wt.% aq. solution of compounds **1**, **2**, and **3** (a) and
893 expanded graph of 2.0 wt.% aq. solution of compound **3** (b) as a function of temperature; blue solid
894 circle: **1**; orange solid circle: **2**; green solid circle: **3**; black solid circle: commercially available
895 methylcellulose SM-4.
- 896 Figure 4. DSC thermograms of 2.0 wt. % aqueous solutions of compounds **1**, **2**, and **3**. Heating rate:
897 3.5°C/min.
- 898 Figure 5. Photographs of dispersion of compounds **1**, **2**, and **3** in water at 0, 30, and 35°C
- 899 Figure 6. Scanning electron microscopic images of hydrogels from compounds **1** (a, b), **2** (c, d), and
900 **3** (e, f); a transmission electron microscopic image of compound **1** (g). a, c, e were enlarged images
901 from low magnified images (b, d and f). Arrows in g indicate square and rectangular aggregated
902 particles.
- 903
- 904 Table 1. Physicochemical properties of compounds **1**, **2**, and **3**
- 905
- 906 Figure S1. ¹³C-NMR spectra of cellobiose derivatives **9**, **10**, and **11**
- 907 Figure S2. MALDI-TOF MS spectra of compounds after CuAAC reaction and of compounds **1**, **2**,
908 and **3** after removal of protective groups
- 909 Figure S3. Schematic figure of self-assembly process of compound **1** upon heating
910 Red hexagon: 2,3,6-tri-*O*-methyl glucose residue; Blue hexagon: unmodified glucose residue
911
- 912 **References**
- 913 Ashraf, S., Park, H.-K., Park, H., & Lee, S.-H. (2016). Snapshot of phase transition in
914 thermoresponsive hydrogel PNIPAM: Role in drug delivery and tissue
915 engineering. *Macromol. Res.*, 24(4), 297-304.
- 916 Chen, Q., Bian, N., Cao, C., Qiu, X. L., Qi, A. D., & Han, B. H. (2010). Glucosamine
917 hydrochloride functionalized tetraphenylethylene: A novel fluorescent probe for
918 alkaline phosphatase based on the aggregation-induced emission. *Chemical*
919 *Communications*, 46(23), 4067-4069.
- 920 Heinze, T., Erler, U., Nehls, I., & Klemm, D. (1994). Determination of the substituent
921 pattern of heterogeneously and homogeneously synthesized carboxymethyl
922 cellulose by using high-performance liquid chromatography. *Angew. Makromol.*
923 *Chem.*, 215, 93-106.
- 924 Hossel, P., Dieing, R., Norenberg, R., Pfau, A., & Sander, R. (2000). Conditioning

- 925 polymers in today's shampoo formulations - efficacy, mechanism and test
926 methods. *Int. J. Cosmet. Sci.*, 22(1), 1-10.
- 927 Isogai, A., & Kato, Y. (1998). Preparation of polyuronic acid from cellulose by
928 TEMPO-mediated oxidation. *Cellulose (London)*, 5(3), 153-164.
- 929 Kamitakahara, H., & Nakatsubo, F. (2005). Synthesis of diblock copolymers with
930 cellulose derivatives. 1. Model study with azidoalkyl carboxylic acid and
931 cellobiosylamine derivative. *Cellulose*, 12(2), 209-219.
- 932 Kamitakahara, H., Nakatsubo, F., & Klemm, D. (2006). Block co-oligomers of
933 tri-O-methylated and unmodified cello-oligosaccharides as model compounds for
934 methylcellulose and its dissolution/gelation behavior. *Cellulose*, 13(4), 375-392.
- 935 Kamitakahara, H., Suhara, R., Yamagami, M., Kawano, H., Okanishi, R., Asahi, T., &
936 Takano, T. (2016). A versatile pathway to end-functionalized cellulose ethers for
937 click chemistry applications. *Carbohydrate Polymers*, 151, 88-95.
- 938 Kato, T., Yokoyama, M., & Takahashi, A. (1978). Melting temperatures of thermally
939 reversible gels. *Colloid and Polymer Science*, 256, 15-21.
- 940 Moni, L., Marra, A., Skotnicki, J. S., Koehn, F. E., Abou-Gharbia, M., & Dondoni, A.
941 (2013). Synthesis of rapamycin glycoconjugates via a CuAAC-based approach.
942 *Tetrahedron Lett.*, 54(51), 6999-7003.
- 943 Nakagawa, A., Fenn, D., Koschella, A., Heinze, T., & Kamitakahara, H. (2011a).
944 Physical Properties of Diblock Methylcellulose Derivatives with Regioselective
945 Functionalization Patterns: First Direct Evidence that a Sequence of
946 2,3,6-Tri-O-methyl-glucopyranosyl Units Causes Thermoreversible Gelation of
947 Methylcellulose. *Journal of Polymer Science Part B-Polymer Physics*, 49(21),
948 1539-1546.
- 949 Nakagawa, A., Fenn, D., Koschella, A., Heinze, T., & Kamitakahara, H. (2011b).
950 Synthesis of Diblock Methylcellulose Derivatives with Regioselective
951 Functionalization Patterns. *Journal of Polymer Science Part A-Polymer
952 Chemistry*, 49(23), 4964-4976.
- 953 Nakagawa, A., Kamitakahara, H., & Takano, T. (2012). Synthesis and
954 thermoreversible gelation of diblock methylcellulose analogues via Huisgen
955 1,3-dipolar cycloaddition. *Cellulose*, 19(4), 1315-1326.
- 956 Rees, D. A. (1972). Polysaccharide gels, A molecular view. *Chem. & Ind. (London)*, 19,
957 630-636.
- 958 Rinaudo, M. (2006). Chitin and chitosan: properties and applications. *Prog. Polym. Sci.*,
959 31(7), 603-632.
- 960 Saito, T., Kimura, S., Nishiyama, Y., & Isogai, A. (2007). Cellulose Nanofibers

- 961 Prepared by TEMPO-Mediated Oxidation of Native Cellulose.
962 *Biomacromolecules*, 8(8), 2485-2491.
- 963 Saito, T., Nishiyama, Y., Putaux, J.-L., Vignon, M., & Isogai, A. (2006). Homogeneous
964 Suspensions of Individualized Microfibrils from TEMPO-Catalyzed Oxidation of
965 Native Cellulose. *Biomacromolecules*, 7(6), 1687-1691.
- 966 Savage, A. B. (1957). Temperature-Viscosity Relationships for Water-Soluble Cellulose
967 Ethers. *Industrial and Engineering Chemistry*, 49, 99.
- 968 Schamann, M., & Schafer, H. J. (2003). TEMPO-mediated anodic oxidation of methyl
969 glycosides and 1-methyl and 1-azido disaccharides. *Eur. J. Org. Chem.*(2),
970 351-358.
- 971 Teshirogi, T., Yamamoto, H., Sakamoto, M., & Tonami, H. (1979). Synthesis of
972 6-amino-6-deoxycellulose. *Sen'i Gakkaishi*, 35(12), T525-T529.
- 973 Ying, L. Q., & Gervay-Hague, J. (2003). General methods for the synthesis of
974 glycopyranosyluronic acid azides. *Carbohydrate Research*, 338(9), 835-841.
975