TITLE:

One-Step Synthesis of Dendritic Highly Branched Polystyrenes by Organotellurium-Mediated Copolymerization of Styrene and a Dienyl Telluride Monomer

AUTHOR(S):

Lu, Yangtian; Yamago, Shigeru

CITATION:

Lu, Yangtian ...[et al]. One-Step Synthesis of Dendritic Highly Branched Polystyrenes by Organotellurium-Mediated Copolymerization of Styrene and a Dienyl Telluride Monomer. *Angewandte Chemie International Edition* 2019, 58(12): 3952-3956

ISSUE DATE:

2019-03-18

URL:

<http://hdl.handle.net/2433/237368>

RIGHT:

This is the peer reviewed version of the following article: Y. Lu, S. Yamago, *Angew. Chem. Int. Ed.* 2019, 58, 3952., which has been published in final form at <https://doi.org/10.1002/anie.201814566>. This article may be used for non-commercial purposes in accordance with Wiley Terms and Conditions for Use of Self-Archived Versions; The full-text file will be made open to the public on 18 March 2020 in accordance with publisher's 'Terms and Conditions for Self-Archiving'; この論文は出版社版ではありません。引用の際には出版社版をご確認ご利用ください。 ; This is not the published version. Please cite only the published version.

COMMUNICATION

One-step Synthesis of Dendritic Highly Branched Polystyrenes by Organotellurium-mediated Copolymerization of Styrene and a Dienyl Telluride Monomer

Yangtian Lu,^[a] and Shigeru Yamago^{*[a]}

Abstract: Dendritic highly branched polystyrenes (HB-PSTs) were prepared by a one-step copolymerization of dienyl telluride **6** and St in the presence of organotellurium chain transfer agent **2**. The molecular weight (MW), dendritic generation, and branching density were easily controlled by the ratio of **2** to **6** to St with maintaining monodispersity. The branching efficiency estimated by a deuterium-labeling experiment showed that **6** quantitatively (>95%) served as the branching point. The end group fidelity was high (~90%) as determined by the end group transformation to pyrene-derivative. Intrinsic viscosity of the HP-polystyrenes was significantly lower than that of linear polystyrenes and were easily tuned by the branching number and branching density. The method is compatible of various functional groups and chloro and acetoxy-substituted styrenes were also used as a comonomer. A tadpole block copolymer was also synthesized starting from linear PSt as a macroinitiator.

Highly branched polymers (HBPs) have attracted a great deal of attention due to their unique topological structure associated with characteristic physical properties, such as a lower intrinsic viscosity, lower glass transition temperature, and a larger number of terminal groups than the corresponding linear polymers.^[1] Therefore, HBPs are promising for various applications including lubricants, coatings, drug-delivery vehicles, and catalysts.^[2] However, the development of a practical method for synthesizing structurally controlled HBPs has been a significant challenge.

Among HBPs, dendrimers and dendrons are the most precisely controlled three-dimensional (3D) structures, i.e., molecular weight, dispersity, branching number, and branching density. However, the necessity of a multistep synthesis limits their applications in materials science.^[3] In contrast, hyperbranched polymers can be easily synthesized by one-step methods, such as 1) the step-growth poly-condensation of AB_n monomers and the copolymerization of A₂ and B_n monomers, in which A and B refer to two functional groups that react with each other and n represents the numbers of B groups,^[4] and 2) self-condensing vinyl (co)polymerization (SCV(C)P) and self-condensing ring-opening polymerization using the AB* monomer, in which A and B* refer to olefin and initiating groups, respectively.^[5] Though some 3D structural control could be possible by using special conditions, such as emulsion polymerization to avoid intermolecular reactions^[6] or the slow addition technique to avoid the step-growth mechanism,^[7] no general method to control the 3D structure has been realized. Only two methods have been reported so far for controlling the

3D structure of HBPs by chemical means under the polycondensation of AB₂ monomers. Yokozawa reported the condensation polymerization of an aromatic AB₂ monomer, in which the reactivity of the B₂ group is enhanced after the monomer is incorporated into a polymer.^[8] Gao reported the “click” polymerization of the AB₂ monomer, and catalyst-transfer enables the control.^[9]

a) Previous work: Synthesis of HB-polyacrylates using **2**

b) This work: Synthesis of HB-polystyrene using **6**

a: X = TeMe, b: X = H, c: X = D, d: X = pyrene-TEMPO

c) Schematic structures of ideal polymer products by changing [6]/[2] ratio

Scheme 1. Synthesis of HBPs by radical copolymerization under organotellurium mediated radical polymerization (TERP).

Recently, we reported a new method for controlling the 3D structure of HBPs by radical polymerization,^[10] in which vinyl telluride **1** was copolymerized with acrylate monomers in the presence of an organotellurium chain transfer agent **2** used for organotellurium mediated radical polymerization, TERP (Scheme 1).^[11] While both **1** and **2** have C-Te bonds that potentially generate the corresponding initiating radicals, **1** does not serve as an initiator due to its high *sp*² C-Te bond strength compared to the *sp*³ C-Te bond, such as that in **2**. However, once **1** reacts as a monomer forming a dormant species **3**, both *sp*³ C-Te bonds in

[a] Y. Lu, Prof. Dr. S. Yamago
Institute for Chemical Research, Kyoto University
Uji 611-0011 (Japan)
E-mail: yamago@scl.kyoto-u.ac.jp

Supporting information for this article is given via a link at the end of the document.

COMMUNICATION

3 are activated and generate new polymer chains giving HB polyacrylates **5**. The molecular weight, branching density, and branching number of the resulting polymer were easily controlled by the molar ratio of **1**, **2**, and the acrylate monomer with maintaining a narrow dispersity. This method has significant potential because it is based on radical polymerization, which is the most versatile industrial polymerization method.^[12]

Despite the novelty and synthetic potential, however, controlled syntheses of HBPs with **1** have been limited for polyacrylates and polyacrylamides. For example, styrene (St) is one of the most important monomers, but it does not copolymerize with **1**. The results are reasonable because St does not copolymerize with α -olefin.^[13] Thus, considering the copolymerizability of conjugated dienes with St,^[13] we envisioned that a dienyl telluride would copolymerize with St and induce branching. Herein, we report a new monomer **6**, which copolymerizes with St in the presence of **2** in a one-pot synthesis affording structurally controlled HB-PSt (Scheme 1b).

The difference in the C-Te bond dissociation energies (BDEs) of monomer **6** and possible intermediates **7**, **8**, and **9a** (X = TeMe) were estimated by DFT calculations, in which model compounds **10**, **11**, and **12** were used for **7**, **8**, and **9a**, respectively. The BDE of **6** is 225 kJ mol⁻¹, which is substantially higher than that of **10** (121 kJ mol⁻¹), **11** (108 kJ mol⁻¹), and **12** (118 kJ mol⁻¹). Such an energy difference strongly suggests the selective activation of **10**, **11**, and **12** over **6**. The similar BDEs of **10** and **11** also indicate the spontaneous formation of a branched structure after **6** has reacted.

Figure 1. C-Te bond dissociation energies of the branching monomer **6** and model dormant species.

The requisite **6** was prepared by modifying the reported method.^[15] The synthesis of HB-PSt **9a** with the dendritic generation $N = 3$ was examined by mixing **2**, **6**, and St in a molar ratio of 1/7/500, as the number of branching points is determined by $[\mathbf{6}]_0/[\mathbf{2}]_0 = (2^N - 1)$. The resulting mixture was heated at 100 °C in the presence of 1,4-dimethoxybenzene as an internal standard (Table 1, run 1).^[14] The conversion of **6** and St was monitored by ¹H NMR and showed nearly linear consumptions of both monomers, though **6** was consumed slightly faster than St (Figure 2a). The results clearly confirm the occurrence of statistical copolymerization. The number averaged molecular weight estimated from SEC ($M_{n(\text{SEC})}$) increased with the monomer conversion but deviated significantly from the theoretical values ($M_{n(\text{theo})}$) with the increase in monomer conversion (Figure 2b). This observation is consistent with the formation of a branched polymer, which has a smaller hydrodynamic volume than its linear analog (see below). SEC traces were unimodal throughout the polymerization and shifted to high molecular weight for monomer conversion (Figure 2c), with a dispersity ($\bar{D}$) below 2.02. When the

conversions of **6** and St reached 94% and 71%, respectively, the reaction was quenched by thiophenol, giving terminal-hydrogenated **9b** (X = H).^[15] The absolute molecular weight determined by multiangle laser light scattering (MALLS) ($M_{n(\text{MALLS})} = 36.6 \times 10^3 \text{ g mol}^{-1}$, estimated from Mw determined by MALLS and $\bar{D}$ determined by SEC) was in good agreement with $M_{n(\text{theo})}$ ($37.4 \times 10^3 \text{ g mol}^{-1}$). All the results support the controlled synthesis of HB-PSt.

Figure 2. a) Time evolution of the consumption of **6** (red empty squares) and St (black dots) by ¹H NMR analysis; b) correlation among the St conversion, M_n and $\bar{D}$; and c) time evolution of the SEC traces from 12 to 36 h (Table 1, run 1). d) MHKS plots for linear-PSt ($N = 0$) and **9b**s with $N = 3$ at different molecular weights (runs 1-4).

The generality of this method was investigated at first by the control of molecular weight and branching density $\bar{X}_{br}$ ^[16] by changing the St/**2** ratio to 1000, 250, and 100 while maintaining the **6**/**2** ratio at 7 (Table 1, runs 2-4). Statistical copolymerization took place, and the conversions of **6** and St reached >94% and >73% in all cases after 36-48 hrs. All the $M_{n(\text{SEC})}$ s of the resulting polymers were smaller than the $M_{n(\text{theo})}$ s, and the $M_{n(\text{MALLS})}$ s were in good agreement with the $M_{n(\text{theo})}$ s in all cases (Figure 2d). The SEC traces were unimodal with $\bar{D}$ s of 1.91-2.10. While the dispersity of the PB-PSts was higher than that of linear PSt synthesized by TERP ($\bar{D} < 1.5$),^[11b, 14] the results must be due to the presence of distribution of the branching number and high molecular mass of each branching unit in the HB-PSts.

Mark-Houwink-Kuhn-Sakurada (MHKS) plots of **9b** prepared in runs 1-4 were estimated from the universal curve calibrated by linear PSt standards and revealed the intrinsic viscosity ($[\eta]$) of **9b** to be significantly lower than that of linear PSt. In particular, $[\eta]$ decreased with decreasing $\bar{X}_{br}$. The values of the MHKS constant a of **9b** were 0.32-0.46, which were significantly smaller than that of linear PSt ($a = 0.72$).^[17] All results support the successful synthesis of structurally controlled HB-PSts.

The control of branching number was next examined by changing the **6**/**2** ratio to 3, 15, and 31, which correspond to

COMMUNICATION

dendritic generation $N = 2, 4$, and 5 , respectively, while maintaining the St/2 ratio as 500 (runs 5–7). Controlled copolymerization was observed for $N = 2$ and 4 as judged by unimodal GPC traces, controlled $M_{n(\text{MALLS})}$ s, and $M_{n(\text{SEC})}$ s smaller than $M_{n(\text{theo})}$ s. The dispersity increased to 2.74 for $N = 4$, but it is still acceptable. In contrast, no controlled copolymerization took place for $N = 5$ due to the partial gelation with increasing monomer conversion. This is probably due to the occurrence of intermolecular terminations of the PSt-end radical, which selectively gives coupling products.^[18] The MHKS plots of the HB-PSTs with $N = 2$ –4 (runs 1, 5, and 6) showed a significant decrease in $[\eta]$ with increasing N at the same molecular weight. The MHKS constant a (0.45–0.47) was also significantly smaller than that of linear PSt (see Supporting Info).

Styrenes having functional groups, such as *p*-chloro and *p*-acetoxy styrenes, were also successfully copolymerized with **6** giving the corresponding HB-PSTs (runs 8 and 9). In both cases, the monomer consumptions showed similar behaviors with that of styrene, suggesting the occurrence of statistical copolymerization regardless of the substituent (see Supporting Info). The $M_{n(\text{SEC})}$ s were smaller than the $M_{n(\text{theo})}$ s, while the $M_{n(\text{MALLS})}$ s were close to $M_{n(\text{theo})}$ s in both cases, indicating the successful formation of highly branched structures. Although the dispersities were relatively high, the SEC traces were unimodal throughout the polymerization in both cases suggesting the formation of controlled branching structures (see Supporting Info).

The method is also applicable to the synthesis of a tadpole block copolymer (run 10). A linear-PSt ($M_{n(\text{SEC})} = 18.1 \times 10^3$, $\bar{D} = 1.27$) synthesized from **2** and St was treated with **6** (7 equiv.) and St (325 equiv.) under the same conditions used above (run 10). After >99% and 66% conversion of **6** and St, the linear-PSt-block-HB-PSt copolymer was obtained (with $M_{n(\text{SEC})} = 25.2 \times 10^3$, $\bar{D} = 1.82$, $M_{n(\text{MALLS})} = 38.2 \times 10^3$). The SEC traces shifted to the higher molecular weight region while remaining unimodal, suggesting the successful synthesis of the desired block copolymer (see Supporting Info).

The branching efficiency of **6** was examined by a deuterium labeling experiment. Key radical intermediate **10** formed by the cross-propagation of the polystyrene-end radical ($R = \text{PSt}$) and **6** not only undergoes the desired 1,4-addition giving **11** and finally **9a** but also the undesired 1,2-addition giving **12** and then **13a** (Figure 3a). Since the sp^2 C–Te bond in **13a** cannot generate a propagating radical species under the polymerization conditions, no further branching occurs. The ω -end structures of **9a** and **13a** were analyzed by ^2H NMR after the reduction of the polymer-end group by Bu_3SnD , giving **9c** and **13c** (run 11).^[19] The ^2H NMR of the resulting polymers only showed a single peak at 2.3 ppm corresponding to the benzylic position, and no olefinic signal was detected (Figure 3b). These results clearly suggest the selective occurrence of the desired 1,4-addition, and the branching efficiency was determined to be >95%.

The observed regioselectivity is consistent with the theoretical investigation by DFT calculations at the (U)M062X/[6-31G(d,p)(C,H) + LANL2DZ(Te)] level using a model reaction between **10** ($R = \text{H}$) and styrene (see Supporting Info). The activation energy of the 1,4-addition is 21.5 kJ mol^{-1} , which is 6.8 kJ mol^{-1} lower than that of the 1,2-addition. Furthermore, the formation of the 1,4-addition adduct is highly exothermic with a

formation enthalpy of $-78.8 \text{ kJ mol}^{-1}$, which is 12.1 kJ mol^{-1} more thermodynamically stable than that forming the 1,2-adduct.

Figure 3. a) Possible reaction pathways via 1,2-addition and 1,4-addition of intermediate radical **10**. b) ^2H NMR of the ω -end deuterated HB-PST (run 11). c) Fluorescence spectra of **9ds** with various $\overline{X}_{br}$ at the same concentration of pyrene ($3.0 \times 10^{-4} \text{ mol L}^{-1}$) in DMF and optical image of **9d- $\overline{X}_{br}$ - ∞** (1), **9d- $\overline{X}_{br}$ -25** (2), and **9d- $\overline{X}_{br}$ -12** (3) excited by 365 nm UV lamp.

The chain-end fidelity and further evidence of the branched structure were obtained by the excimer formation via pyrene introduced at the polymer ends. Thus, **9a** with $N = 3$ and different $\overline{X}_{br}$ prepared using 250, 500, and 1000 equiv. of St were photolyzed in the presence of *N*-(2,2,6,6-tetramethylpiperidine-1-oxy-4-yl)-4-(pyren-1-yl)butanamide (pyrene-TEMPO), prepared from 4-(pyren-1-yl)butanoic acid and 4-amino-2,2,6,6-tetramethylpiperidine, at room temperature giving **9d** (see Supporting Info).^[20] The ^1H NMR and UV-vis analyses of the product assuming 100% branching efficiency revealed 86–90% incorporation of the pyrene, which was almost identical to that of the linear PSt (92%). The fluorescence spectrum of **9d** showed a broad peak at 476 nm corresponding to the excimer of pyrene,^[21] and the intensity of exciplex increased with decreasing $\overline{X}_{br}$ (Figure 3c). In contrast, no exciplex emission was observed for the linear PSt. These results clearly demonstrate an increase in the local concentration of pyrene by the decrease in $\overline{X}_{br}$ and support the controlled branching of the synthesized HB-PSTs.

In summary, 3D HB-PSTs were successfully synthesized from the copolymerization of **6** and St with structural control over molecular weight, branching number, branching density, and dispersity. While TERP was used in the current work, the same concept would be applicable to other reversible deactivation (living) radical polymerization methods.

Experimental Section

COMMUNICATION

Synthesis of Z-1-methyltellanyl-3-methyl-1,3-butadiene (**6**).^[22] Dimethyl ditelluride (0.64 ml, 6.0 mmol), and MeOH (10 ml) were charged into a Schlenk tube. NaBH₄ (1.33 g, 35 mmol) was added in small portions at room temperature until the reddish colour was faded. The mixture was stirred at room temperature for 5 mins and transferred into a Schlenk tube with a J Young valve. 2-Methyl-1-buten-3-yne (2.8 ml, 29 mmol) was then added at room temperature, and the resulting mixture was heated at 90 °C for 90 mins after the tube and valve were sealed. The reaction mixture was cooled to room temperature and quenched by addition of deaerated distilled water (5 ml). The resulting mixture was extracted by deaerated hexane (5 ml) for five times. The resulting organic phase was washed by deaerated distilled water (5 ml) for five times. The resulting organic solution was filtered through a plug of MgSO₄, and solvent was removed under vacuum to give a reddish oil (1.83 g, 72% yield containing 3% of regioisomer). The part of the crude product (0.30 g) was purified by preparative SEC giving 0.20 g of **6** as an orange liquid in 66% yield containing 3% of regioisomer. ¹H NMR (CDCl₃) of the major isomer; 1.89 (s, 3H), 1.96 (s, Te satellite with $J_{\text{HTe}} = 22.5$ Hz, 3H), 4.80 (s, 1H), 5.06 (s, 1H), 6.67 (d, $J = 10.5$ Hz, 1H), 6.80 (d, $J = 10.5$ Hz, Te satellite with $J_{\text{HTe}} = 23.9$ Hz, 1H); Several signals could be characterized to the minor regioisomer; 2.00 (dd, $J = 0.68$ Hz, $J = 1.43$ Hz, 3H), 2.00 (s, 3H), 5.12 (m, 1H), 5.17 (m, 1H), 5.52 (d, $J = 0.48$ Hz, 1H), 6.08 (d, $J = 0.48$ Hz, 1H); ¹³C NMR (CDCl₃) -15.72, 22.09, 105.26, 115.05, 138.84, 144.07; EI HRMS Calcd for [M]⁺, 211.9845, found 211.9852; IR (neat) 3076, 2969, 2925, 1622, 1619, 1566, 1453, 1435, 1369, 1330, 1301, 1237, 1224, 1178, 885.

Typical example for the synthesis of HB-PSt **9** (Run 1). A solution of **2** (1.8 μl, 0.010 mmol), **6** (9.5 μl, 0.070 mmol), St (0.57 ml, 5.0 mmol) was heated at 100 °C in the dark for 36 hours. During the polymerization, 10 μl of the reaction mixture was taken as the monitoring sample each time. After the NMR measurement, PhSH (5 μl, 0.049 mmol) was added to the NMR sample solution at room temperature. After 30 mins at this temperature, the solution was used for SEC measurement. The polymerization was quenched by putting the reaction vessel in a freezer at -20 °C for 5 mins. Conversion of **6** (94%) and St (71%) was determined from ¹H NMR spectroscopy. The crude mixture was dissolved in anhydrous THF (5 ml), and PhSH (10 μl, 0.098 mmol) were added at room temperature. The resulting solution was stirred for 2 hours at room temperature and precipitate in MeOH (100 ml) twice to obtain 0.22 g (yield 41%) of product, which was analyzed by the SEC-MALLS ($M_{\text{n(SEC)}} = 20.4 \times 10^3$ g mol⁻¹, $\bar{D} = 1.99$, $M_{\text{n(MALLS)}} = 36.6 \times 10^3$ g mol⁻¹).

Acknowledgements

This work was partly supported by the JSPS KAKENHI Grant No. 16H06352. The computational studies were supported by the Super Computer Laboratory, ICR, KU.

Keywords: Hyperbranched polymer • TERP • dienyI telluride • control radical polymerization

- [1] N. Hadjichristidis, M. Pitsikalis, S. Pispas, H. Iatrou, *Chem. Rev.* **2001**, *101*, 3747-3792; B. I. Voit, A. Lederer, *Chem. Rev.* **2009**, *109*, 5924-5973; D. Yan, C. Gao, H. Frey, John Wiley & Sons, Inc., Hoboken, New Jersey, **2011**.
- [2] M. Jikei, M. Kakimoto, *Prog. Polym. Sci.* **2001**, *26*, 1233-1285; C. Gao, D. Yan, *Prog. Polym. Sci.* **2004**, *29*, 183-275; D. Astruc, F. Chardac, *Chem. Rev.* **2001**, *101*, 2991-3023; U. Boas, M. H. Heegaad, *Chem. Soc. Rev.* **2004**, *33*, 43-63.
- [3] D. A. Tomalia, J. Christensen, U. Boas, *Dendrimers, Dendrons, and Dendritic Polymers*, Cambridge University press, New York, **2012**; D. A. Tomalia, H. Baker, J. Dewald, M. Hall, G. Kallos, S. Martin, J. Roeck, J. Ryder, P. Smith, *Polym. J.* **1985**, *17*, 117-132; S. M. Grayson, J. M. J. Fréchet, *Chem. Rev.* **2001**, *101*, 3819-3867.
- [4] P. J. Flory, *J. Am. Chem. Soc.* **1952**, *74*, 2718-2723; Y. H. Kim, O. W. Webster, *J. Am. Chem. Soc.* **1990**, *112*, 4592-4593.
- [5] J. M. J. Fréchet, M. Henmi, I. Gitsov, S. Aoshima, M. R. Leduc, R. B. Grubbs, *Science* **1995**, *269*, 1080-1083; C. J. Hawker, J. M. J. Fréchet, R. B. Grubbs, J. Dao, *J. Am. Chem. Soc.* **1995**, *117*, 10763-10764; B. Liu, A. Kazlauciusas, J. T. Guthrie, S. Perrier, *Macromolecules* **2005**, *38*, 2131-2136; S. G. Gaynor, S. Edelman, K. Matyjaszewski, *Macromolecules* **1996**, *29*, 1079-1081; K. Sakamoto, T. Aimiya, M. Kira, *Chem. Lett.* **1997**, 1245-1246.
- [6] K. Min, H. Gao, *J. Am. Chem. Soc.* **2012**, *134*, 15680-15683.
- [7] R. Hanselmann, D. Höltter, H. Frey, *Macromolecules* **1998**, *31*, 3790-3801.
- [8] Y. Ohta, S. Fujii, A. Yokoyama, T. Furuyama, M. Uchiyama, T. Yokozawa, *Angew. Chem. Int. Ed.* **2009**, *48*, 5942-5945.
- [9] Y. Shi, R. W. Graff, X. Cao, X. Wang, H. Gao, *Angew. Chem. Int. Ed.* **2015**, *54*, 7631-7635.
- [10] Y. Lu, T. Nemoto, M. Tosaka, S. Yamago, *Nature Commun* **2017**, *8*, 1863.
- [11] S. Yamago, K. Iida, J. Yoshida, *J. Am. Chem. Soc.* **2002**, *124*, 13666-13667.
- [12] S. Yamago, *Chem. Rev.* **2009**, *109*, 5051-5068.
- [13] P. Nesvadba, in *Encyclopedia of Radicals in Chemistry, Biology and Materials* (Eds.: C. Chatgililoglu, A. Studer), John Wiley & Sons, Ltd., **2012**.
- [14] G. Odian, *Principles of Polymerization*, John Wiley & Sons, Inc., Hoboken, New Jersey, **2007**.
- [15] S. M. Barros, M. J. Dabdoub, V. M. B. Dabdoub, J. V. Comasseto, *Organometallics* **1989**, *8*, 1661-1665.
- [16] S. Yamago, K. Iida, J. Yoshida, *J. Am. Chem. Soc.* **2002**, *124*, 2874-2875.
- [17] S. Yamago, A. Matsumoto, *J. Org. Chem.* **2008**, *73*, 7300-7304.
- [18] The branching density $\bar{X}_{\text{br}}$ corresponding to as the average monomer unit between branching points is defined as the following equation: $\bar{X}_{\text{br}} = ([\text{St}]_0 \times \text{Conv. St}) / ([2]_0 \times (2 \times [\text{6}]_0 / [2]_0 - 1) \times \text{Conv. 6})$
- [19] J. Xie, *POLYMER* **1994**, *35*, 2385-2389.
- [20] Y. Nakamura, T. Ogihara, S. Hatano, M. Abe, S. Yamago, *Chem. Eur. J.* **2017**, *23*, 1299-1305; Y. Nakamura, S. Yamago, *Macromolecules* **2015**, *48*, 6450-6456.
- [21] S. Yamago, M. Miyoshi, H. Miyazoe, J. Yoshida, *Angew. Chem. Int. Ed.* **2002**, *41*, 1407-1409.
- [22] S. Yamago, Y. Ukai, A. Matsumoto, Y. Nakamura, *J. Am. Chem. Soc.* **2009**, *131*, 2100-2101.
- [23] S. Farhangi, R. Casier, L. Li, J. L. Thoma, J. Duhamel, *Macromolecules* **2016**, *49*, 9597-9604.

COMMUNICATION

Table 1. Synthesis of structurally controlled HB-PSs by the copolymerization of **2**, **6**, and styrene

Run	[2]/[6]/[St] (<i>N</i>)	Time (h)	Conv. 6 (%) ^[a]	Conv. St (%) ^[b]	$M_{n(\text{Theo})}$ ($\times 10^3$)	$M_{n(\text{SEC})}$ ($\times 10^3$) ^[c]	$M_{n(\text{MALLS})}$ ($\times 10^3$) ^[d]	$\bar{D}$ ^[c]	$\bar{X}_{br}$
1	1/7/500 (3)	36	94	71	37.4	20.4	36.6	1.99	27
2	1/7/1000 (3)	45	99	73	76.6	41.7	81.3	2.10	52
3	1/7/250 (3)	36	94	78	20.6	15.8	27.1	1.91	15
4	1/7/100 (3)	35	99	76	8.7	8.8	11.0	1.91	5
5	1/3/500 (2)	48	99	78	41.0	28.1	44.3	1.69	65
6	1/15/500 (4)	36	94	72	38.7	22.9	42.5	2.74	13
7	1/31/500 (5)	24	87	69	33.5	24.0	N.D. ^[e]	14.3	6
8 ^[f]	1/7/500 (3)	16	99	78	54.8	27.7	55.1	2.68	25
9 ^[g]	1/7/500 (3)	20	99	77	63.1	36.1	77.6	3.25	25
10 ^[h]	1/7/325 (3)	36	99	66	40.6	25.2	38.2	1.82	17
11 ^[i]	1/7/500 (3)	40	99	76	40.2	26.7	48.5	2.07	25

[a] Copolymerization was carried out in bulk at 100 °C, and the resulting cured mixture was treated with PhSH at room temperature in THF. [b] Determined by ¹H NMR. [c] Determined by SEC. [d] Calculated from $M_{w(\text{MALLS})}/\bar{D}$, where $M_{w(\text{MALLS})}$ was determined from MALLS and $\bar{D}$ was determined from SEC. [e] Not determined. [f] *p*-Chlorostyrene was used instead of St. [g] *p*-Acetoxystyrene was used instead of St. [h] Linear PSt ($M_{n(\text{SEC})} = 18.1 \times 10^3$, $\bar{D} = 1.27$) was used instead of **2**. [i] Polymer-end was reduced by Bu₃SnD (16 equiv.) in the presence of AIBN (0.2 equiv.) at 60 °C in toluene.

COMMUNICATION

Layout 1:

COMMUNICATION

Dendritic highly branched polystyrenes (HB-PSTs) were synthesized by a one-step copolymerization of a dieny l telluride and styrene in the presence of organotellurium chain transfer agent. The controlled branched structure was ascertained by several control experiments including structure dependent exciplex formation for the pyrene-functionalized HB-PSTs.

Yangtian Lu and Shigeru Yamago*

Page No. – Page No.

One-step Synthesis of Dendritic Highly Branched Polystyrenes by Organotellurium-mediated Copolymerization of Styrene and a Dieny l Telluride Monomer

Layout 2:

COMMUNICATION

((Insert TOC Graphic here))

Author(s), Corresponding Author(s)*

Page No. – Page No.

Title

Text for Table of Contents