TITLE:

Time-domain measurement of picosecond light-pulse propagation in a two-dimensional photonic crystal-slab waveguide

AUTHOR(S):

Asano, T; Kiyota, K; Kumamoto, D; Song, BS; Noda, S

CITATION:

Asano, T ...[et al]. Time-domain measurement of picosecond light-pulse propagation in a two-dimensional photonic crystal-slab waveguide. APPLIED PHYSICS LETTERS 2004, 84(23): 4690-4692

ISSUE DATE:

2004-06-07

URL:

<http://hdl.handle.net/2433/50164>

RIGHT:

Copyright 2004 American Institute of Physics. This article may be downloaded for personal use only. Any other use requires prior permission of the author and the American Institute of Physics.

Time-domain measurement of picosecond light-pulse propagation in a two-dimensional photonic crystal-slab waveguide

Takashi Asano,^{a)} Kazuaki Kiyota, Daisuke Kumamoto, Bong-Shik Song, and Susumu Noda^{b)}

Department of Electronic Science and Engineering, Kyoto University, Kyoto 615-8510, Japan

(Received 6 January 2004; accepted 15 April 2004; published online 19 May 2004)

The optical properties of line-defect waveguides in two-dimensional photonic crystal slabs are investigated using picosecond light pulses. Time-domain waveforms of the light pulse propagating through the waveguide are successfully observed using an autocorrelation method. The group velocity of the waveguide is directly determined from the group delay time for light pulses reflected back and forth along the waveguide. A small group velocity of one-twentieth the speed of light in vacuum is observed at a frequency near the edge of the waveguide mode. The frequency dependence of the group velocity is also measured, and the group-velocity dispersion is found to be larger than that of normal single-mode optical fibers by a factor of 10^4 – 10^5 . © 2004 American Institute of Physics. [DOI: 10.1063/1.1760224]

A photonic crystal (PC) is an optical material with a periodically varying refractive index, in which a gap in frequency, known as a photonic band gap (PBG), is created in the photonic mode spectrum. It is expected that the control of photons in PCs can be realized by introducing artificial defects that locally disturb the PBG. Line and point defects in PCs have previously been utilized as waveguides^{1–3} and cavities,^{4–8} respectively. Unique characteristics have been predicted, such as a low group velocity in line-defect waveguides and the ability to trap photons for long periods of time in point-defect cavities. Although such characteristics result from the dynamics of light pulses or wavepackets within the defects, experimental results reported so far in this field have been based on measurements using continuous-wave light.^{8,9} Such wavelength-domain measurements are considered to be important, but do not give a fully adequate description of the dynamic behavior of photons in artificial PC defects. Time-domain experiments utilizing considerably shorter light pulses are indispensable for this purpose. For bulk PCs containing no artificial defects, there have been a few reports of the direct measurement of the propagation of light pulses.^{10–14} The change in shape or the time delay of light pulses propagated through three-dimensional^{10,11} and two-dimensional^{12,13} PCs have been investigated. However, there are no reports on the dynamics of wavepackets in artificial PC defects, the study of which is of great importance for the development of practical devices. In this report, we present the results of time-domain measurements of the propagation of picosecond light pulses along line-defect waveguides in a two-dimensional PC slab. The group delay for pulse propagation along the waveguide is successfully obtained, from which the group velocity is directly determined. The group-velocity dispersion is also discussed.

We investigated line-defect waveguides that were introduced in air-bridge-type two-dimensional PC slabs in which air holes form triangular lattice patterns, shown schemati-

cally in Fig. 1(b). Three samples with different lattice constants a (420, 415, and 410 nm) were prepared. Silicon-on-insulator (SOI) substrates were used for the fabrication of samples, which consisted of a 0.25- μm -thick Si slab on top of a 1.5- μm -thick SiO_2 layer formed on a 700- μm -thick Si substrate. Electron-beam lithography and induction-coupled plasma-reactive ion-etching techniques were used to construct the PC patterns on the upper Si slabs. The radius of the air holes was 120 nm and the line-defect waveguide was formed by removing a row of air holes along the Γ - J direction. After the PC patterns had been created, an air-bridge-type structure was formed by removing the underlying SiO_2 layers using a selective wet-etching technique. The samples were then cleaved, giving waveguides with lengths (L) of $\sim 250 \mu\text{m}$. Optical measurements were carried out using a passive mode-lock fiber laser as a light source, in which the time width and center wavelength (λ_c) of the pulses were tunable in the range 0.6–3.0 ps and 1530–1555 nm, respectively. The repetition frequency of the laser was 50 MHz and hence the interval between the output pulses was 20 ns. Light pulses were injected into the waveguide through an objective lens, and pulses emitted from the opposite end of the waveguide were collected by a second objective lens. The collected light was collimated into a single-mode fiber and amplified by an Er-doped fiber amplifier. An optical autocorrelation method using second harmonic generation was utilized to analyze the time-domain waveform of the output light.

Typical results of our measurements are shown in Fig. 1(a); in this case, the lattice constant of the sample is 420 nm, and the time width and λ_c of the input light pulses are 0.6 ps and 1530 nm, respectively. The obtained waveform is symmetric about the time origin as it is detected by the autocorrelation method. The figure shows a pulse train with decreasing intensities and constant intervals of ~ 8.5 ps between pulses, which is much smaller than the pulse interval of the light source (20 ns). The observed pulse train can be explained as follows [see Figs. 1(b) and 1(c)]. The first pulse passes directly through the waveguide, and subsequent

^{a)}Electronic mail: tasano@kuee.kyoto-u.ac.jp

^{b)}Electronic mail: snoda@kuee.kyoto-u.ac.jp

FIG. 1. (a) Autocorrelation signal of a pulse propagating through a sample with lattice constant 420 nm. The center wavelength and time width of the injected light pulse are 1530 nm and 0.6 ps, respectively; (b) schematic drawing of the sample configuration and propagation path of the light pulse; (c) schematic drawing of the relationship between group velocity and the interval of output pulses.

pulses correspond to those that experience additional roundtrips back and forth along the waveguide due to reflection at the waveguide edges. The interval between individual pulses (Δt) represents the group delay for a single roundtrip, and hence the group velocity (v_g) of the waveguide can be directly obtained:

$$v_g = \frac{2l}{\Delta t}. \quad (1)$$

In the case of Fig. 1, in which the observed pulse interval is 8.5 ps and the waveguide length is 250 μm , the group velocity is found to be 0.20 c (c is the speed of light in vacuum).

We next investigated the group velocities for samples with different lattice constants (410–420 nm) by varying the λ_c of the light pulse between 1530 and 1555 nm. The group velocity is plotted in Fig. 2(a) as a function of the center frequency of the light pulse (f), which has been normalized by the unit frequency of the PC (c/a). Here, we have expanded the normalized frequency range of the measurement by employing the fact that the normalized frequency varies with the lattice constant of the PC, even though the frequency of the light is constant.¹⁴ It is clearly seen in the figure that the group velocity rapidly decreases as the frequency is reduced. For comparison, the dispersion curve of the waveguide is theoretically calculated using the three-dimensional finite-difference time domain (FDTD) method. Figure 2(b) shows the calculated dispersion curve and the dotted line in Fig. 2(a) represents the calculated group velocity.

FIG. 2. (a) Measured group velocities as a function of the normalized frequency of the light pulse (open symbols). The theoretically calculated group velocity is also shown for comparison (dotted line); (b) theoretical dispersion curve of the sample waveguide.

ity, which was obtained from the slope of the dispersion curve. Figure 2(a) shows that the experimental and theoretical group velocities agree well with each other. By comparing Figs. 2(a) and 2(b), it is found that the group velocity becomes small as the frequency approaches the lower edge of the waveguide mode. The time-domain waveform for the propagation of the light pulse with the lowest normalized frequency is shown in Fig. 3. It is seen that the light pulse takes up to 32 ps to complete a roundtrip along a waveguide of length 250 μm . The corresponding group velocity is the smallest observed in our series of experiments, reaching a minimum value of 0.05 c .

We have also investigated the group-velocity dispersion (GVD) and the energy loss involved in the propagation. In the case of Fig. 1, in which the frequency of the injected

FIG. 3. Autocorrelation signal of a pulse propagating through a sample with lattice constant 410 nm at a frequency near the lower edge of the waveguide mode. The center wavelength and time width of the injected light pulse are 1555 nm and 3 ps, respectively. The group delay for one roundtrip is 32 ps and the calculated group velocity is as small as 0.05 c .

light pulse is relatively high ($0.275c/a$), the pulse shape is maintained for two roundtrips along a $250\text{ }\mu\text{m}$ waveguide. This implies that the effect of GVD at $f=0.275c/a$ is so small that it cannot be observed under the conditions utilized here (pulse width=0.6 ps and propagation length=1 mm). As the pulse shape is maintained, the decrease in the pulse intensity, which is ~ 10 dB per roundtrip, originates from propagation loss and reflection loss at both ends of the waveguide. The reflection loss calculated by the three-dimensional FDTD method is ~ 4 dB per reflection and, as a result, the propagation loss might be roughly estimated as ~ 2 dB per $500\text{ }\mu\text{m}$. By contrast, in the case of Fig. 3, in which the frequency of the injected light pulse ($f=0.263c/a$) is near the edge of the waveguide mode, the second pulse is broader than the first pulse. Therefore, the deformation of the pulse shape makes it impossible to estimate the intensity loss for the roundtrip. This result implies that GVD has an observable effect on the pulse propagation (pulse width= ~ 3 ps and propagation length= $500\text{ }\mu\text{m}$) when the frequency is near the mode edge. The values of the GVD were also evaluated using the derivative of the experimental dispersion curve shown in Fig. 2(a) and ranged from 1×10^5 ps/nm/km (at $f=0.275c/a$) to 4×10^6 ps/nm/km (at $f=0.263c/a$). The observed GVDs are four to five orders of magnitude larger than those in conventional single-mode optical fibers (typically 17 ps/nm/km at 1550 nm).

In summary, we have studied the propagation of picosecond light pulses along line-defect waveguides in two-dimensional PC slabs. The group velocity of the waveguide has been directly determined from the group-delay time for reflected light pulses that undergo roundtrips back and forth along the waveguide. A small group velocity of $0.05c$ has been observed. The frequency dependence of the group velocity has also been measured and the group velocity disper-

sion was found to be larger than that of conventional single-mode fibers by a factor of 10^4 – 10^5 . Our results indicate that time-domain measurements are useful for the investigation of the dynamic characteristics of artificial defects in PCs. We expect that line-defect waveguides in two-dimensional PC slabs will find applications in the near future as dynamic pulse-control devices such as ultracompact delay lines and dispersion compensators.

This work was partly supported by Core Research for Evolution Science and Technology (CREST), Japan Science and Technology Corporation (JST) and Grant-in-Aids for Scientific Research from the Ministry of Education, Culture, Sport, Science, and Technology of Japan.

- ¹A. Chutinan and S. Noda, Phys. Rev. B **62**, 4488 (2000).
- ²A. Chutinan and S. Noda, Jpn. J. Appl. Phys., Part 1 **39**, 2353 (2000).
- ³S. G. Jonson, P. R. Villeneuve, S. Fan, and J. D. Joannopoulos, Phys. Rev. B **62**, 8212 (2000).
- ⁴S. Noda, A. Chutinan, and M. Imada, Nature (London) **407**, 608 (2000).
- ⁵O. Painter, J. Vuckovic, and A. Scherer, J. Opt. Soc. Am. B **16**, 275 (1999).
- ⁶T. Asano, M. Mochizuki, S. Noda, M. Okano, and M. Imada, J. Lightwave Technol. **21**, 1370 (2003).
- ⁷K. Srinivasan *et al.*, Appl. Phys. Lett. **83**, 1915 (2003).
- ⁸Y. Akahane, T. Asano, B. S. Song, and S. Noda, Nature (London) **425**, 944 (2003).
- ⁹M. Notomi, K. Yamada, A. Shinya, J. Takahashi, C. Takahashi, and I. Yokohama, Phys. Rev. Lett. **87**, 253902 (2001).
- ¹⁰A. Imhof, W. L. Vos, R. Sprik, and A. Lagendijk, Phys. Rev. Lett. **83**, 2942 (1999).
- ¹¹T. Tanaka, S. Noda, A. Chutinan, T. Asano, and N. Yamamoto, J. Opt. Quantum Electron. **34**, 37 (2002).
- ¹²K. Inoue, N. Kawai, Y. Sugimoto, N. Charlsson, N. Ikeda, and K. Asakawa, Phys. Rev. B **65**, 121308(R) (2002).
- ¹³M. C. Netti, C. E. Finlayson, J. J. Baumberg, M. D. B. Charlton, M. E. Zoorob, J. S. Wilkinson, and G. Parker, Appl. Phys. Lett. **81**, 3927 (2002).
- ¹⁴B. S. Song, S. Noda, and T. Asano, Science **300**, 1537 (2003).