

LABORATORY OF CERAMIC CHEMISTRY

Head: Dr. Megumi Tashiro

Researches on ceramic science were taken up by Professor Ikutaro Sawai and his associates in the institute in 1937. The research items first chosen were special glasses (optical glasses) and glass fibers. In 1958, Professor Megumi Tashiro succeeded Professor Sawai as the head of the laboratory. In 1964, the laboratory was officially named as Laboratory of Ceramic Chemistry. The researches made since 1958 deal with basic problems in ceramic science, especially of glasses, glass-ceramics, sintered ceramics and fused ceramics. The main stress has been laid on elucidation of relations between microstructures of these materials and their properties, which would lead to discovery of new ceramics. The major researches made since 1967 are outlined hereunder.

I. Crystallization of Glasses

Mechanism of crystallization of glasses by heat-treatment, and properties of the resultant crystallized glasses were investigated. The compositions of the glasses examined were of the $\text{Li}_2\text{O-SiO}_2$ system and those from which ferroelectric crystals were precipitated. The findings are summarized as follows: a) The extremely high rate of nucleation in the $\text{Li}_2\text{O}\cdot 2\text{SiO}_2$ glass is attributed to the big change in free energy associated with bulk transformation of glass into crystal. b) Mechanical strengths of crystallized glasses and phase-separated glasses increase with decreasing size of the constituent crystal grains and the phase-separated glassy droplets, respectively. The strength of the formers is further increased by the formation of a glassy layer with low thermal expansion coefficients. c) Addition of Al_2O_3 together with SiO_2 , both in limited amounts, respectively, to the components of ferroelectric crystals is effective in producing transparent ferroelectric crystallized glasses. d) Dielectric constant of the PbTiO_3 crystallized glasses show two maxima at $0.15\ \mu\text{m}$ and $25\ \text{nm}$ of size of the constituent PbTiO_3 crystals, which are explained in terms of internal stress and internal electric field, respectively.

II. Crystallization of Melts

Methods for fabrication of inorganic and non-metallic polycrystalline aggregates from their melts by simple casting or unidirectional solidification, and properties of the resultant ingots were investigated. The findings are summarized as follows: a) When a melt is solidified unidirectionally in a crucible, a layer of sintered ceramics or glass-ceramics previously placed or applied on the inner surface of the bottom of the crucible acts as crystal seeds which facilitate growth of a stable crystal phase, leading to the formation of a well-oriented, fine-grained, polycrystalline aggregate. b) Formation of

bubbles in viscous $\text{Li}_2\text{O-SiO}_2$ melts during their solidification can be avoided by lowering the solidification rate to a certain degree. The bubble formation is attributed to the high viscosity of the melts and the big difference in solubility of gas between the melt and crystal phase. c) The $0.7 \text{ NaNbO}_3 \cdot 0.3 \text{ BaTiO}_3$ melt, when solidified unidirectionally at a slow rate, forms a transparent polycrystalline aggregate showing a high electro-optic effect.

III. Structure and Properties of Special Glasses

Glass-forming tendency of aluminate melts containing no simple glass-forming oxide such as SiO_2 , B_2O_3 , P_2O_5 , and GeO_2 , and properties of their glasses were investigated. New families of aluminate glasses showing high infrared transmissions were obtained on a practically useful scale from ternary systems $(\text{Na}_2\text{O}, \text{K}_2\text{O} \text{ or } \text{BaO})\text{-TiO}_2\text{-Al}_2\text{O}_3$ and $(\text{K}_2\text{O} \text{ or } \text{Cs}_2\text{O})\text{-(Nb}_2\text{O}_5 \text{ or } \text{Ta}_2\text{O}_5)\text{-Al}_2\text{O}_3$.

IV. Photochromism of Glassy and Crystalline Oxides

Photochromism of glasses containing silver halides were investigated in relation to their manufacturing conditions and microstructures. Phototropic behavior of alkaline earth tungstates were investigated in relation to their composition. CaWO_4 , SrWO_4 , BaWO_4 , and their solid solutions prepared by solid state reaction showed strong phototropy when doped with a small amount of Bi.

V. Glassy State

The ratio of glass transition temperature to the liquidus temperature was found to be $2/3$ for a wide variety of inorganic glass forming systems including the elements, oxides and sulfides and technologically important systems such as borates and silicates. Coordination number of Al was investigated for a wide variety of oxide glasses by X-ray emission spectroscopy.

VI. High Pressure Effects on Glasses

Powders of Co- or Ag-containing or γ -irradiated glasses were compressed at 10–65 Kbar with a simple squeezer apparatus, and the effects of compression on their light absorption spectra, density, and crystallization tendency were investigated.

VII. Special Ceramics

Addition of glass powders rich in BaO and TiO_2 to BaTiO_3 crystal powders was found to be effective to extend the firing range of BaTiO_3 ceramics, without giving no detrimental effect on their dielectric properties. Adsorption of heavy metal ions in aqueous solutions to powder compacts of various hydroxides such as $\text{Ca}_6\text{Si}_6\text{O}_{17}(\text{OH})_2$ and $\text{CaHPO}_4 \cdot 2\text{H}_2\text{O}$, were investigated in relation to their compositions and microstructures.

Publications

(* indicates an article published in Japanese)

Originals

I. Crystallization of Glasses

1. T. Kanbara and M. Tashiro: Effects of the Addition of Fluorine on the Surface Structure of Glass-Ceramics, *Yogyo-Kyokai-Shi (Journal of the Ceramic Association, Japan)*, **76**, 385 (1968).
2. T. Kokubo, C. Kung, and M. Tashiro: Preparation of Thin Films of BaTiO₃ Glass-Ceramics and Their Dielectric Properties, *ibid.*, **76**, 89 (1968).
3. T. Kokubo: Crystallization of BaO·TiO₂·SiO₂·Al₂O₃ Glasses and Dielectric Properties of Their Crystallized Products, *Bull. Inst. Chem. Res., Kyoto Univ.*, **47**, 572 (1969).
4. T. Kokubo, C. Kung, and M. Tashiro: Crystallization Process of a BaO·TiO₂·Al₂O₃·SiO₂ Glass, *Yogyo-Kyokai-Shi (Journal of the Ceramic Association, Japan)*, **77**, 367 (1969).
5. T. Kokubo, H. Nagao, and M. Tashiro: Crystallization of PbO·TiO₂·Al₂O₃·SiO₂ Glasses and Dielectric Properties of Their Crystallized Products, *ibid.*, **77**, 293 (1969).
6. T. Kokubo and M. Tashiro: Thick-Film Capacitors Made from Glass-Ceramics Containing PbO and TiO₂, *ibid.*, **78**, 58 (1970).
7. S. Sakka: Formation of Tungsten Bronze and Other Electrically Conducting Crystals by Crystallization of Glass Containing Alkali and Tungsten Oxide, *Bull. Inst. Chem. Res., Kyoto Univ.*, **48**, 185 (1970).
8. Y. Utsumi, S. Sakka, and M. Tashiro: Experimental Study on the Bending Strength of Glass in Relation to Liquid-Liquid Phase Separation, *Glass Technol.*, **11**, 80 (1970).
9. Y. Utsumi and S. Sakka: Ball Indentation Strength of Phase Separated Glasses, *ibid.*, **11**, 86 (1970).
10. Y. Utsumi and S. Sakka: Strength of Glass-Ceramics Relative to Crystal Size, *J. Amer. Ceram. Soc.*, **53**, 286 (1970).
11. Y. Utsumi: Microstructure and Strength of Crystallized Glass of Photoceram-Type, *Yogyo-Kyokai-Shi (Journal of the Ceramic Association, Japan)*, **79**, 20 (1971).
12. T. Yamamoto, S. Sakka, and M. Tashiro: In-Situ Observation on Growth of Crystals Out of Glass Surface Caused by Electron Beam Bombardment, *Bull. Inst. Chem. Res., Kyoto Univ.*, **49**, 368 (1971).
13. T. Yamamoto, S. Sakka, and M. Tashiro: Formation of Defects in Glass under Electron Bombardment, *J. Amer. Ceram. Soc.*, **55**, 473 (1972).
14. T. Yamamoto and M. Tashiro: Growth of Crystals Out of Silver-Containing Glass under Electron Bombardment, *Bull. Inst. Chem. Res., Kyoto Univ.*, **50**, 591 (1972).
15. T. Kokubo, K. Yamashita, and M. Tashiro: Effects of Al₂O₃ Addition on Glassy Phase Separation and Crystallization of a PbO·TiO₂·SiO₂ Glass, *ibid.*, **50**, 608 (1972), *Yogyo-Kyokai-Shi (Journal of the Ceramic Association, Japan)*, **81**, 132 (1973)*.
16. T. Yamamoto, K. Haraga, and M. Tashiro: Identification of Crystals Protruding from Surface of Na₂O·3SiO₂ Glass, *ibid.*, **51**, 305 (1973).
17. S. Ito, T. Kokubo, and M. Tashiro: Formation of a Metastable Pyrochlore-Type Crystal in K(Ta, Nb) O₃-Containing Glasses and Its Relation to Structure of the Glasses, *Yogyo-Kyokai-Shi (Journal of the Ceramic Association, Japan)*, **81**, 327 (1973)*.
18. K. Matusita and M. Tashiro: Rate of Crystal Growth in Li₂O·2SiO₂ Glass, *ibid.*, **81**, 500 (1973).
19. K. Matusita and M. Tashiro: Effect of Added Oxides on the Crystallization of Li₂O·2SiO₂ Glasses, *Phys. Chem. Glasses*, **14**, 77 (1973).
20. K. Matusita and M. Tashiro: Rate of Homogeneous Nucleation in Alkali Disilicate Glasses, *J. Non-Crystalline Solids*, **11**, 471 (1973).
21. T. Kokubo and M. Tashiro: Dielectric Properties of Fine-Grained PbTiO₃ Crystals Precipitated in a Glass, *ibid.*, **13**, 328 (1973).
22. K. Matusita, T. Maki, and M. Tashiro: Effect of Added Oxides on the Crystallization and Phase Separation of Li₂O·3SiO₂ Glasses, *Phys. Chem. Glasses*, **15**, 106 (1974).
23. T. Kanbara and M. Tashiro: Factors Governing the Strength of Glass-Ceramics, Proceedings of the 1974 Symposium on Mechanical Behavior of Materials, **1**, 543 (1974).

24. K. Matusita, S. Sakka, T. Maki, and M. Tashiro: Study on Crystallization of Glass by Differential Thermal Analysis. Effect of Added Oxide on Crystallization of $\text{Li}_2\text{O-SiO}_2$ Glasses, *J. Materials Sci.*, **10**, 94 (1975).
25. T. Kokubo and M. Tashiro: Fabrication of Transparent PbTiO_3 Glass-Ceramics, *Bull. Inst. Chem. Res., Kyoto Univ.*, **54**, 301 (1976).
26. S. Ito, T. Kokubo, and M. Tashiro: Crystallization Process of a $\text{LiTaO}_3\text{-Al}_2\text{O}_3\text{-SiO}_2$ Glass, *ibid.*, **54**, 307 (1976).

II. Crystallization of Melts

1. S. Ito, T. Kokubo, and M. Tashiro: Microstructure and Properties of Fused-Cast $\text{NaNbO}_3\text{-BaTiO}_3$ Ceramics, *Bull. Inst. Chem. Res., Kyoto Univ.*, **52**, 641 (1974).

III. Structure and Properties of Special Glasses

1. M. Tashiro, T. Kokubo, M. Nishimura, and S. Ito: Glass Formation in the Systems $(\text{R}_2\text{O or R}'\text{O})\text{-Al}_2\text{O}_3\text{-(TiO}_2, \text{Nb}_2\text{O}_5 \text{ or Ta}_2\text{O}_5)$ and Optical Properties of Their Glasses, Proceedings of Xth International Congress on Glass, **13**, 129 (1974).
2. T. Kokubo, M. Nishimura, and M. Tashiro: Glass Formation in the Systems $(\text{K or Cs})_2\text{O-(Nb or Ta)}_2\text{O}_5\text{-Al}_2\text{O}_3$, *J. Non-Crystalline Solids*, **15**, 329 (1974).
3. T. Kokubo and M. Tashiro: Glass Formation in the Systems $(\text{Na}_2\text{O, K}_2\text{O or BaO})\text{-TiO}_2\text{-Al}_2\text{O}_3$, *Bull. Inst. Chem. Res., Kyoto Univ.*, **52**, 633 (1974).
4. T. Kokubo, M. Nishimura, and M. Tashiro: Infrared Transmission of $(\text{R}_2\text{O or R}'\text{O})\text{-(TiO}_2, \text{Nb}_2\text{O}_5 \text{ or Ta}_2\text{O}_5)\text{-Al}_2\text{O}_3$ Glasses, *J. Non-Crystalline Solids*, **22**, 125 (1976).

IV. Photochromism of Glassy and Crystalline Oxides

1. S. Sakka: Spectra of UV-Induced Absorption in Alkaline-Earth Tungstates, *J. Appl. Phys.*, **39**, 4863 (1968).
2. S. Sakka: Compound Formation in Alkali Tungstate Systems, *Bull. Inst. Chem. Res., Kyoto Univ.*, **46**, 300 (1968).
3. S. Sakka: Coloring of Alkaline Earth Sulfides Induced by Application of Shear, *J. Phys. Chem.*, **73**, 2468 (1969).
4. S. Sakka: Phototropy of Alkaline Earth Tungstates Doped with Bismuth, *J. Amer. Ceram. Soc.*, **52**, 69 (1969).
5. T. Maki and M. Tashiro: Loss of Ag and Cl from Photochromic Glasses during Melting in Various Atmosphere, *Bull. Inst. Chem. Res., Kyoto Univ.*, **50**, 596 (1972).
Yogyo-Kyokai-Shi (Journal of the Ceramic Association, Japan), **80**, 417 (1972).*
6. T. Maki and M. Tashiro: Effects of Various Manufacturing Conditions on Darkening and Fading of Photochromic Glasses, *Bull. Inst. Chem. Res., Kyoto Univ.*, **50**, 621 (1972).

V. Glassy State

1. S. Sakka and J. D. Mackenzie: Relation between Apparent Glass Transition Temperature and Liquidus Temperature for Inorganic Glasses, *J. Non-Crystalline Solids*, **6**, 145 (1971).
2. S. Sakka: Application of X-ray Emission Spectroscopy to the Study of Glass Structure, *Bull. Inst. Chem. Res., Kyoto Univ.*, **49**, 349 (1971).

VI. High Pressure Effects on Glasses

1. M. Tashiro, T. Yamamoto, and S. Sakka: Changes in Light Absorption Spectrum of the Cobalt-Containing Glasses Subjected to High Pressure, *Yogyo-Kyokai-Shi (Journal of the Ceramic Association, Japan)*, **75**, 201 (1967).*
2. T. Yamamoto, S. Sakka, and M. Tashiro: Effect of High Pressure on Precipitation of Silver Colloids in Glass, *ibid.*, **77**, 378 (1969).
3. T. Yamamoto, S. Sakka, and M. Tashiro: Effect of Pressure on Radiation-Induced Color Centers in Silicate Glasses, *J. Non-Crystalline Solids*, **1**, 441 (1969).

4. T. Yamamoto, H. Yamamoto, and S. Sakka: Pressure-Induced Formation of Noble Metal Colloids in Glass, *Phys. Chem. Glasses*, **11**, 11 (1970).

VII. Special Ceramics

1. T. Maki and M. Tashiro: On the Reaction between Petalite Crystals and Lithia-Containing Glass, *Yogyo-Kyokai-Shi (Journal of the Ceramic Association, Japan)*, **75**, 359 (1967).*
2. T. Maki and M. Tashiro: Effects of Addition of Glasses Containing BaO and TiO₂ on Properties of BaTiO₃ Ceramics, *ibid.*, **75**, 278 (1967).*
3. T. Maki: Effects of Addition of Glass Powders Containing BaO and TiO₂ on Temperature Characteristics of Dielectric Properties of BaTiO₃ ceramics, *ibid.*, **76**, 320 (1968).*
4. T. Maki and M. Ohkubo: Separation of Heavy-Metal Ions from Their Water Solutions by Xonotolite Crystal Compacts, *Bull. Inst. Chem. Res., Kyoto Univ.*, **51**, 278 (1973).
5. T. Maki and M. Ohkubo: Adsorptive Properties of Cu (II) on CaHPO₄·2H₂O and MgHPO₄·3H₂O Powders in Aqueous Solutions, *Nippon Kagaku Kaishi*, **1976**, (1) 50.*

Reviews

1. M. Tashiro, T. Yamamoto, and S. Sakka: Effects of High Pressure on the Properties of Glass, *Bull. Inst. Chem. Res., Kyoto Univ.*, **45**, 318 (1967).
2. M. Tashiro: Nucleation and Crystal Growth in Glasses, Proceedings of Eighth International Congress on Glass, 1968, p. 113.
3. T. Kokubo: Preparation and Properties of Glass-Ceramics Containing Ferroelectric Crystals, *Bull. Inst. Chem. Res. Kyoto Univ.*, **47**, 553 (1969).
4. S. Sakka: X-ray K-Emission Spectroscopy and Its Application to Oxides and Silicates, *ibid.*, **47**, 584 (1969).
5. T. Kokubo: Ferroelectric or Ferrimagnetic Ceramics Produced by Crystallization of Glasses, *Denshi Zairyo (Electronic Materials)*, **8**, (9) 68 (1969).*
6. M. Tashiro: The Trend of Glass-Ceramics Research, Ceramic Data Book, 1969, p. 337.*
7. S. Sakka and J. D. Mackenzie: High Pressure Effects on Glass, *J. Non-Crystalline Solids*, **1**, 107 (1969).
8. S. Sakka: Colloids in Glass, Photosensitive and Photochromic Glasses, *Hyomen (Surface)*, **7**, 227 (1969).*
9. T. Yamamoto: Colors of Glasses Produced by Transition Metal Ions, *Kagaku-to-Kogyo (Chemistry and Chemical Industry)*, **43**, 57 (1969).*
10. S. Sakka: New Glasses and Recent Activities in the Field of Glass, *ibid.*, **20**, 1525 (1969).*
11. S. Sakka: Radiation-Induced Color Centers in Glasses, *Bull. Inst. Chem. Res., Kyoto Univ.*, **48**, 53 (1970).
12. S. Sakka: Application of Glass-Ceramics, *Kinzoku (Metals)*, **15**, 49 (1971).*
13. S. Sakka: Phase Separation and Crystallization of Glasses and Their Application, *Kagaku-to-Kogyo (Chemistry and Chemical Industry)*, **45**, 73 (1971).*
14. S. Sakka: Glasses with Heterogeneous Structure, *Oyo-Butsuri (Applied Physics)*, **40**, 63 (1971).*
15. S. Sakka: Inorganic Photochromic Materials; Compounds and Glasses, *Zairyo-Kagaku*, **8**, 191 (1971).*
16. T. Yamamoto: Observation of Glass Surfaces with Electron Microscope, *Hyomen (Surface)*, **10**, 174 (1971).*
17. M. Tashiro: Advances in Glass Materials, *Zairyo (J. Soc. Materials Sci., Japan)*, **21**, 817 (1972).*
18. T. Kokubo, S. Ito, and M. Tashiro: Formation of Metastable Pyrochlore-Type Crystals in Glass, *Bull. Inst. Chem. Res., Kyoto Univ.*, **51**, 315 (1973).
19. T. Kokubo: Surface Structure of Glass-Ceramics, *Hyomen (Surface)*, **12**, 189 (1974).*
20. T. Kokubo: Recent Development of Ferroelectric Glass-Ceramics, *Erekutoronikku Seramikkusu (Electronic Ceramics)*, **6**, 9 (1974).*
21. M. Tashiro: Recent Advances in Glass-Ceramics and Their Application, *Seramikkusu (Ceramics)*, **9**, 382 (1974).*
22. M. Tashiro, T. Kokubo, S. Ito, and M. Arioka: Oriented Polycrystalline Oxide Ceramics Fabricated by Unidirectional Solidification of Their Melts, *Bull. Inst. Chem. Res., Kyoto Univ.*, **53**, 471 (1975).

23. M. Tashiro: Crystallized Glass, *Kotai Butsuri (Solid State Physics)*, **11**, 163 (1976).*

Books

1. T. Kokubo: Dielectric Properties of Glass and Glass-Ceramics, in "Inorganic Materials Science" M. Kunugi, ed., Seibundo Shinkosha, Tokyo, 1972, p. 46.
2. T. Yamamoto: High Pressure Effects on Glasses, in "Inorganic Materials Science" M. Kunugi, ed., Seibundo Shinkosha; Tokyo, 1972, p. 81.
3. S. Sakka: Glass-Ceramics, in "Inorganic Materials Science", M. Kunugi, ed., Seibundo Shinkosha, Tokyo, 1972, p. 125.
4. M. Tashiro: The Future Aspects of Glass and Glass Industry, in "Glass Handbook", S. Sakka *et al.*, ed., Asakura, Tokyo, 1975, p. 16.

Patent

1. M. Tashiro, K. Tamaki, and T. Kokubo: Production Method of Transparent High Permittive Glass-Ceramics, Japanese Pat., 822609 (1976).