

Atomic-Level Pd-Au Alloying and Controllable Hydrogen-Absorption Properties in Size-Controlled Nanoparticles Synthesized by Hydrogen Reduction Method†

Hirokazu Kobayashi, ‡^a Miho Yamauchi§^{ab} and Hiroshi Kitagawa¶^{*a,c}

⁵ Received (in XXX, XXX) Xth XXXXXXXXXX 200X, Accepted Xth XXXXXXXXXX 200X

First published on the web Xth XXXXXXXXXX 200X

DOI: 10.1039/b000000x

Size-controlled atomic-level Pd-Au alloy nanoparticles have been synthesized with a wide range of atomic ratios by a facile method using H₂ gas, and their controllable hydrogen-absorption properties have been studied from hydrogen pressure-composition isotherms and solid-state ²H NMR spectra.

Bimetallic nanoparticles have attracted great interest as magnetic,¹ optical² and catalytic materials³ in many fields of science and technology due to their unique and different properties from those of the monometallic nanoparticles. Pd-Au bimetallic nanoparticles are the significant systems, and they play an important role as the effective catalysts in the direct synthesis of hydrogen peroxide from H₂ and O₂, the hydrodesulfurization of thiophene, the oxidation of alcohols to aldehydes, etc. The enhanced performance can directly be attributed to the synergistic effects of Pd-Au alloying. Due to the wide applications of these Pd-Au catalysts, it is of great interest to study the structure of the bimetallic nanoparticles. Various phase-separated structures such as core/shell⁴ or cluster-in-cluster,⁵ or alloy structures⁶ have been reported. On the other hand, a few reports are there on the solid-solution structured alloy nanoparticles⁷ where Pd and Au are homogeneously mixed at the atomic level. Most of the Pd-Au nanoparticles reported were supported on carbon, activated carbon, or Al₂O₃.^{7a-e} A limited number of the reports regarding on the solid-solution nanoparticles originates from the fact that Pd and Au are hard to mix at the atomic level due to their segregation tendency.⁸ The further development of a facile and effective synthesis method for the size-controllable solid-solution Pd-Au nanoparticles is, therefore, still required for technical applications with high efficiency and performance.

In this study, we have synthesized size-controlled solid-solution alloy nanoparticles where Pd and Au are homogeneously mixed at the atomic level with a wide range of atomic ratios by the successive method using H₂ gas as a reducing agent (Fig. 1). A detailed investigation of the structure of the Pd-Au nanoparticles was carried out using high-resolution transmission electron microscopy (HRTEM), energy dispersive spectra (EDS) and powder X-ray diffractions (XRD). Moreover, we have studied the hydrogen-absorption properties of the Pd-Au nanoparticles from hydrogen pressure-composition (PC) isotherms and solid-state ²H NMR spectra.

Poly(*N*-vinyl-2-pyrrolidone) (PVP)-protected Pd




Fig. 1 Schematic view of as-made Pd-Au solid-solution nanoparticles during the successive reduction. (brown ; Au³⁺, red ; Pd, yellow ; Au)

nanoparticles were prepared from the alcoholic reduction of palladium chloride (PdCl₂) in presence of PVP.⁹ The aqueous solution of tetrachloroauric acid (HAuCl₄) was added to the thus-obtained Pd nanoparticles, with a diameter of 7.1 nm, and the mixture was vigorously stirred under H₂ gas. The atomic ratio of Pd and Au depends on the HAuCl₄ concentration.

The atomic ratios of Pd and Au were determined by ICP-MS spectrometry, and the corresponding particles were characterized, Pd₈₀-Au₂₀, Pd₅₀-Au₅₀ and Pd₂₀-Au₈₀. From the results of TEM measurements (Fig. S1 in ESI†), the corresponding mean diameters of the nanoparticles were 8.4 ± 1.6, 9.1 ± 1.7 and 10.1 ± 2.3 nm, respectively, and the size increased with the additional Au content. From the intensity and position of the surface plasmon resonance peak observed in the ultraviolet-visible absorption spectra for various Pd-Au nanoparticles (Fig. S2 in ESI†), we confirmed the incorporation of Au atoms into Pd nanoparticles. All the Pd-Au nanoparticles showed the XRD patterns from a single face-centered-cubic (fcc) lattice (Figs S3a, S3b in ESI†). The diffraction peaks of Pd-Au nanoparticles shifted linearly to the lower-angle side with increasing Au content in the Pd-Au nanoparticles in agreement with the larger unit cell parameter for Au (Fig. S3c in ESI†). These results strongly support the formation of the atomic-level Pd-Au alloy over the whole inside the particle.

In order to investigate the distribution of Pd and Au atoms inside the nanoparticle, HRTEM images and EDS spectra were measured for the Pd₈₀-Au₂₀ and Pd₅₀-Au₅₀ nanoparticles, as shown Figs 2a, 2c and Figs 2b, 2d, respectively. In general, each domain (phase separation) structure of Pd and Au such as a core/shell type is observable in the HRTEM image due to the difference in contrast between Pd and Au atoms.^{4a-d} The difference of such a contrast is not seen in Figs 2a and 2b,




Fig. 2 HRTEM images and EDS spectra in (a) Pd₈₀-Au₂₀ and (b) Pd₅₀-Au₅₀ nanoparticles. The analysis was performed for the surface part (blue line) and center part (red line) with a 1 nm electron beam.




Fig. 3 PC isotherms of Pd (black), Pd₈₀-Au₂₀ (blue), Pd₅₀-Au₅₀ (green) and Au nanoparticles (red). Isotherms were measured according direction of arrows. H/M shows the number of hydrogen atoms divided by the total number of metal.

change of the hydrogen-absorption properties accompanied by the addition of Au atoms to Pd nanoparticles, PC isotherms of Pd-Au nanoparticles were measured at 303 K. As shown in Fig. 3, only 20 at% replacement of Pd with Au atom results in a reduction of more than half of total amount of hydrogen absorption. With the further addition of Au atoms, the Pd₅₀-Au₅₀ nanoparticles hardly absorbed hydrogen. It may be expected that the hydrogen concentration in the Pd₅₀-Au₅₀ nanoparticles is equal to half that of Pd since Au nanoparticles does not absorb hydrogen. This drastic reduction of hydrogen absorption also indicates that the Pd-Au nanoparticles are not exhibit phase-separation structure but is solid-solution type, where Pd and Au atoms are homogeneously mixed at the atomic level. In the desorption process of Pd and Pd₈₀-Au₂₀ nanoparticles, the curve does not completely return back to the starting point, indicating that some hydrogen atoms are strongly trapped inside the nanoparticles.^{12a}

It is well known that the hydrogen concentration in Pd bulk is linked to the number of holes in the 4d conduction band.¹³ As the 4d conduction band is filled, the hydrogen concentration is reduced. The band-filling effect on hydrogen absorption has been reported in the cases of Pd-Ag^{13a, 14} and Pd-Au¹⁵ bulk alloys. In our experimental results, the decrease of the hydrogen concentrations originates from the filling up




Fig. 4 Solid-state ²H NMR spectra for the samples of Pd-Au nanoparticles at Pd/Au ratios = (d) 80/20, (c) 50/50, (b) 20/80. The samples of (f) ²H₂ gas, (e) Pd and (a) Au nanoparticles were also measured. (g). NMR shift of ²H absorbed inside Pd-Au nanoparticles.

indicating that the structure of the obtained Pd-Au nanoparticles is not phase-separated structure of Pd and Au. In the EDS spectrum for the Pd₈₀-Au₂₀ nanoparticle (Fig. 2c), the X-ray emission lines from both Pd Lα and Au Mα were observed inside one nanoparticle, the difference between the intensity ratios of Pd Lα / Au Mα in the surface and the center parts was not observed. From these results, it was revealed out that the obtained Pd-Au nanoparticles form a homogeneous solid solution alloy, where Pd and Au are mixing at the atomic level. The EDS spectrum for Pd₅₀-Au₅₀ nanoparticles also showed the similar result to the Pd₈₀-Au₂₀ nanoparticle; Pd and Au atoms are homogeneously distributed in the nanoparticle (Fig. 2d). The atomic ratios of Pd and Au for Pd₈₀-Au₂₀ and Pd₅₀-Au₅₀ nanoparticles were estimated by the EDS spectra to be 86 : 14 and 50 : 50, respectively, and are consistent with the molar ratios determined by ICP-MAS. Similarly, the distributions of Pd and Pt have been investigated for several particles and showed the same results that the intensity ratios of Pd Lα / Au Mα were equal. These results indicate the occurrence of Pd-Au alloying at the atomic level. It is well known that H atoms are generated on the surface of Pd metal from H₂ gas and the H atoms are very active (the so-called nascent hydrogen) and therefore have high reducing ability. The formation of Pd-Au alloy is considered to originate not from the replacement between Pd and Au³⁺ but from the hydrogen reduction.¹⁰

It is also well known that hydrogen molecules can easily invade inside metal or alloy lattices as hydrogen atoms, and generate the defect structures with superabundant vacancies, leading to the atomic rearrangements of alloys.¹¹ The formation of the Pd-Au atomic-level alloy can be explained as follows. First, Au³⁺ is reduced near the Pd surface by hydrogen, and the Au atoms diffuse into the inside of Pd nanoparticles owing to hydrogen-induced vacancies or lattice defects over the entire structure. Consequently, Pd and Au are mixing at the atomic level. Hydrogen gas is considered to work as a double reagent to reduce Au³⁺ ions to Au atom and form vacancies, resulting in Pd-Au atomic level alloys.

Studies of hydrogen-absorption properties of the nanoparticles give important information related to the structure and the electronic state.¹² In order to investigate the

of the Pd 4d conduction band due to the addition of Au; 6s-electron of Au donates to the 4d-band of Pd and the numbers of 4d band holes in Pd-Au nanoparticles are decreased. (Fig. S4 in ESI†)

5 Solid-state ^2H NMR measurements were performed to investigate the states of ^2H in Pd-Au nanoparticles (Fig. 4b-d). The sharp line at around 0 ppm and broad absorption lines at a lower field were observed for Pd and Pd-Au nanoparticles with Au contents of 20 and 50 at% (Fig. 4c-e)). In the
10 spectrum for $^2\text{H}_2$ gas, only a sharp line at 3.4 ppm was observed. By comparison of these spectra, it is reasonable to attribute the sharp component in the spectrum of particle to free deuterium gas ($^2\text{H}_2$) and the broad component to absorbed deuterium atoms (^2H) (Fig. 4 inset). Additionally, in the
15 spectra for samples of Pd and Pd₈₀-Au₂₀ nanoparticles, sharp components were observed at upper field in comparison with the peak position of free $^2\text{H}_2$ gas, attributing to deuterium atoms diffusing and/or exchanging with free deuterium on the particles surface (Fig. 4 inset). It should be noted that the
20 broad absorption lines, originating from ^2H inside the Pd-Au lattice, is markedly shifted to upfield linearly with the Au content (Fig. 4g). This shift implies an increase of the electron density around ^2H nuclei, which is caused by change in the occupancies of valence electrons due to hybridization of the
25 valence bands.¹⁶ This linear shift also demonstrates that atomic-level alloying occurs in Pd-Au system and deuterium in the nanoparticles perceives the different potentials depending on the composition of Pd and Au. Deuterium NMR is, therefore, very sensitive and a powerful probe to the
30 electronic state of nanoparticles.

In summary, we have synthesized and characterized size-controlled alloy nanoparticles where Pd and Au are homogeneously mixed at the atomic level with a wide range of ratios by the successive reduction method using H_2 gas. The
35 atomic-level Pd-Au alloying has been confirmed by means of HRTEM, EDS and XRD measurements. Only 20 at% of Au in Pd is sufficient to suppress the hydrogen absorption completely. The amount of hydrogen absorption is controllable at low-concentration alloying with Au and is considered to depend on
40 the band filling of Pd 4d, which is consistent with the observed linear upfield shift of ^2H NMR signal. The atomic-level alloy of variable-size and size-controlled Pd-Au nanoparticles are expected to be useful as effective catalysts for various reactions. The present hydrogen reduction method gives us a big advantage
45 for constructing various size-controlled Pd-Au nanoparticles by changing the size of Pd seeds.

Notes and references

^a Department of Chemistry, Faculty of Science, Kyushu University, Hakozaki 6-10-1, Fukuoka 812-8581, Japan E-mail:

50 kitagawa@kuchem.kyoto-u.ac.jp; Fax: +75-753-4035; Tel: +75-753-4035

^b JST PRESTO, Sanbancho 5, Chiyoda-ku, Tokyo 102-0075, Japan

^c JST CREST, Sanbancho 5, Chiyoda-ku, Tokyo 102-0075, Japan

[†] Current address: Department of Biomedical Engineering,

55 Washington University, St. Louis, Missouri 63130, USA,
[§] Current address: Catalysis Research Center, Hokkaido University, West 10, North 21, Kita-ku, Sapporo 001-0021, Japan

[¶] Current address: Department of Chemistry, Graduate School of Science, Kyoto University, Kitashirakawa-Oiwakecho, Sakyo-ku, Kyoto
60 606-8502, Japan

[†] Electronic Supplementary Information (ESI) available: Experimental details, transmission electron microscopy images, electronic spectra, powder x-ray diffraction, schematic view of the density of states. See DOI: 10.1039/b000000x/

- 65 1 (a) A.-H. Lu, E. L. Salabas, F. Schueth, *Angew. Chem., Int. Ed.* 2007, **46**, 1222; (b) W. S. Seo, et al. *Nat. Mater.* 2006, **5**, 971.
- 2 (a) V. I. Klimov, S. A. Ivanov, J. Nanda, M. Achermann, I. Bezel, J. A. McGuire, A. Piryatinski, *Nature* 2007, **447**, 441; (b) Y. Yang, O. Chen, A. Angerhofer, Y. C. Cao, *J. Am. Chem. Soc.* 2006, **128**, 12428.
- 3 (a) F. Raimondi, G. G. Scherer, R. Koetz, A. Wokaun, *Angew. Chem., Int. Ed.* 2005, **44**, 2190; (b) J. Schulz, A. Roucoux, H. Patin, *Chem. Rev.* 2002, **102**, 3757.
- 75 4 (a) D. Jose, B. R. Jagirdar, *J. Phys. Chem. C* 2008, **112**, 10089; (b) D. Ferrer, A. Torres-Castro, X. Gao, S. Sepúlveda-Guzmán, U. Ortiz-Méndez, M. José-Yacamán, *Nano Lett.* 2007, **7**, 1701; (c) R. Harpeness, A. Gedanken, *Langmuir* 2004, **20**, 3431; (d) C. Kan, W. Cai, C. Li, L. Zhang, H. Hofmeister, *J. Phys. D: Appl. Phys.* 2003, **36**, 1609.
- 80 5 (a) N. Toshima, T. Yonezawa, *New J. Chem.* 1998, 1179. (b) N. Toshima, M. Harada, Y. Yamazaki, K. Asakurat, *J. Phys. Chem.* 1992, **96**, 9927.
- 6 (a) Y. H. Chen, Y. H. Tseng, C. S. Yeh, *Mater. Chem.* 2002, **12**, 1419; (b) P. Landon, P. J. Collier, A. F. Carley, D. Chadwick, A. J. Papworth, A. Burrows, C. J. Kiely, G. J. Hutchings, *Phys. Chem. Chem. Phys.* 2003, **5**, 1917; (c) A. M. Venezia, V. La Parola, V. Nicoli, G. Deganello, *J. Catal.* 2002, **212**, 56; (d) P. Landon, P. J. Collier, A. J. Papworth, C. J. Kiely, G. J. Hutchings, *Chem. Commun.* 2002, 2058; (f) A. Benedetti, L. Bertoldo, P. Canton, G. Goerigk, F. Pinna, P. Riello, S. Polizzi, *Catal. Today* 1999, **49**, 485.
- 90 7 (a) J. A. L-Sanchez, N. Dimitratos, P. Miedziak, E. Ntainjua, J. K. Edwards, D. Morgan, A. F. Carley, R. Tiruvalam, C. J. Kiely, G. J. Hutchings *Phys. Chem. Chem. Phys.*, 2008, **10**, 1921; (b) J. K. Edwards, G. J. Hutchings, *Angew. Chem., Int. Ed.* 2008, **47**, 9192; (c) A. A. Herzing, A. F. Carley, J. K. Edwards, G. J. Hutchings, C. J. Kiely, *Chem. Mater.* 2008, **20**, 1492; (d) D. Wang, A. Villa, F. Porta, L. Prati, D. S. Su, *J. Phys. Chem. C* 2008, **112**, 8617; (e) D. Wang, A. Villa, F. Porta, D. S. Su, L. Prati, *Chem. Commun.* 2006, 1956; (f) X. Teng, Q. Wang, P. Liu, W. Han, A. I. Frenkel, W. Wen, N. Marinkovic, J. C. Hanson, J. A. Rodriguez, *J. Am. Chem. Soc.* 2008, **130**, 1093; (g) S. J. Mejía-Rosales, C. Fernández-Navarro, E. Pérez-Tijerina, D. A. Blom, L. F. Allard, M. José-Yacamán, *J. Phys. Chem. C* 2007, **111**, 1256.
- 105 8 V. I. Pârvulescu, V. Pârvulescu, U. Endruschat, G. Filoti, F. E. Wagner, C. Kübel, R. Richards, *Chem. Eur. J.* 2006, **12**, 2343.
- 9 T. Teranishi, M. Miyake, *Chem. Mater.* 1998, **10**, 594.
- 10 C. H. Chen, L. S. Sarma, J. M. Chen, S. C. Shih, G. R. Wang, D. G. Liu, M. T. Tang, J. F. Lee, B. J. Hwang, *ACS Nano*, 2007, **1**, 114.
- 110 11 (a) Y. Fukai, Y. Ishii, Y. Gotoc, K. Watanabe, *J. Alloys Compd.* 2000, **313**, 121; (b) Y. Fukai, *J. Alloys Compd.* 2003, **356-357**, 263; (c) Y. Fukai, H. Sugimoto, *J. Phys.: Condens. Matter* 2007, **19**, 436201.
- 12 (a) H. Kobayashi, M. Yamauchi, H. Kitagawa, Y. Kubota, K. Kato, M. Takata, *J. Am. Chem. Soc.* 2008, **130**, 1818; (b) H. Kobayashi, M. Yamauchi, H. Kitagawa, Y. Kubota, K. Kato, M. Takata, *J. Am. Chem. Soc.* 2008, **130**, 1828; (c) M. Yamauchi, R. Ikeda, H. Kitagawa, M. Takata, *J. Phys. Chem. C* 2008, **112**, 3294.
- 120 13 (a) E. Wicke, *J. Less-Common Met.* 1984, **101**, 17; (b) D.A. Papaconstantopoulos, B.M. Klein, E.N. Economov, C.C. Boyer, *Phys. Rev. B* 1979, **17**, 141.
- 14 A.K.M. F. Kibria, Y. Sakamoto, *Int. J. Hydrogen Energy* 2000, **25**, 853.
- 15 (a) A. Maeland, T. B. Flanagan, *J. Phys. Chem.* 1965, **69**, 3575. (b) N. Mott, H. Jones, "Theory of Metals and Alloys," Clarendon Press, Oxford 1936.
- 125 16 Nascente, P.A.P.; de Castro, S.G.C.; Landers, R.; Kleiman, G.G. *Phys. Rev.* 1991-II, **43**, 4659.