

Comment on Anomalies in $K_{1-x}Rb_xC_8$

Hiroshi Kamimura

Department of Physics, University of Tokyo

Since Professor Hartmut Zabel explained the characteristic features of anomalies and our mechanism to explain them very clearly in a previous talk, I do not think to repeat them.

The most important point in the mechanism by Akera and Kamimura [1,2,3] is that the elastic anomaly is due to an electronic origin. That is, when the interlayer spacing increases by mixing Rb into C_8K , the upper interlayer band with 3D character comes down towards the Fermi level, and then when a saddle point type van Hove singularity in the density of states of the upper interlayer band touches just at the Fermi level at a certain value of x near $2/3$, the softening in the layer compressional elastic constant C_{33} occurs.

In C_8Rb both the upper and lower interlayer bands lie below the Fermi level. Thus this softening always must occur at a certain value of x , irrespective of whether the dependence of the interlayer spacing on x obeys Vegard's law or not. Only discrepancy between theory and experiment was with regard to the magnitude of the anomaly. The calculated value of anomaly was very small; it was only one third of the observed value previously reported.

However, I am very pleased to hear in Prof. Zabel's talk today that experimental results of C_{33} recently performed on various kinds of samples show less deep anomalies, consistent with our prediction based on the band structure effect.

Acknowledgments I would like to thank Prof. Hartmut Zabel for his valuable discussion on this subject.

1. H. Akera and H. Kamimura, Synthetic Metals 12 (1985) 275
2. H. Akera and H. Kamimura, J. Phys. Soc. Jpn. 55 (1986) 2326
3. H. Kamimura and H. Akera, Proc. Sino-Japan Bilateral Workshop on Statistical Physics and Condensed Matter Theory, ed. Xie Xide (World Scientific, Singapore, 1986) p.16.