

16. Plasticity of Bentonite Clay

Rempei Goto, Nishio Hirai and Tetsuya Hanai

(Goto Laboratory)

It was reported recently that the bentonite clay swelled with water showed peculiar slip bands under compression by two parallel planes [Goto and Hirai: This Bull. 20 48 (1940)].

The direction of the slip bands corresponds to that of the maximum shearing stress which inclines at 45° in the direction of the force applied. When a block of clay is closed in a test box of shearing (a soil testing apparatus) under a vertical (P) and a horizontal shearing force (F) the threshold value (F_0) of the shearing is generally given by the relation

$$F_0 = P \tan \varphi + \nu \dots\dots\dots (1)$$

where φ is the angle of internal friction and ν is the cohesion force. For the bentonite clay swelled with water, it was confirmed that $\varphi=0$ or $F_0=\nu$. And ν changes its value with the amount (W) of water added, holding the relation

$$\nu = Ae^{-bw} \dots\dots\dots (2)$$

where A and b are constants. The analogous relation has been found between the yield value (S_f) of plastics and the amount of the plastizer [Kanamaru: Chem. and Chem. Ind.; 2 246 (1944)]. Thus it is suggested that the threshold value of shearing stress or cohesion force ν , corresponds to the yield value and water acts as a plastizer in this case.

It was found that when the aqueous solution of NaCl or alcohol at various concentration is used as a plastizer instead of water, the relation (2) is somewhat modified. This means the decrease of the hydrophilic property of the bentonite.

17. Sedimentation Volume of Powders

Rempei Goto and Nishio Hirai

(Goto Laboratory)

In order to investigate the lyophilic properties of various powder in benzene, the sedimentation velocity v and its final volume per gram V_1 were observed. v of ZnO_2 , starch or carbon black in benzene begins to decrease steeply at the sedimenting volume V_2 , which is several times as large as V_1 , and when V_2 is reached, the rest angle appears and increases rapidly as sedimentation proceeds. This means that the interaction or the friction between the particles begins to