


24. Studies on the Syntheses of Ethylene Sulfide and Vinyl Thiol Acetate

Kiyohisa Furukawa, Mototeru Nomura and Ryohei Oda

(Oda Laboratory)

I. Synthesis of Ethylene Sulfide.

The authors have synthesized ethylene sulfide (I) with 50-60% yield by some improved method of G.P. 636708 according to the following reaction:




The chief improvements were as follows:

- 1) Ethyl alcohol was used as solvent.
- 2) Reaction temperature was maintained at 1-3°
- 3) Reaction mixture was neutralized by glacial acetic acid.

The polymerisation of (I) occurred easily.

The polymer was a white powder, m. 140-150° and insoluble in ordinary solvents.

II. Synthesis of Vinyl Thiol Acetate.



According to the above course, monothioethyleneglycol-diacetate, b. 98-99°/11mm, was prepared with 76% yield.

The diacetate was converted to vinyl thiol acetate (II), b. 121°, in 10-15% yield by passing the diacetate through a glass packed quartz tube heated to 500° in a CO₂ atmosphere.

In U.S.P. 2378535, it is stated that (II) can be polymerized by heating at 100° with 0.1% Bz₂O₂, or copolymerized with vinyl acetate to an infusible and insoluble resin. We could not however, obtain such a resin under the same conditions, but only a viscous liquid.

Further investigation on the chemical characters of ethylene sulfide is in progress.