

16. Studies on Silicone Resins. (XI) On the Diamagnetic Properties

Kiyoshi Abe and Minoru Toyoda

(Abe Laboratory)

The object of this investigation is to discuss the ionic properties of the siloxane bond in the silicone by a magnetic measurement.

By Quincke method the susceptibilities χ_g of hexamethyldisiloxane and methyl silicone oil are measured.

The measured results indicate diamagnetic properties as follows.

$$\chi_g \text{ of hexamethyldisiloxane} = -0.804 \times 10^{-6}$$

$$\chi_g \text{ of methyl silicone oil} = -0.730 \times 10^{-6}$$

On the other hand, there is so called Pascal's additive law on the diamagnetic properties of organic compounds as shown in the following equation:

$$\chi_M = \sum a \chi_A + \lambda \dots \dots \dots (1)$$

where χ_M is molecular susceptibility, a is the number of atoms in the molecule of susceptibility χ_A and λ is a constitutive constant depending on the nature of the linkage between the atoms.

The diamagnetic susceptibilities of H, C and O in organic compounds are already known experimentally. And the diamagnetic susceptibilities of Si, Si^{+2} can be calculated by the Slater-Angus method,

These experimental and calculated values of the susceptibilities of atoms and ions are put into formula (1), and the ionic properties of a siloxane bond may be discussed.

As the results, on two or three assumptions, ionic properties of a siloxane bond in hexamethyldisiloxane are seemed to be considerably few and its ion is considered as Si^{+1} . By Pauling it is said that the siloxane bond has the ionic character of 50%.

Then the degree of ionic character of a siloxane bond in methyl silicone oil, whose molecular weight measured from its viscosity is 69300, is calculated to be about 60%, and its ion is considered as Si^{+2} .